



PRODUCT/PROCESS CHANGE NOTIFICATION

PCN IPD-PWR/13/8223

Dated 20 Nov 2013

4D4K Front-End Capacity Extension - Ang Mo Kio (Singapore)

Table 1. Change Implementation Schedule

Forecasted implementation date for change	13-Nov-2013
Forecasted availability date of samples for customer	13-Nov-2013
Forecasted date for STMicroelectronics change Qualification Plan results availability	13-Nov-2013
Estimated date of changed product first shipment	15-May-2014

Table 2. Change Identification

Product Identification (Product Family/Commercial Product)	see attached list
Type of change	Waferfab process change
Reason for change	Improve service to Customers
Description of the change	Following the continuous improvement of our service and in order to rationalize and optimize Power MOSFET productivity, this document is announcing that the Production Line 4D4K, currently manufactured in Catania Wafer FAB, will be also produced in 6" wafer dimension in the ST's Ang Mo Kio (Singapore) plant. All commercials from 4D4K Line produced in Ang Mo Kio (Singapore), guarantee the same quality and electrical characteristics as reported in the relevant data sheet. Devices used for qualification are available as Samples.
Change Product Identification	by the digit 6 as front-end code
Manufacturing Location(s)	

DOCUMENT APPROVAL

Name	Function
Mottese, Anna	Marketing Manager
Aleo, Mario-Antonio	Product Manager
Falcone, Giuseppe	Q.A. Manager

Dear Customer,

Please be informed that the production Line 4D4K, currently manufactured in Catania Wafer FAB, will be also produced in 6" wafer dimension in the ST's Ang Mo Kio (Singapore) plant.

Qualification program and results availability:

The reliability test report is provided in attachment to this document.

Samples availability:

Samples of the test vehicle devices will be available on request starting from week 45-2013.

Product Family	Package	Part Number - Test Vehicle
Power MOSFET Transistor	PowerSO-10™	STV270N4F3

Change implementation schedule:

The first shipments will be implemented according to our work in progress and materials availability:

Product Family	1st Shipments
Power MOSFET Transistor	From Week 19-2014

Marking and traceability:

Unless otherwise stated by customer specific requirement, traceability of Commercial Product produced from 4D4K Line, manufactured in 6" wafer dimension in the ST's Ang Mo Kio (Singapore) plant, will be ensured by the digit 6 as front-end code.

Sincerely Yours.



Reliability Report

4D4K Front-End Capacity Extension -
 Ang Mo Kio (Singapore)

General Information		Locations	
Product Lines:	4D4K	Wafer Diffusion Plants:	Ang Mo Kio (Singapore)
Product Families:	Power MOSFET	EWS Plants:	Ang Mo Kio (Singapore)
P/Ns:	STV270N4F3	Assembly plant:	BOUSKOURA (Morocco)
Product Group:	IMS - IPG	Reliability Lab:	IMS-IPG Catania Reliability Lab.
Product division:	Power Transistor Division		
Package:	PowerSO-10™		
Silicon Process techn.:	STripFET™ III		

DOCUMENT INFORMATION

Version	Date	Pages	Prepared by	Approved by	Comment
1.0	November 2013	8	C. Cappello	G. Falcone	First issue

Note: This report is a summary of the reliability trials performed in good faith by STMicroelectronics in order to evaluate the potential reliability risks during the product life using a set of defined test methods.

This report does not imply for STMicroelectronics expressly or implicitly any contractual obligations other than as set forth in STMicroelectronics general terms and conditions of Sale. This report and its contents shall not be disclosed to a third party without previous written agreement from STMicroelectronics.

TABLE OF CONTENTS

1	APPLICABLE AND REFERENCE DOCUMENTS	3
2	GLOSSARY	3
3	RELIABILITY EVALUATION OVERVIEW.....	3
3.1	OBJECTIVES	3
3.2	CONCLUSION	3
4	DEVICE CHARACTERISTICS	4
4.1	DEVICE DESCRIPTION	4
4.2	CONSTRUCTION NOTE	4
5	TESTS RESULTS SUMMARY.....	5
5.1	TEST VEHICLE.....	5
5.2	RELIABILITY TEST PLAN SUMMARY.....	5
6	ANNEXES 6.0.....	8
6.1	TESTS DESCRIPTION	8

1 APPLICABLE AND REFERENCE DOCUMENTS

Document reference	Short description
AEC-Q101	Stress test qualification for automotive grade discrete semiconductors

2 GLOSSARY

DUT	Device Under Test
SS	Sample Size

3 RELIABILITY EVALUATION OVERVIEW

3.1 Objectives

Qualification of the Power MOSFET silicon line 4D4K made in Ang Mo Kio (Singapore) ST-Wafer Fab.

3.2 Conclusion

Qualification Plan requirements have been fulfilled without exception. It is stressed that reliability tests have shown that the devices behave correctly against environmental tests (no failure). Moreover, the stability of electrical parameters during the accelerated tests demonstrates the ruggedness of the products and safe operation, which is consequently expected during their lifetime.

4 DEVICE CHARACTERISTICS

4.1 Device description

N-channel Power MOSFET

4.2 Construction note

D.U.T.: STV270N4F3

LINE: 4D4K

PACKAGE: PowerSO-10™

Wafer/Die fab. information	
Wafer fab manufacturing location	Ang Mo Kio (Singapore)
Technology	STripFET™ III
Die finishing back side	Ti/Ni/Au – Ti/Ni/Ag
Die size	6340 x 4600 μm^2
Metal	Al/Si/Cu
Passivation type	TEOS/NITRIDE

Wafer Testing (EWS) information	
Electrical testing manufacturing location	Ang Mo Kio (Singapore)
Test program	WPIS

Assembly information	
Assembly site	Bouskoura (Morocco)
Package description	PowerSO-10™
Molding compound	Epoxy Resin
Frame material	Copper
Die attach process	Soft Solder
Die attach material	Pb/Sn/Ag
Wire bonding process	Ultrasonic
Wires bonding materials	Gate: Wire Al/Mg 5 mils Source: Ribbon Al 50x8 mils
Lead finishing/bump solder material	Pure Tin

Final testing information	
Testing location	Bouskoura (Morocco)
Tester	IP TEST

5 TESTS RESULTS SUMMARY

5.1 Test vehicle

Lot #	Process/ Package	Product Line	Comments
1	STV270N4F3	4D4K	Power MOSFET
2	STV270N4F3	4D4K	Power MOSFET

5.2 Reliability test plan summary

Lot. 1&2 - D.U.T.: STV270N4F3 LINE: 4D4K PACKAGE: PowerSO-10™

#	Stress (Abrv)	PC	Std ref.	Conditions	Sample Size (S.S.)	Steps	Failure/SS		Family DATA (*)
							Lot 1	Lot 2	
1	TEST		User specification	All qualification parts tested per the requirements of the appropriate device specification.			0/462	0/462	
2	External visual		JESD22 B-101	All devices submitted for testing			0/462	0/462	
3	Parametric Verification		User specification	all parameters according to user specification from -55°C to 175°C	50		0/25	0/25	
4	Pre-conditioning		JESD22 A-113	Dryng 24H @ 125°C Store 168H @ TA=85°C RH=85% IR Reflow @ 245°C 3 times	All devices to be subjected to H3TRB, TC, AC, IOL		0/308	0/308	0/616
5	HTRB	N	JESD22 A-108	TA=175°C ; BIAS=32V TIME=1000 HOURS	154	168H	0/77	0/77	0/154
6	HTGB	N	JESD22 A-108	TA=175°C ; BIAS=20V TIME=1000 HOURS		500H	0/77	0/77	
7	TC	Y	JESD22 A-104	TA=-55°C TO 150°C 1 HOURS / CYCLE TIME=1000CYCLES		1000H	0/77	0/77	
8	AC	Y	JESD22 A-102	TA=121°C ; PA=2ATM TIME=96H	154	168H	0/77	0/77	0/154
9	H3TRB	Y	JESD22 A-101	TA=85°C ; RH=85% BIAS=30V TIME=1000 HOURS	154	500H	0/77	0/77	
10	IOL / TF	Y	MIL-STD-750 Method 1037	ΔTC=105°C Ton / Toff = 3.5min		1000H	0/77	0/77	
						8.6Kcy	0/77	0/77	0/154

11	ESD		AEC Q101-001,002 and 005	CDM / HBM / MM	30		0/30		
12	D.P.A.		AEC-Q101-004 Section 4	Devices after H3TRB - TC	4		0/2	0/2	
13	Thermal Resistance		JESD24-3, 24-4, 24-6 as appropriate		10 pre & post change		0/10		
14	Wire Bond Strength		MIL-STD-750 Method 2037		10 bonds from min of 5 devices		0/50		
15	Bond Shear		AEC-Q101-003		10 bonds from min of 5 devices		0/50		
16	Unclamped Inductive Switching		AEC-Q101-004 Section 2		5		0/5		
17	Dielectric Integrity		AEC-Q101-004 Section 3		5		0/5		
18	Die Shear		MIL-STD-750 Method 2017		5		0/5		

(*) Family data: STripFET™ III Power MOSFET see following tables.

FAMILY DATA

Line: 4D5K

Package..... H²PAK-6

Test	Test description	AEC Q101 S.S.	STM TEST CONDITIONS	STM S.S.	RESULTS Fail/s.s.
H.T.R.B.	High Temperature Reverse Bias	77 x 1 Lot	TA=175°C – BIAS=44V TIME=1000 HOURS	77	0/77
H.T.G.B.	High Temperature Foward Bias	77 x 1 Lot	TA=150°C – BIAS=20V TIME=1000 HOURS	77	0/77
PC	Preconditioning	All devices to be subjected to H3TRB, TC, AC,IOL	DRYNG 24H @ 125°C STORE 168H @ TA=85°C RH=85% Reflow @ 245°C 3 times	308	0/308
H3TRB	Temperature Humidity Reverse Bias	77 x 1 Lot	TA=85°C – RH=85% - BIAS=50V TIME=1000 HOURS	77	0/77
AC	Autoclave	77 x 1 Lot	TA=121°C – PA=2ATM TIME=96h	77	0/77
TC	Temperature Cycling	77 x 1 Lot	-55°C TO 150°C 1 HOURS / CYCLE TIME=1000CYCLES	77	0/77
TF/IOL	Intermittent Operating Life	77 x 1 Lot	T on/off=3.5 min 8.6 Kcycles	77	0/77

Line: 4L63

Package..... PowerFLAT™ 5x6 D.I.

Test	Test description	AEC Q101 S.S.	STM TEST CONDITIONS	STM S.S.	RESULTS Fail/s.s.
H.T.R.B.	High Temperature Reverse Bias	77 x 1 Lot	TA=175°C – BIAS=48V TIME=1000 HOURS	77	0/77
H.T.G.B.	High Temperature Foward Bias	77 x 1 Lot	TA=150°C – BIAS=20V TIME=1000 HOURS	77	0/77
PC	Preconditioning	All devices to be subjected to H3TRB, TC, AC,IOL	DRYNG 24H @ 125°C STORE 168H @ TA=85°C RH=85% Reflow @ 260°C 3 times	308	0/308
H3TRB	Temperature Humidity Reverse Bias	77 x 1 Lot	TA=85°C – RH=85% - BIAS=50V TIME=1000 HOURS	77	0/77
AC	Autoclave	77 x 1 Lot	TA=121°C – PA=2ATM TIME=96h	77	0/77
TC	Temperature Cycling	77 x 1 Lot	-55°C TO 150°C 1 HOURS / CYCLE TIME=1000CYCLES	77	0/77
TF/IOL	Intermittent Operating Life	77 x 1 Lot	T on/off=2 min 15 Kcycles	77	0/77

6 ANNEXES 6.0

6.1 Tests Description

Test name	Description	Purpose
Die Oriented Tests		
HTRB High Temperature Reverse Bias	The device is stressed in static configuration, trying to satisfy as much as possible the following conditions: <ul style="list-style-type: none">• low power dissipation;• max. supply voltage compatible with diffusion process and internal circuitry limitations;	To determine the effects of bias conditions and temperature on solid state devices over time. It simulates the devices' operating condition in an accelerated way. To maximize the electrical field across either reverse-biased junctions or dielectric layers, in order to investigate the failure modes linked to mobile contamination, oxide ageing, layout sensitivity to surface effects.
HTGB High Temperature Forward (Gate) Bias		
Package Oriented Tests		
AC Auto Clave (Pressure Pot)	The device is stored in saturated steam, at fixed and controlled conditions of pressure and temperature.	To investigate corrosion phenomena affecting die or package materials, related to chemical contamination and package hermeticity.
TC Temperature Cycling	The device is submitted to cycled temperature excursions, between a hot and a cold chamber in air atmosphere.	To investigate failure modes related to the thermo-mechanical stress induced by the different thermal expansion of the materials interacting in the die-package system. Typical failure modes are linked to metal displacement, dielectric cracking, molding compound delamination, wire-bonds failure, die-attach layer degradation.
TF / IOL Thermal Fatigue / Intermittent Operating Life	The device is submitted to cycled temperature excursions generated by power cycles (ON/OFF) at T ambient.	To investigate failure modes related to the thermo-mechanical stress induced by the different thermal expansion of the materials interacting in the die-package system. Typical failure modes are linked to metal displacement, dielectric cracking, molding compound delamination, wire-bonds failure, die-attach layer degradation.
H3TRB Temperature Humidity Bias	The device is biased in static configuration minimizing its internal power dissipation, and stored at controlled conditions of ambient temperature and relative humidity.	To evaluate the package moisture resistance with electrical field applied, both electrolytic and galvanic corrosion are put in evidence.
PC Preconditioning	The device is submitted to a typical temperature profile used for surface mounting devices, after a controlled moisture absorption.	To verify that the surface mounting stress does not impact on the subsequent reliability performance. The typical failure modes are "pop corn" effect and delamination.



Public Products List

PCN Title : 4D4K Front-End Capacity Extension - Ang Mo Kio (Singapore)

PCN Reference : IPD-PWR/13/8223

PCN Created on : 20-NOV-2013

Subject : Public Products List

Dear Customer,

Please find below the Standard Public Products List impacted by the change:

ST COMMERCIAL PRODUCT

STB270N4F3
STV270N4F3

STH270N4F3-6

STI270N4F3

Please Read Carefully:

Information in this document is provided solely in connection with ST products. STMicroelectronics NV and its subsidiaries ("ST") reserve the right to make changes, corrections, modifications or improvements, to this document, and the products and services described herein at any time, without notice.

All ST products are sold pursuant to ST's terms and conditions of sale.

Purchasers are solely responsible for the choice, selection and use of the ST products and services described herein, and ST assumes no liability whatsoever relating to the choice, selection or use of the ST products and services described herein.

No license, express or implied, by estoppel or otherwise, to any intellectual property rights is granted under this document. If any part of this document refers to any third party products or services it shall not be deemed a license grant by ST for the use of such third party products or services, or any intellectual property contained therein or considered as a warranty covering the use in any manner whatsoever of such third party products or services or any intellectual property contained therein.

UNLESS OTHERWISE SET FORTH IN ST'S TERMS AND CONDITIONS OF SALE ST DISCLAIMS ANY EXPRESS OR IMPLIED WARRANTY WITH RESPECT TO THE USE AND / OR SALE OF ST PRODUCTS INCLUDING WITHOUT LIMITATION IMPLIED WARRANTIES OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE (AND THEIR EQUIVALENTS UNDER THE LAWS OF ANY JURISDICTION), OR INFRINGEMENT OF ANY PATENT, COPYRIGHT OR OTHER INTELLECTUAL PROPERTY RIGHT.

ST PRODUCTS ARE NOT DESIGNED OR AUTHORIZED FOR USE IN: (A) SAFETY CRITICAL APPLICATIONS SUCH AS LIFE SUPPORTING, ACTIVE IMPLANTED DEVICES OR SYSTEMS WITH PRODUCT FUNCTIONAL SAFETY REQUIREMENTS; (B) AERONAUTIC APPLICATIONS; (C) AUTOMOTIVE APPLICATIONS OR ENVIRONMENTS, AND/OR (D) AEROSPACE APPLICATIONS OR ENVIRONMENTS. WHERE ST PRODUCTS ARE NOT DESIGNED FOR SUCH USE, THE PURCHASER SHALL USE PRODUCTS AT PURCHASER'S SOLE RISK, EVEN IF ST HAS BEEN INFORMED IN WRITING OF SUCH USAGE, UNLESS A PRODUCT IS EXPRESSLY DESIGNATED BY ST AS BEING INTENDED FOR "AUTOMOTIVE, AUTOMOTIVE SAFETY OR MEDICAL" INDUSTRY DOMAINS ACCORDING TO ST PRODUCT DESIGN SPECIFICATIONS. PRODUCTS FORMALLY ESCC, QML OR JAN QUALIFIED ARE DEEMED SUITABLE FOR USE IN AEROSPACE BY THE CORRESPONDING GOVERNMENTAL AGENCY.

RESTRICTIONS OF USE AND CONFIDENTIALITY OBLIGATIONS:

THIS DOCUMENT AND ITS ANNEXES CONTAIN ST PROPRIETARY AND CONFIDENTIAL INFORMATION. THE DISCLOSURE, DISTRIBUTION, PUBLICATION OF WHATSOEVER NATURE OR USE FOR ANY OTHER PURPOSE THAN PROVIDED IN THIS DOCUMENT OF ANY INFORMATION CONTAINED IN THIS DOCUMENT AND ITS ANNEXES IS SUBMITTED TO ST PRIOR EXPRESS AUTHORIZATION. ANY UNAUTHORIZED REVIEW, USE, DISCLOSURE OR DISTRIBUTION OF SUCH INFORMATION IS EXPRESSLY PROHIBITED.

Resale of ST products with provisions different from the statements and/or technical features set forth in this document shall immediately void any warranty granted by ST for the ST product or service described herein and shall not create or extend in any manner whatsoever, any liability of ST.

ST and the ST logo are trademarks or registered trademarks of ST in various countries.

Information in this document supersedes and replaces all information previously supplied.

The ST logo is a registered trademark of STMicroelectronics. All other names are the property of their respective owners

©2013 STMicroelectronics - All rights reserved.

STMicroelectronics group of companies

Australia - Belgium - Brazil - Canada - China - Czech Republic - Finland - France - Germany - Hong Kong - India - Israel - Italy - Japan -
Malaysia - Malta - Morocco - Philippines - Singapore - Spain - Sweden - Switzerland - United Kingdom - United States of America

www.st.com