



12500 TI Boulevard, MS 8640, Dallas, Texas 75243

PCN#20240423000.1

**Qualification of Cu as an alternate bond wire for select devices
Change Notification / Sample Request**

Date: April 23, 2024

To: Mouser PCN

Dear Customer:

This is an announcement of a change to a device that is currently offered by Texas Instruments. The details of this change are on the following pages.

Texas Instruments requires acknowledgement of receipt of this notification within **30** days of the date of this notice. Lack of acknowledgement of this notice within 30 days constitutes acceptance and approval of this change. If samples or additional data are required, requests must be received within **30 days** of this notification.

The changes discussed within this PCN will not take effect any earlier than the proposed first ship date on Page 3 of this notification, unless customer agreement has been reached on an earlier implementation of the change.

This notice does not change the end-of-life status of any product. Should product affected be on a previously issued product withdrawal/discontinuance notice, this notification does not extend the life of that product or change the life time buy offering/discontinuance plan.

For questions regarding this notice or to provide acknowledgement of this PCN, you may contact your local Field Sales Representative or the change management team.

For sample requests or sample related questions, contact your local Field Sales Representative.

Sincerely,

Change Management Team
SC Business Services

20240423000.1
Change Notification / Sample Request
Attachments

Products Affected:

The devices listed on this page are a subset of the complete list of affected devices. According to our records, you have recently purchased these devices. The corresponding customer part number is also listed, if available.

DEVICE	CUSTOMER PART NUMBER
AMC3336DWER	NULL
TPS92691PWP	NULL
TPS92691PWPR	NULL
TPS92692PWPR	NULL
TPS92692PWPT	NULL

Technical details of this Product Change follow on the next page(s).

PCN Number:	20240423000.1			PCN Date:	April 23, 2024								
Title:	Qualification of Cu as an alternate bond wire for select devices												
Customer Contact:	Change Management Team		Dept:	Quality Services									
Proposed 1st Ship Date:	July 22, 2024		Sample Requests accepted until:	May 23, 2024*									
*Sample requests received after May 23, 2024 will not be supported.													
<input type="checkbox"/>	Assembly Site	<input type="checkbox"/>	Design	<input type="checkbox"/>	Wafer Bump Material								
<input checked="" type="checkbox"/>	Assembly Process	<input type="checkbox"/>	Data Sheet	<input type="checkbox"/>	Wafer Bump Process								
<input checked="" type="checkbox"/>	Assembly Materials	<input type="checkbox"/>	Part number change	<input type="checkbox"/>	Wafer Fab Site								
<input type="checkbox"/>	Mechanical Specification	<input type="checkbox"/>	Test Site	<input type="checkbox"/>	Wafer Fab Material								
<input type="checkbox"/>	Packing/Shipping/Labeling	<input type="checkbox"/>	Test Process	<input type="checkbox"/>	Wafer Fab Process								
PCN Details													
Description of Change:													
<p>This PCN is to inform of an alternative bond wire qualification for the devices in the product affected section as follows:</p> <table border="1" style="width: 100%; border-collapse: collapse;"> <thead> <tr> <th style="background-color: #d9e1f2; text-align: center; padding: 5px;">What</th> <th style="background-color: #d9e1f2; text-align: center; padding: 5px;">Current</th> <th style="background-color: #d9e1f2; text-align: center; padding: 5px;">Additional</th> </tr> </thead> <tbody> <tr> <td style="padding: 5px;">Bond wire type, Diameter</td> <td style="padding: 5px;">Au, 0.96 mil</td> <td style="padding: 5px;">Cu, 0.8 mil</td> </tr> </tbody> </table>						What	Current	Additional	Bond wire type, Diameter	Au, 0.96 mil	Cu, 0.8 mil		
What	Current	Additional											
Bond wire type, Diameter	Au, 0.96 mil	Cu, 0.8 mil											
Reason for Change:													
<p>Continuity of supply.</p> <ol style="list-style-type: none"> 1) To align with world technology trends and use wiring with enhanced mechanical and electrical properties 2) Maximize flexibility within our Assembly/Test production sites. 3) Cu is easier to obtain and stock 													
Anticipated impact on Form, Fit, Function, Quality or Reliability (positive / negative):													
None													
Impact on Environmental Ratings													
<p>Checked boxes indicate the status of environmental ratings following implementation of this change. If below boxes are checked, there are no changes to the associated environmental ratings.</p> <table border="1" style="width: 100%; border-collapse: collapse;"> <thead> <tr> <th style="background-color: #d9e1f2; text-align: center; padding: 5px;">RoHS</th> <th style="background-color: #d9e1f2; text-align: center; padding: 5px;">REACH</th> <th style="background-color: #d9e1f2; text-align: center; padding: 5px;">Green Status</th> <th style="background-color: #d9e1f2; text-align: center; padding: 5px;">IEC 62474</th> </tr> </thead> <tbody> <tr> <td style="padding: 5px;"><input checked="" type="checkbox"/> No Change</td> </tr> </tbody> </table>						RoHS	REACH	Green Status	IEC 62474	<input checked="" type="checkbox"/> No Change			
RoHS	REACH	Green Status	IEC 62474										
<input checked="" type="checkbox"/> No Change	<input checked="" type="checkbox"/> No Change	<input checked="" type="checkbox"/> No Change	<input checked="" type="checkbox"/> No Change										
Changes to product identification resulting from this PCN:													
None													
Product Affected:													
TPS92691PWP	TPS92692PWP	TPS92692PWPT											
TPS92691PWPR	TPS92692PWPR	AMC3336DWER											

Automotive Qualification Summary
 (As per AEC-Q100 Rev. J and JEDEC Guidelines)
 Approve Date 31-March-2024

Product Attributes

Attributes		Qual Device: TPS92691QPWPRQ1	QBS Process Reference: S0704038C0PLPR	QBS Package Reference: TPS61175QPWPRQ1	QBS Package Reference: SN2HA08CQPWPRQ1	QBS Product Reference: TPS92691QPWPQ1
Automotive Grade Level		Grade 1	Grade 1	Grade 1	Grade 1	Grade 1
Operating Temp Range (C)		-40 to 125	-40 to 125	-40 to 125	-40 to 125	-40 to 125
Product Function		Power Management	Power Management	Power Management	Power Management	Power Management
Wafer Fab Supplier		RFAB	RFAB	MH8	RFAB	RFAB
Assembly Site		TAI	TAI	TAI	TAI	TAI
Package Group		TSSOP	QFP	TSSOP	TSSOP	TSSOP
Package Designator		PWP	PLP	PWP	PWP	PWP
Pin Count		16	128	14	24	16

QBS: Qual By Similarity

Qual Device TPS92691QPWPRQ1 is qualified at MSL3 260C

Qualification Results

Data Displayed as: Number of lots / Total sample size / Total failed

Type	#	Test Spec	Min Lot Qty	SS / Lot	Test Name	Condition	Duration	Qual Device: TPS92691QPWPRQ1	QBS Process Reference: S0704038C0PLPR	QBS Package Reference: TPS61175QPWPRQ1	QBS Package Reference: SN2HA08CQPWPRQ1	QBS Product Reference: TPS92691QPWPQ1
Test Group A - Accelerated Environment Stress Tests												
PC	A1	JEDEC J-STD-020 JESD22-A113	3	77	Preconditioning	MSL3 260C	-	1/All/0	3/All/0	3/All/0	3/All/0	1/All/0
HAST	A2	JEDEC JESD22-A110	3	77	Biased HAST	130C/85%RH	96 Hours	1/77/0	3/231/0	-	3/231/0	1/77/0
AC/UHAST	A3	JEDEC JESD22-A102/JEDEC JESD22-A118	3	77	Autoclave	121C/15psig	96 Hours	-	3/231/0	-	3/231/0	1/77/0
AC/UHAST	A3	JEDEC JESD22-A102/JEDEC JESD22-A118	3	77	Unbiased HAST	130C/85%RH	96 Hours	1/77/0	-	3/231/0	-	-
TC	A4	JEDEC JESD22-A104 and Appendix 3	3	77	Temperature Cycle	-55C/150C	1000 Cycles	1/77/0	-	-	-	-
TC	A4	JEDEC JESD22-A104 and Appendix 3	3	77	Temperature Cycle	-65C/150C	500 Cycles	-	3/236/0	3/231/0	3/231/0	1/77/0
TC-BP	A4	MIL-STD883 Method 2011	1	5	Post Temp Cycle Bond Pull	-	-	-	1/5/0	1/5/0	-	1/5/0
PTC	A5	JEDEC JESD22-A105	1	45	PTC	-40/125C	1000 Cycles	-	3/45/0	-	1/45/0	-
HTSL	A6	JEDEC JESD22-A103	1	45	High Temperature Storage Life	150C	1000 Hours	1/45/0	-	1/45/0	3/135/0	-
HTSL	A6	JEDEC JESD22-A103	1	45	High Temperature Storage Life	175C	500 Hours	-	3/45/0	-	-	-
Test Group B - Accelerated Lifetime Simulation Tests												
HTOL	B1	JEDEC JESD22-A108	3	77	Life Test	125C	1000 Hours	-	3/231/0	-	-	-
HTOL	B1	JEDEC JESD22-A108	3	77	Life Test	150C	300 Hours	-	-	-	-	3/231/0

Type	#	Test Spec	Min Lot Qty	SS / Lot	Test Name	Condition	Duration	Qual Device: TPS92691QPWPRQ1	QBS Process Reference: S0704038C0PLPR	QBS Package Reference: TPS61175QPWPRQ1	QBS Package Reference: SN2HA08CQPWPRQ1	QBS Product Reference: TPS92691QPWPRQ1
HTOL	B1	JEDEC JESD22-A108	3	77	Life Test	150C	408 Hours	-	-	-	3/231/0	-
ELFR	B2	AEC Q100-008	3	800	Early Life Failure Rate	125C	48 Hours	-	3/2400/0	-	-	-
ELFR	B2	AEC Q100-008	3	800	Early Life Failure Rate	150C	24 Hours	-	-	-	3/2400/0	-
EDR	B3	AEC Q100-005	1	77	NVM Endurance, Data Retention, and Op Life	Per QSS-009-018	1 Step	-	-	-	3/231/0	-
Test Group C - Package Assembly Integrity Tests												
WBS	C1	AEC Q100-001	1	30	Wire Bond Shear	Minimum of 5 devices, 30 wires Cpk>1.67	Wires	1/30/0	-	3/90/0	3/90/0	1/30/0
WBP	C2	MIL-STD883 Method 2011	1	30	Wire Bond Pull	Minimum of 5 devices, 30 wires Cpk>1.67	Wires	1/30/0	-	3/90/0	3/90/0	1/30/0
SD	C3	JEDEC J-STD-002	1	15	PB-Free Solderability	>95% Lead Coverage	-	-	-	-	1/15/0	1/15/0
PD	C4	JEDEC JESD22-B100 and B108	3	10	Physical Dimensions	Cpk>1.67	-	-	-	3/30/0	3/30/0	1/10/0
Test Group D - Die Fabrication Reliability Tests												
EM	D1	JESD61	-	-	Electromigration	-	-	Completed Per Process Technology Requirements	Completed Per Process Technology Requirements	Completed Per Process Technology Requirements	Completed Per Process Technology Requirements	Completed Per Process Technology Requirements
TDDB	D2	JESD35	-	-	Time Dependent Dielectric Breakdown	-	-	Completed Per Process Technology Requirements	Completed Per Process Technology Requirements	Completed Per Process Technology Requirements	Completed Per Process Technology Requirements	Completed Per Process Technology Requirements
HCI	D3	JESD60 & 28	-	-	Hot Carrier Injection	-	-	Completed Per Process Technology Requirements	Completed Per Process Technology Requirements	Completed Per Process Technology Requirements	Completed Per Process Technology Requirements	Completed Per Process Technology Requirements
BTI	D4	-	-	-	Bias Temperature Instability	-	-	Completed Per Process Technology Requirements	Completed Per Process Technology Requirements	Completed Per Process Technology Requirements	Completed Per Process Technology Requirements	Completed Per Process Technology Requirements
SM	D5	-	-	-	Stress Migration	-	-	Completed Per Process Technology Requirements	Completed Per Process Technology Requirements	Completed Per Process Technology Requirements	Completed Per Process Technology Requirements	Completed Per Process Technology Requirements
Test Group E - Electrical Verification Tests												
ESD	E2	AEC Q100-002	1	3	ESD HBM	-	2000 Volts	-	1/3/0	-	3/9/0	1/3/0
ESD	E3	AEC Q100-011	1	3	ESD CDM	-	500 Volts	-	1/3/0	-	3/9/0	1/3/0
LU	E4	AEC Q100-004	1	6	Latch-Up	Per AEC Q100-004	-	-	1/6/0	-	1/6/0	1/3/0
ED	E5	AEC Q100-009	3	30	Electrical Distributions	Cpk>1.67 Room, hot, and cold	-	-	3/90/0	-	3/90/0	3/90/0

Preconditioning was performed for Autoclave, Unbiased HAST, THB/Biased HAST, Temperature Cycle, Thermal Shock, and HTSL, as applicable

The following are equivalent HTOL options based on an activation energy of 0.7eV : 125C/1k Hours, 140C/480 Hours, 150C/300 Hours, and 155C/240 Hours

The following are equivalent HTSL options based on an activation energy of 0.7eV : 150C/1k Hours, and 170C/420 Hours

The following are equivalent Temp Cycle options per JESD47 : -55C/125C/700 Cycles and -65C/150C/500 Cycles

Ambient Operating Temperature by Automotive Grade Level:

Grade 0 (or E): -40C to +150C

Grade 1 (or Q): -40C to +125C

Grade 2 (or T): -40C to +105C

Grade 3 (or I) : -40C to +85C

E1 (TEST): Electrical test temperatures of Qual samples (High temperature according to Grade level):

Room/Hot/Cold : HTOL, ED

Room/Hot : THB / HAST, TC / PTC, HTSL, ELFR, ESD & LU

Room : AC/uHAST

Quality and Environmental data is available at TI's external Web site: <http://www.ti.com/>

Qualification Report
 Automotive New Product Qualification Summary
 (As per AEC-Q100 and JEDEC Guidelines)
 Approve Date 07-September -2023

Qualification Results
 Data Displayed as: Number of lots / Total sample size / Total failed

Type	#	Test Spec	Min Lot Qty	SS / Lot	Test Name	Condition	Duration	Qual Device: AMC3311QDWQRQ1	QBS Process Reference: ISO7741FQDWQ1	QBS Process Reference: AMC1305M25QDWQRQ1	QBS Product Reference: AMC131M03QDFMRQ1
Test Group A - Accelerated Environment Stress Tests											
PC	A1	JEDEC J-STD-020 JESD22-A113	3	77	Preconditioning	MSL3 260C	-	No Fails	-	-	No Fails
HAST	A2	JEDEC JESD22-A110	3	77	Biased HAST	110C/85%RH	264 Hours	1/77/0	-	-	3/231/0
AC/UHAST	A3	JEDEC JESD22-A102/JEDEC JESD22-A118	3	77	Unbiased HAST	110C/85%RH	264 Hours	3/231/0	-	-	3/231/0
TC	A4	JEDEC JESD22-A104 and Appendix 3	3	77	Temperature Cycle	-65C/150C	500 Cycles	3/231/0	-	-	3/231/0
TC-BP	A4	MIL-STD883 Method 2011	1	5	Post Temp Cycle Bond Pull	-	-	1/5/0	-	-	-
HTSL	A6	JEDEC JESD22-A103	1	45	High Temperature Storage Life	175C	500 Hours	1/45/0	-	-	3/135/0
Test Group B - Accelerated Lifetime Simulation Tests											
HTOL	B1	JEDEC JESD22-A108	1	77	Life Test	125C	1000 Hours	-	3/231/0	-	-
HTOL	B1	JEDEC JESD22-A108	1	77	Life Test	150C	408 Hours	-	-	3/231/0	-
ELFR	B2	AEC Q100-008	1	77	Early Life Failure Rate	125C	48 Hours	-	3/2400/0	-	-
ELFR	B2	AEC Q100-008	1	77	Early Life Failure Rate	150C	24 Hours	-	-	3/2400/0	-
Test Group C - Package Assembly Integrity Tests											
WBS	C1	AEC Q100-001	1	30	Wire Bond Shear	Minimum of 5 devices, 30 wires Cpk>1.67	Wires	3/90/0	-	-	-
WBP	C2	MIL-STD883 Method 2011	1	30	Wire Bond Pull	Minimum of 5 devices, 30 wires Cpk>1.67	Wires	3/90/0	-	-	-
SD	C3	JEDEC J-STD-002	1	15	PB Solderability	>95% Lead Coverage	-	-	-	-	1/15/0
SD	C3	JEDEC J-STD-002	1	15	PB-Free Solderability	>95% Lead Coverage	-	-	-	-	1/15/0
PD	C4	JEDEC JESD22-B100 and B108	1	10	Physical Dimensions	Cpk>1.67	-	3/30/0	-	-	-

Test Group D - Die Fabrication Reliability Tests											
EM	D1	JESD61	-	-	Electromigration	-	-	Completed Per Process Technology Requirements			
TDDB	D2	JESD35	-	-	Time Dependent Dielectric Breakdown	-	-	Completed Per Process Technology Requirements			
HCI	D3	JESD60 & 28	-	-	Hot Carrier Injection	-	-	Completed Per Process Technology Requirements			
NBTI	D4	-	-	-	Negative Bias Temperature Instability	-	-	Completed Per Process Technology Requirements			
SM	D5	-	-	-	Stress Migration	-	-	Completed Per Process Technology Requirements			

Test Group E - Electrical Verification Tests											
ESD	E2	AEC Q100-002	1	3	ESD HBM	-	2000 Volts	1/3/0	-	-	-
ESD	E3	AEC Q100-011	1	3	ESD CDM	-	500 Volts	1/3/0	-	-	-
LU	E4	AEC Q100-004	1	6	Latch-Up	Per AEC Q100-004	-	1/6/0	-	-	-
ED	E5	AEC Q100-009	3	30	Electrical Distributions	Cpk>1.67 Room, hot, and cold	-	3/90/0	-	-	-

QBS: Qual By Similarity

Qual Device AMC3311QDWERQ1 is qualified at MSL3 260C

Preconditioning was performed for Autoclave, Unbiased HAST, THB/Biased HAST, Temperature Cycle, Thermal Shock, and HTSL, as applicable

The following are equivalent HTOL options based on an activation energy of 0.7eV : 125C/1k Hours, 140C/480 Hours, 150C/300 Hours, and 155C/240 Hours

The following are equivalent HTSL options based on an activation energy of 0.7eV : 150C/1k Hours, and 170C/420 Hours

The following are equivalent Temp Cycle options per JESD47 : -55C/125C/700 Cycles and -65C/150C/500 Cycles

Ambient Operating Temperature by Automotive Grade Level:

Grade 0 (or E): -40C to +150C

Grade 1 (or Q): -40C to +125C

Grade 2 (or T): -40C to +105C

Grade 3 (or I) : -40C to +85C

E1 (TEST): Electrical test temperatures of Qual samples (High temperature according to Grade level):

Room/Hot/Cold : HTOL, ED

Room/Hot : THB / HAST, TC / PTC, HTSL, ELFR, ESD & LU

Room : AC/uHAST

Quality and Environmental data is available at TI's external Web site: <http://www.ti.com/>

Qualification Report
 Automotive New Product Qualification Summary
 (As per AEC-Q100 and JEDEC Guidelines)
 Approve Date 26-September -2023

Qualification Results
 Data Displayed as: Number of lots / Total sample size / Total failed

Type	#	Test Spec	Min Lot Qty	SS / Lot	Test Name	Condition	Duration	Qual Device: AMC3330QDWERQ1	QBS Process Reference: INA215AQDCKBQ1	QBS Process Reference: ISO7741LEQDWBQ1	QBS Product Reference: AMC3330QDWERQ1	QBS Package Reference: ISOW7741LEQDWEQ1	QBS Package Reference: TPS31050QDWBZBQ1	QBS Package Reference: UCC12051QDVERQ1
Test Group A - Accelerated Environment Stress Tests														
PC	A1	JEDEC J-STD-020 JEDEC22-A113	3	77	Preconditioning	MSL3 260C	-	3/0/0	-	-	3/0/0	-	3/0/0	3/0/0
HAST	A2	JEDEC JEDEC22-A110	3	77	Biased HAST	110C/85%RH	264 Hours	-	-	-	-	-	3/231/0	3/231/0
HAST	A2	JEDEC JEDEC22-A110	3	77	Biased HAST	130C/85%RH	96 Hours	-	-	-	3/231/0	-	-	-
AC/UHAST	A3	JEDEC JEDEC22-A102/JEDEC JEDEC22-A118	3	77	Unbiased HAST	110C/85%RH	264 Hours	1/20/0	-	-	1/77/0	-	3/231/0	-
AC/UHAST	A3	JEDEC JEDEC22-A102/JEDEC JEDEC22-A118	3	77	Unbiased HAST	130C/85%RH	96 Hours	-	-	-	3/231/1 ¹	-	-	-
TC	A4	JEDEC JEDEC22-A104 and Appendix 3	3	77	Temperature Cycle	-55C/150C	1000 Cycles	-	-	-	-	-	3/231/0	-
TC	A4	JEDEC JEDEC22-A104 and Appendix 3	3	77	Temperature Cycle	-65C/150C	500 Cycles	1/20/0	-	-	3/231/0	-	-	3/231/0
TC-BP	A4	MIL-STD883 Method 2011	1	5	Post Temp Cycle Bond Pull	-	-	-	-	-	3/15/0	-	1/5/0	3/15/0
HTSL	A6	JEDEC JEDEC22-A103	1	45	High Temperature Storage Life	170C	620 Hours	-	-	-	3/231/0	-	-	-
Test Group B - Accelerated Lifetime Simulation Tests														
HTOL	B1	JEDEC JEDEC22-A108	3	77	Life Test	125C	1000 Hours	-	3/231/0	3/231/0	-	-	-	-
HTOL	B1	JEDEC JEDEC22-A108	3	77	Life Test	150C	408 Hours	-	-	-	3/231/3 ²	-	-	-
ELFR	B2	AEC Q100-008	3	800	Early Life Failure Rate	125C	48 Hours	-	3/2400/0	3/2400/0	-	-	-	-
Test Group C - Package Assembly Integrity Tests														
WBS	C1	AEC Q100-001	1	30	Wire Bond Shear	Minimum of 5 devices, 30 wires Cpk>1.67	Wires	1/30/0	-	-	3/90/0	3/90/0	-	-
WBP	C2	MIL-STD883 Method 2011	1	30	Wire Bond Pull	Minimum of 5 devices, 30 wires Cpk>1.67	Wires	1/30/0	-	-	3/90/0	3/90/0	-	-
SD	C3	JEDEC J-STD-002	1	15	PB Solderability	>95% Lead Coverage	-	-	-	-	1/15/0	1/15/0	-	-
SD	C3	JEDEC J-STD-002	1	15	PB-Free Solderability	>95% Lead Coverage	-	-	-	-	1/15/0	1/15/0	-	-
PD	C4	JEDEC JEDEC22-B100 and B108	3	10	Physical Dimensions	Cpk>1.67	-	1/10/0	-	-	-	2/20/0	-	-
Test Group D - Die Fabrication Reliability Tests														
EM	D1	JESD61	-	-	Electromigration	-	-	Completed Per Process Technology Requirements	Completed Per Process Technology Requirements	Completed Per Process Technology Requirements	Completed Per Process Technology Requirements	Completed Per Process Technology Requirements	Completed Per Process Technology Requirements	Completed Per Process Technology Requirements

Type	#	Test Spec	Min Lot Qty	SS / Lot	Test Name	Condition	Duration	Qual Device: AMC3330QDWERQ1	QBS Process Reference: INA215AQDCRK01	QBS Process Reference: IS0741FQDWQ1	QBS Product Reference: AMC3301QDWERQ1	QBS Package Reference: ISOW7841FQDWQ1	QBS Package Reference: TPS1050QDWZRO1	QBS Package Reference: UCC120510QDVERQ1
TDDB	D2	JESD35	-	-	Time Dependent Dielectric Breakdown	-	-	Completed Per Process Technology Requirements	Completed Per Process Technology Requirements	Completed Per Process Technology Requirements	Completed Per Process Technology Requirements	Completed Per Process Technology Requirements	Completed Per Process Technology Requirements	Completed Per Process Technology Requirements
HCI	D3	JESD60 & 28	-	-	Hot Carrier Injection	-	-	Completed Per Process Technology Requirements	Completed Per Process Technology Requirements	Completed Per Process Technology Requirements	Completed Per Process Technology Requirements	Completed Per Process Technology Requirements	Completed Per Process Technology Requirements	Completed Per Process Technology Requirements
NBTI	D4	-	-	-	Negative Bias Temperature Instability	-	-	Completed Per Process Technology Requirements	Completed Per Process Technology Requirements	Completed Per Process Technology Requirements	Completed Per Process Technology Requirements	Completed Per Process Technology Requirements	Completed Per Process Technology Requirements	Completed Per Process Technology Requirements
SM	D5	-	-	-	Stress Migration	-	-	Completed Per Process Technology Requirements	Completed Per Process Technology Requirements	Completed Per Process Technology Requirements	Completed Per Process Technology Requirements	Completed Per Process Technology Requirements	Completed Per Process Technology Requirements	Completed Per Process Technology Requirements
Test Group E - Electrical Verification Tests														
ESD	E2	AEC Q100-002	1	3	ESD HBM	-	3500 Volts	-	-	-	-	3/9/0	-	-
ESD	E3	AEC Q100-011	1	3	ESD CDM	-	1500 Volts	-	-	-	-	3/9/0	-	-
LU	E4	AEC Q100-004	1	6	Latch-Up	Per AEC Q100-004	-	-	-	-	-	3/18/0	-	-
ED	E5	AEC Q100-009	3	30	Electrical Distributions	Cpk>1.67 Room, hot, and cold	-	-	-	-	-	3/9/0	-	-

QBS: Qual By Similarity

Qual Device [AMC3330QDWERQ1](#) is qualified at MSL3 260C

Preconditioning was performed for Autoclave, Unbiased HAST, THB/Biased HAST, Temperature Cycle, Thermal Shock, and HTSL, as applicable

The following are equivalent HTOL options based on an activation energy of 0.7eV : 125C/1k Hours, 140C/480 Hours, 150C/300 Hours, and 155C/240 Hours

The following are equivalent HTSL options based on an activation energy of 0.7eV : 150C/1k Hours, and 170C/420 Hours

The following are equivalent Temp Cycle options per JESD47 : -55C/125C/700 Cycles and -65C/150C/500 Cycles

Ambient Operating Temperature by Automotive Grade Level:

Grade 0 (or E): -40C to +150C

Grade 1 (or Q): -40C to +125C

Grade 2 (or T): -40C to +105C

Grade 3 (or I) : -40C to +85C

E1 (TEST): Electrical test temperatures of Qual samples (High temperature according to Grade level):

Room/Hot/Cold : HTOL, ED

Room/Hot : THB / HAST, TC / PTC, HTSL, ELFR, ESD & LU

Room : AC/uHAST

Quality and Environmental data is available at TI's external Web site: <http://www.ti.com/>

For questions regarding this notice, e-mails can be sent to Change Management team or your local Field Sales Representative.

IMPORTANT NOTICE AND DISCLAIMER

TI PROVIDES TECHNICAL AND RELIABILITY DATA (INCLUDING DATASHEETS), DESIGN RESOURCES (INCLUDING REFERENCE DESIGNS), APPLICATION OR OTHER DESIGN ADVICE, WEB TOOLS, SAFETY INFORMATION, AND OTHER RESOURCES "AS IS" AND WITH ALL FAULTS, AND DISCLAIMS ALL WARRANTIES, EXPRESS AND IMPLIED, INCLUDING WITHOUT LIMITATION ANY IMPLIED WARRANTIES OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE OR NON-INFRINGEMENT OF THIRD PARTY INTELLECTUAL PROPERTY RIGHTS.

These resources are intended for skilled developers designing with TI products. You are solely responsible for (1) selecting the appropriate TI products for your application, (2) designing, validating and testing your application, and (3) ensuring your application meets applicable standards, and any other safety, security, or other requirements. These resources are subject to change without notice. TI grants you permission to use these resources only for development of an application that uses the TI products described in the resource. Other reproduction and display of these resources is prohibited. No license is granted to any other TI intellectual property right or to any third party intellectual property right. TI disclaims responsibility for,

and you will fully indemnify TI and its representatives against, any claims, damages, costs, losses, and liabilities arising out of your use of these resources.

TI's products are provided subject to TI's Terms of Sale (www.ti.com/legal/termsofsale.html) or other applicable terms available either on ti.com or provided in conjunction with such TI products. TI's provision of these resources does not expand or otherwise alter TI's applicable warranties or warranty disclaimers for TI products.