



**12500 TI Boulevard, MS 8640, Dallas, Texas 75243**

**PCN# 20260414000.2**  
**Qualification of MIHO using qualified Process Technology and**  
**additional Assembly site for select devices**  
**Change Notification / Sample Request**

**Date:** April 14, 2026  
**To:** MOUSER PCN

Dear Customer:

This is an announcement of a change to a device that is currently offered by Texas Instruments. The details of this change are on the following pages.

Texas Instruments requires acknowledgement of receipt of this notification within 60 days of the date of this notice. Lack of acknowledgement of this notice within 60 days constitutes acceptance and approval of this change. If samples or additional data are required, requests must be received within 60 days of this notification.

The changes discussed within this PCN will not take effect any earlier than the proposed first ship date on Page 3 of this notification, unless customer agreement has been reached on an earlier implementation of the change.

This notice does not change the end-of-life status of any product. Should product affected be on a previously issued product withdrawal/discontinuance notice, this notification does not extend the life of that product or change the life time buy offering/discontinuance plan.

For questions regarding this notice or to provide acknowledgement of this PCN, you may contact your local Field Sales Representative or the change management team.

For sample requests or sample related questions, contact your local Field Sales Representative.

TI values customer engagement and feedback related to TI changes. Customers should contact TI if there are questions or concerns regarding a change notification.

Sincerely,

Change Management Team  
SC Business Services

**20260414000.2**  
**Change Notification / Sample Request**  
**Attachments**

**Products Affected:**

The devices listed on this page are a subset of the complete list of affected devices. According to our records, you have recently purchased these devices. The corresponding customer part number is also listed, if available.

<b>DEVICE</b>	<b>CUSTOMER PART NUMBER</b>
ESD501DPYRQ1	NULL
ESD601DPYRQ1	NULL
TPD1E05U06QDPYRQ1	NULL

Technical details of this Product Change follow on the next page(s).

<b>PCN Number:</b>	20260414000.2			<b>PCN Date:</b>	April 14, 2026
<b>Title:</b>	Qualification of MIHO using qualified Process Technology and additional Assembly site for select devices				
<b>Customer Contact:</b>	Change Management team		<b>Dept:</b>	Quality Services	
<b>Proposed 1<sup>st</sup> Ship Date:</b>	October 11, 2026		<b>Sample requests accepted until:</b>	June 13, 2026	
<b>*Sample requests received after June 13, 2026 will not be supported.</b>					
<b>Change Type:</b>					
<input checked="" type="checkbox"/>	Assembly Site	<input type="checkbox"/>	Design	<input type="checkbox"/>	Wafer Bump Material
<input type="checkbox"/>	Assembly Process	<input type="checkbox"/>	Data Sheet	<input type="checkbox"/>	Wafer Bump Process
<input checked="" type="checkbox"/>	Assembly Materials	<input type="checkbox"/>	Part number change	<input checked="" type="checkbox"/>	Wafer Fab Site
<input type="checkbox"/>	Mechanical Specification	<input type="checkbox"/>	Test Site	<input type="checkbox"/>	Wafer Fab Material
<input checked="" type="checkbox"/>	Packing/Shipping/Labeling	<input type="checkbox"/>	Test Process	<input type="checkbox"/>	Wafer Fab Process
<b>PCN Details</b>					
<b>Description of Change:</b>					
Texas Instruments is pleased to announce the addition of MIHO using the VDIODE qualified process technology and Clark Assembly site for the devices listed below.					
<b>Current Fab Site</b>			<b>Additional Fab Site</b>		
<b>Current Fab Site</b>	<b>Process</b>	<b>Wafer Diameter</b>	<b>Additional Fab Site</b>	<b>Process</b>	<b>Wafer Diameter</b>
CFAB	VDIODE	200 mm	MIHO	VDIODE	200 mm
Construction differences are as follows:					
	<b>Current</b>	<b>Additional</b>			
<b>Assembly Site</b>	<b>CARZAT</b>	<b>CLARK</b>			
Lead Finish	NiPdAuAg	NiPdAu			
Mount compound	SID# 438933	4207123			
Bond Wire	Au 0.8mil	Cu 0.8mil			
Marking	Pin 1 Stripe	Pin 1 Dot			
Qual details are provided in the Qual Data Section.					
<b>Reason for Change:</b>					
Continuity Supply					
<b>Anticipated impact on Form, Fit, Function, Quality or Reliability (positive / negative):</b>					
Review the updated Standard Data Packet for more details on the changes.					
<b>Impact on Environmental Ratings:</b>					
Checked boxes indicate the status of environmental ratings following implementation of this change. If the boxes below are checked, there are no changes to the associated environmental ratings.					
<b>RoHS</b>	<b>REACH</b>	<b>Green Status</b>	<b>IEC 62474</b>		
<input checked="" type="checkbox"/> No Change	<input checked="" type="checkbox"/> No Change	<input checked="" type="checkbox"/> No Change	<input checked="" type="checkbox"/> No Change		

**Changes to product identification resulting from this PCN:**

**Fab Site Information:**

Chip Site	Chip Site Origin Code (20L)	Chip Site Country Code (21L)	Chip Site City
CFAB	CU3	CHN	CHENGDU
<b>MIHO</b>	<b>MH8</b>	<b>JPN</b>	<b>Ibaraki</b>

**Assembly Site Information:**

Assembly Site	Assembly Site Origin (22L)	Assembly Country Code (23L)	Assembly City
CARZ	CSZ	CHN	Jiangsu
<b>Clark -AT</b>	<b>QAB</b>	<b>PHL</b>	<b>Pampanga</b>

Sample product shipping label (not actual product label):

(1P) SN74LS07NSR  
 (Q) 2000 (D) 0336  
 (31T) LOT: 3959047MLA  
 (4W) TKY (1T) 7523483SI2  
 (P)  
 (2P) REV: (V) 0033317  
 (20L) CSO: SHE (21L) CCO: USA  
 (22L) ASO: MLA (23L) ACO: MYS

**Product Affected: FAB and A/T**

ESD501DPYRQ1 ESD601DPYRQ1

**Product Affected: A/T only**

TPD1E05U06QDPYRQ1

**Qualification Data**

**Automotive New Product Qualification Summary  
(As per AEC-Q101 and JEDEC Guidelines)**

**2DPY Offload to Clark  
Approve Date 23-February-2026**

**Product Attributes**

Attributes	Qual Device: ESD601DPYRQ1	QBS Process Reference: ESD2CAN24DBZRQ1	QBS Process Reference: TSM24CADBZRQ1
Automotive Grade Level	Grade 1	Grade 1	Grade 0
Operating Temp Range (C)	-40 to 125	-40 to 125	-55 to 150
Product Function	Interface	Interface	Interface
Wafer Fab Supplier	CFAB	CFAB	CFAB
Assembly Site	CLARK-AT	PHI	PHI
Package Group	UXQFN	SOT	SOT
Package Designator	DPY	DBZ	DBZ
Pin Count	2	3	3

- QBS: Qual By Similarity, also known as Generic Data
- Qual Device ESD601DPYRQ1 is qualified at MSL1260C

**Qualification Results**

**Data Displayed as: Number of lots / Total sample size / Total failed**

Type	#	Test Spec	Min Lot Qty	SS / Lot	Test Name	Condition	Duration	Qual Device: ESD601DPYRQ1	QBS Process Reference: ESD2CAN24DBZRQ1	QBS Process Reference: TSM24CADBZRQ1
<b>Test Group A - Accelerated Environment Stress Tests</b>										
PC	A1	JEDEC J-STD-020 JESD22-A113	-	0	Preconditioning	MSL1260C	1 Step	3/00	3/00	3/30
HAST	A2	JEDEC JESD22-A110	3	77	Bias ed HAST	130C85%RH	96 Hours	3/23/0	3/23/0	3/23/0
HAST	A2.1	JEDEC JESD22-A110	3	77	Bias ed HAST	130C85%RH	96 Hours	3/23/0	3/23/0	3/23/0
HAST	A2.1.2	-	3	1	Cross Section, post bHAST, 1X	Poststress cross section	Completed	3/30	3/30	3/30

Type	#	Test Spec	Min Lot Qty	SS / Lot	Test Name	Condition	Duration	Qual Device: ESD601DPYRQ1	QBS Process Reference: ESD2CAN24DBZRQ1	QBS Process Reference: TSM24CADBZRQ1
HAST	A2.1.3	-	3	3	Wire Bond Shear, post bHAST, 1X	Poststress	-	3/90	3/90	3/90
HAST	A2.1.4	-	3	3	Bond Pull over Stitch, post bHAST, 1X	Poststress	-	3/90	3/90	3/90
HAST	A2.1.5	-	3	3	Bond Pull over Ball, post bHAST, 1X	Poststress	-	3/90	3/90	3/90
HAST	A2.2	JEDEC JESD22-A110	3	70	Bias ed HAST	130C85%RH	192 Hours	3/23/0	3/23/0	3/23/0
HAST	A2.2.1	-	3	22	SAM Analysis, post bHAST, 2X	Review for delamination	Completed	3/650	3/650	3/650
HAST	A2.2.2	-	3	1	Cross Section, post bHAST, 2X	Poststress cross section	Completed	3/30	3/30	3/30
HAST	A2.2.3	-	3	3	Wire Bond Shear, post bHAST, 2X	Poststress	-	3/90	3/90	3/90
HAST	A2.2.4	-	3	3	Bond Pull over Stitch, post bHAST, 2X	Poststress	-	3/90	3/90	3/90
HAST	A2.2.5	-	3	3	Bond Pull over Ball, post bHAST, 2X	Poststress	-	3/90	3/90	3/90
AC/UHAST	A3	JEDEC JESD22-A118	3	77	Unbias ed HAST	130C85%RH	96 Hours	3/23/0	3/23/0	3/23/0
TC	A4.1	JEDEC JESD22-A104 and Appendix 3	3	77	Temperature Cycle	-65C/150C	500 Cycles	3/23/0	3/23/0	3/23/0
TC	A4.1.1	-	3	22	SAM Analysis, post TC, 1X	Review for delamination	Completed	3/650	3/650	3/650
TC	A4.1.2	-	3	1	Cross Section, post TC, 1X	Poststress cross section	Completed	3/30	3/30	3/30
TC	A4.1.3	-	3	3	Wire Bond Shear, post TC, 1X	Poststress	-	3/90	3/90	3/90
TC	A4.1.4	-	3	3	Bond Pull over Stitch, post TC, 1X	Poststress	-	3/90	3/90	3/90
TC	A4.1.5	-	3	3	Bond Pull over Ball, post TC, 1X	Poststress	-	3/90	3/90	3/90
TC	A4.2	JEDEC JESD22-A104 and Appendix 3	3	70	Temperature Cycle	-65C/150C	1000 Cycles	3/23/0	3/23/0	3/23/0
TC	A4.2.1	-	3	22	SAM Analysis, post TC, 2X	Review for delamination	Completed	3/650	3/650	3/650
TC	A4.2.2	-	3	1	Cross Section, post TC, 2X	Poststress cross section	Completed	3/30	3/30	3/30
TC	A4.2.3	-	3	3	Wire Bond Shear, post TC, 2X	Poststress	-	3/90	3/90	3/90
TC	A4.2.4	-	3	3	Bond Pull over Stitch, post TC, 2X	Poststress	-	3/90	3/90	3/90
TC	A4.2.5	-	3	3	Bond Pull over Ball, post TC, 2X	Poststress	-	3/90	3/90	3/90
<b>Test Group B - Accelerated Lifetime Simulation Tests</b>										
HTRB	B1.1	MIL-STD-750-1	3	77	High Temperature Reverse Bias	125C	1000 Hours	-	3/23/0	-
HTRB	B1.1	MIL-STD-750-1	3	77	High Temperature Reverse Bias	150C	1000 Hours	-	-	1/770
HTRB	B1.2	MIL-STD-750-1	3	77	High Temperature Reverse Bias	125C	2000 Hours	-	3/23/0	-

Type	#	Test Spec	Min Lot Qty	SS / Lot	Test Name	Condition	Duration	Qual Device: ESD601DPYRQ1	QBS Process Reference: ESD2CAN24DBZRQ1	QBS Process Reference: TSM24CADBZRQ1
HTRB	B12	MIL-STD-750-1	3	77	High Temperature Reverse Bias	150C	2000 Hours	-	-	1/770
Test Group C - Package Assembly Integrity Tests										
DPA	C2	JESD22-B100	-	30	Physical Dimensions	Cpk>1.67	1 Step	3/900	3/900	1/300
WBP	C3	MIL-STD-750-2	-	10	Wire Bond Pull	Minimum of 5 devices, 30 wires Cpk>1.67	1 Step	3/500	3/300	1/100
WBS	C4	AEC-Q101-003	-	10	Wire Bond Shear	Minimum of 5 devices, 30 wires Cpk>1.67	1 Step	3/300	3/300	1/100
DS	C5	MIL-STD-750-2	-	5	Die Shear	MIL-STD-750-2 Method 2017	1 Step	3/150	3/150	1/50
RSH	C8	JESD22-B107	-	30	Solder Heat	260C, 10 seconds	1 Step	1/500	1/300	1/300
SD	C10	JEDEC J-STD-002	-	15	PB-Free Solderability	Precondition w/155C Dry Bake (4 hrs +/- 15 minutes)	1 Step	1/150	1/100	-
Test Group D - Die Fabrication Reliability Tests										
Test Group E - Electrical Verification Tests										
EV	E0	JESD22-B101	3	1000	Visual/Mechanical	Per JESD22 B-101	1 Step	3/50000	3/30000	-
ESD	E3	AEC-Q101-001	3	10	ESD HBM	Room Temp	2000 Volts	1/100	1/800	1/100
ESD	E4	AEC-Q101-005	3	10	ESD CDM	Room Temp	750 Volts	1/100	-	1/100
Type	#	Test Spec	Min Lot Qty	SS / Lot	Test Name	Condition	Duration	Qual Device	QBS Reference	QBS Reference

- Preconditioning was performed for Autoclave, Unbiased HAST, THB/Biased HAST, Temperature Cycle, Thermal Shock, HTSL, and IOL, as applicable
- Passing results reflects hft analysis per Q101 requirement

#### Ambient Operating Temperature by Automotive Grade Level:

- Grade 0 (or E): -40C to +150C
- Grade 1 (or Q): -40C to +125C
- Grade 2 (or T): -40C to +105C
- Grade 3 (or I): -40C to +85C

E1 (TEST): Electrical test temperatures of Qual samples (High temperature according to Grade level):

- Room/Hot/Cold: HTRB, ED
- Room/Hot: THB / HAST, TC / PTC, HTSL, ELFR, ESD & LU
- Room: ACuHAST

Quality and Environmental data is available at TI's external Web site: <http://www.ti.com/>

TI Qualification ID: R-CHG-2409-083

### Automotive Qualification Summary (As per AEC and JEDEC Guidelines)

Q006 DPY at CLARK  
Approve Date 23-FEBRUARY -2026

Attributes	Qual Device: ESD601DPYRQ1	QBS Process Reference: ESD2CAN24DBZRQ1	QBS Process Reference: TSM24CADBZRQ1
Automotive Grade Level	Grade 1	Grade 1	Grade 0
Operating Temp Range (C)	-40 to 125	-40 to 125	-55 to 150
Product Function	Interface	Interface	Interface
Wafer Fab Supplier	CFAB	CFAB	CFAB
Assembly Site	CLARK-AT	PHI	PHI
Package Group	UXQFN	SOT	SOT
Package Designator	DPY	DBZ	DBZ
Pin Count	2	3	3

### Qualification Results

Data Displayed as: Number of lots / Total sample size / Total failed

Type	#	Test Spec	Min Lot Qty	SS / Lot	Test Name	Condition	Duration	Qual Device: <a href="#">ESD601DPYRQ1</a>	QBS Reference: <a href="#">ESD2CAN24DBZRQ1</a>	QBS Reference: <a href="#">TSM24CADBZRQ1</a>
<b>Test Group A - Accelerated Environment Stress Tests</b>										
PC	A1	JEDEC J-STD-020 JESD22-A113	3	77	Preconditioning	MSL1 260C	-	3/0/0	3/0/0	3/3/0
PC	A1.1	-	3	22	SAM Precon Pre	Review for delamination	-	3/66/0	3/66/0	3/66/0
PC	A1.2	-	3	22	SAM Precon Post	Review for delamination	-	3/66/0	3/66/0	3/66/0
HAST	A2.1	JEDEC JESD22-A110	3	77	Biased HAST	130C/85%RH	96 Hours	3/231/0	3/231/0	3/231/0
HAST	A2.1.2	-	3	1	Cross Section, post bHAST, 1X	Post stress cross section	Completed	3/3/0	3/3/0	3/3/0
HAST	A2.1.3	-	3	3	Wire Bond Shear, post bHAST, 1X	Post stress	-	3/9/0	3/9/0	3/9/0
HAST	A2.1.4	-	3	3	Bond Pull over Stitch, post bHAST, 1X	Post stress	-	3/9/0	3/9/0	3/9/0
HAST	A2.1.5	-	3	3	Bond Pull over Ball, post bHAST, 1X	Post stress	-	3/9/0	3/9/0	3/9/0
HAST	A2.2	JEDEC JESD22-A110	3	70	Biased HAST	130C/85%RH	192 Hours	3/231/0	3/231/0	3/231/0
HAST	A2.2.1	-	3	22	SAM Analysis, post bHAST, 2X	Review for delamination	Completed	3/66/0	3/66/0	3/66/0
HAST	A2.2.2	-	3	1	Cross Section, post bHAST, 2X	Post stress cross section	Completed	3/3/0	3/3/0	3/3/0
HAST	A2.2.3	-	3	3	Wire Bond Shear, post bHAST, 2X	Post stress	-	3/9/0	3/9/0	3/9/0
HAST	A2.2.4	-	3	3	Bond Pull over Stitch, post bHAST, 2X	Post stress	-	3/9/0	3/9/0	3/9/0
HAST	A2.2.5	-	3	3	Bond Pull over Ball, post bHAST, 2X	Post stress	-	3/9/0	3/9/0	3/9/0

Type	#	Test Spec	Min Lot Qty	SS / Lot	Test Name	Condition	Duration	Qual Device: ESD601DPYRQ1	QBS Reference: ESD2CAN24DBZRQ1	QBS Reference: TSM24CADBZRQ1
TC	A4.1	JEDEC JESD22-A104 and Appendix 3	3	77	Temperature Cycle	-65C/150C	1000 Cycles	3/231/0	-	3/231/0
TC	A4.1	JEDEC JESD22-A104 and Appendix 3	3	77	Temperature Cycle	-65C/150C	500 Cycles	3/231/0	3/231/0	3/231/0
TC	A4.1.1	-	3	22	SAM Analysis, post TC, 1X	Review for delamination	Completed	3/66/0	3/66/0	-
TC	A4.1.2	-	3	1	Cross Section, post TC, 1X	Post stress cross section	Completed	3/3/0	-	-
TC	A4.1.3	-	3	3	Wire Bond Shear, post TC, 1X	Post stress	-	3/9/0	-	-
TC	A4.1.4	-	3	3	Bond Pull over Stitch, post TC, 1X	Post stress	-	3/9/0	-	-
TC	A4.1.5	-	3	3	Bond Pull over Ball, post TC, 1X	Post stress	-	3/9/0	-	-
TC	A4.2	JEDEC JESD22-A104 and Appendix 3	3	70	Temperature Cycle	-65C/150C	1000 Cycles	-	3/231/0	-
TC	A4.2.1	-	3	22	SAM Analysis, post TC, 2X	Review for delamination	Completed	3/66/0	3/66/0	-
TC	A4.2.2	-	3	1	Cross Section, post TC, 2X	Post stress cross section	Completed	3/3/0	3/3/0	-
TC	A4.2.3	-	3	3	Wire Bond Shear, post TC, 2X	Post stress	-	3/9/0	3/9/0	-
TC	A4.2.4	-	3	3	Bond Pull over Stitch, post TC, 2X	Post stress	-	3/9/0	3/9/0	-
TC	A4.2.5	-	3	3	Bond Pull over Ball, post TC, 2X	Post stress	-	3/9/0	3/9/0	-

**Test Group C - Package Assembly Integrity Tests**

- QBS: Qual By Similarity, also known as Generic Data
- Qual Device ESD601DPYRQ1 is qualified at MSL1 260C
- Preconditioning was performed for Autoclave, Unbiased HAST, THB/Biased HAST, Temperature Cycle, Thermal Shock, and HTSL, as applicable
- The following are equivalent HTOL options based on an activation energy of 0.7eV : 125C/1k Hours, 140C/480 Hours, 150C/300 Hours, and 155C/240 Hours
- The following are equivalent HTSL options based on an activation energy of 0.7eV : 150C/1k Hours, and 170C/420 Hours
- The following are equivalent Temp Cycle options per JESD47 : -55C/125C/700 Cycles and -65C/150C/500 Cycles

**Ambient Operating Temperature by Automotive Grade Level:**

- Grade 0 (or E): -40C to +150C
- Grade 1 (or Q): -40C to +125C
- Grade 2 (or T): -40C to +105C
- Grade 3 (or I): -40C to +85C

**E1 (TEST): Electrical test temperatures of Qual samples (High temperature according to Grade level):**

- Room/Hot/Cold : HTOL, ED
- Room/Hot : THB / HAST, TC / PTC, HTSL, ELFR, ESD & LU
- Room : ACuHAST

Quality and Environmental data is available at TI's external Web site: <http://www.ti.com/>

TI Qualification ID: R-CHG-2409-083

## Automotive New Product Qualification Summary (As per AEC-Q101 and JEDEC Guidelines)

Approve Date 23-FEBRUARY -2025

Update Date 29-September -2025

**Product Attributes**

Attributes	Qual Device:	
	<a href="#">ESD2CAN24DBZRQ1</a>	<a href="#">TSM24ADBZRQ1</a>
Automotive Grade Level	Grade 1	Grade 1
Operating Temp Range (C)	-40 to 125	-40 to 125
Product Function	Interface	Interface
Wafer Fab Supplier	MH8	MH8
Assembly Site	PHI	PHI
Package Group	SOT	SOT
Package Designator	DBZ	DBZ
Pin Count	3	3

- QBS: Qual By Similarity, also known as Generic Data
- Qual Device ESD2CAN24DBZRQ1 and TSM24ADBZRQ1 are qualified at MSL1 260C

**Qualification Results**

Data Displayed as: Number of lots / Total sample size / Total failed

Type	#	Test Spec	Min Lot Qty	SS / Lot	Test Name	Condition	Duration	Qual Device: <a href="#">ESD2CAN24DBZRQ1</a>	Qual Device: <a href="#">TSM24ADBZRQ1</a>
<b>Test Group A - Accelerated Environment Stress Tests</b>									
PC	A1	JEDEC J-STD-020 JESD22-A113	-	0	Preconditioning	MSL1 260C	1 Step	2/0/0	1/0/0
HAST	A2	JEDEC JESD22-A110	3	77	Biased HAST	130C/85%RH	96 Hours	2/154/0	1/77/0
HAST	A2.1	JEDEC JESD22-A110	3	77	Biased HAST	130C/85%RH	96 Hours	2/154/0	1/77/0
HAST	A2.1.2	-	3	1	Cross Section, post bHAST, 1X	Post stress cross section	Completed	2/2/0	1/1/0
HAST	A2.1.3	-	3	3	Wire Bond Shear, post bHAST, 1X	Post stress	-	2/6/0	1/3/0
HAST	A2.1.4	-	3	3	Bond Pull over Slitch, post bHAST, 1X	Post stress	-	2/6/0	1/3/0
HAST	A2.1.5	-	3	3	Bond Pull over Ball, post bHAST, 1X	Post stress	-	2/6/0	1/3/0
HAST	A2.2	JEDEC JESD22-A110	3	70	Biased HAST	130C/85%RH	192 Hours	2/154/0	1/77/0
AC/UHAST	A3	JEDEC JESD22-A118	3	77	Unbiased HAST	130C/85%RH	96 Hours	2/154/0	1/77/0
TCHT	A4.1	JEDEC JESD22-A104 and Appendix 6	3	77	Temperature Cycle	-65C/150C	1000 Cycles	2/154/0	1/77/0
TC	A4.1	JEDEC JESD22-A104 and Appendix 3	3	77	Temperature Cycle	-65C/150C	500 Cycles	2/154/0	1/77/0
TC	A4.1.1	-	3	22	SAM Analysis, post TC 1X	Review for delamination	Completed	2/44/0	1/22/0
TC	A4.1.2	-	3	1	Cross Section, post TC, 1X	Post stress cross section	Completed	1/1/0	1/1/0
TC	A4.1.3	-	3	3	Wire Bond Shear, post TC, 1X	Post stress	-	1/3/0	1/3/0
TC	A4.1.4	-	3	3	Bond Pull over Slitch, post TC, 1X	Post stress	-	2/6/0	1/3/0
TC	A4.1.5	-	3	3	Bond Pull over Ball, post TC, 1X	Post stress	-	2/6/0	1/3/0
TC	A4.2	JEDEC JESD22-A104 and Appendix 3	3	70	Temperature Cycle	-65C/150C	1000 Cycles	2/154/0	1/77/0
TC	A4.2.1	-	3	22	SAM Analysis, post TC, 2X	Review for delamination	Completed	2/44/0	1/22/0

Type	#	Test Spec	Min Lot Qty	SS / Lot	Test Name	Condition	Duration	Qual Device: ESD2CAN24DBZRQ1	Qual Device: TSM24ADBZRQ1
TC	A4.2.2	-	3	1	Cross Section, post TC, 2X	Post stress cross section	Completed	1/1/0	1/1/0
TC	A4.2.3	-	3	3	Wire Bond Shear, post TC, 2X	Post stress	-	2/6/0	1/3/0
TC	A4.2.4	-	3	3	Bond Pull over Stitch, post TC, 2X	Post stress	-	2/6/0	1/3/0
TC	A4.2.5	-	3	3	Bond Pull over Ball, post TC, 2X	Post stress	-	2/6/0	1/3/0
<b>Test Group B - Accelerated Lifetime Simulation Tests</b>									
HTRB	B1.1	MIL-STD-750-1	3	77	High Temperature Reverse Bias	125C	1000 Hours	2/154/0	1/77/0
HTRB	B1.2	MIL-STD-750-1	3	77	High Temperature Reverse Bias	125C	2000 Hours	2/154/0	1/77/0
<b>Test Group C - Package Assembly Integrity Tests</b>									
DPA	C2	JESD22-B100	-	30	Physical Dimensions	Cpk>1.67	1 Step	2/60/0	1/30/0
WBP	C3	MIL-STD-750-2	-	10	Wire Bond Pull	Minimum of 5 devices, 30 wires Cpk>1.67	1 Step	1/10/0	1/10/0
WBS	C4	AEC-Q101-003	-	10	Wire Bond Shear	Minimum of 5 devices, 30 wires Cpk>1.67	1 Step	2/20/0	1/10/0
DS	C5	MIL-STD-750-2	-	5	Die Shear	MIL-STD-750-2 Method 2017	1 Step	2/10/0	1/5/0
RSH	C8	JESD22-B107	-	30	Solder Heat	260C, 10 seconds	1 Step	1/30/0	1/30/0
SD	C10	JEDEC J-STD-002	-	15	PB Solderability	Precondition w.155C Dry Bake (4 hrs +/- 15 minutes)	1 Step	1/10/0	1/10/0
SD	C10	JEDEC J-STD-002	-	15	PB-Free Solderability	Precondition w.155C Dry Bake (4 hrs +/- 15 minutes)	1 Step	1/15/0	1/15/0
<b>Test Group D - Die Fabrication Reliability Tests</b>									
<b>Test Group E - Electrical Verification Tests</b>									
EV	E0	JESD22-B101	3	1000	Visual/Mechanical	Per JESD22 B-101	1 Step	1/1000/0	1/1000/0
ESD	E3	AEC Q101-001	3	10	ESD HBM	Room Temp	2000 Volts	1/10/0	1/10/0
ESD	E4	AEC Q101-005	3	10	ESD CDM	Room Temp	750 Volts	1/10/0	1/10/0
Type	#	Test Spec	Min Lot Qty	SS / Lot	Test Name	Condition	Duration	Qual Device	Qual Device

- Preconditioning was performed for Autoclave, Unbiased HAST, THB/Biased HAST, Temperature Cycle, Thermal Shock, HTSL, and IOL, as applicable
- Passing results reflect shift analysis per Q101 requirements

**Ambient Operating Temperature by Automotive Grade Level:**

- Grade 0 (or E): -40C to +150C
- Grade 1 (or Q): -40C to +125C
- Grade 2 (or T): -40C to +105C
- Grade 3 (or I) : -40C to +85C

**E1 (TEST): Electrical test temperatures of Qual samples (High temperature according to Grade level):**

- Room/Hot/Cold : HTRB, ED
- Room/Hot : THB / HAST, TC / PTC, HTSL, ELFR, ESD & LU
- Room : AC/uHAST

Quality and Environmental data is available at TI's external Web site: <http://www.ti.com/>

TI Qualification ID: R-CHG-2405-014 and R-CHG-2405-054

In performing change qualifications, Texas Instruments follows integrated circuit industry standards in performing defect mechanism analysis and failure mechanism-based accelerated

environmental testing to ensure wafer fab process, assembly process and product quality and reliability. As encouraged by these standards, TI uses both product-specific and generic (family) data in qualifying its changes. For devices to be categorized as a 'product qualification family' for generic data purposes, they must share similar product, wafer fab process and assembly process elements. The applicability of generic data (also known at TI as Qualification by Similarity (QBS)) is determined by the Reliability Engineering function following these industry standards. Generic data is shown in the qualification report in columns titled "QBS Process" (for wafer fab process), "QBS Package" (for assembly process) and "QBS Product" (for product family).

**ZVEI ID:** SEM-PW-13, SEM-PA-18, SEM-PA-13, SEM-PA-07, SEM-PA-08, SEM-PA-05

For questions regarding this notice, e-mails can be sent to the Change Management team or your local Field Sales Representative.

### **IMPORTANT NOTICE AND DISCLAIMER**

TI PROVIDES TECHNICAL AND RELIABILITY DATA (INCLUDING DATASHEETS), DESIGN RESOURCES (INCLUDING REFERENCE DESIGNS), APPLICATION OR OTHER DESIGN ADVICE, WEB TOOLS, SAFETY INFORMATION, AND OTHER RESOURCES "AS IS" AND WITH ALL FAULTS, AND DISCLAIMS ALL WARRANTIES, EXPRESS AND IMPLIED, INCLUDING WITHOUT LIMITATION ANY IMPLIED WARRANTIES OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE OR NON-INFRINGEMENT OF THIRD PARTY INTELLECTUAL PROPERTY RIGHTS.

These resources are intended for skilled developers designing with TI products. You are solely responsible for (1) selecting the appropriate TI products for your application, (2) designing, validating and testing your application, and (3) ensuring your application meets applicable standards, and any other safety, security, or other requirements. These resources are subject to change without notice. TI grants you permission to use these resources only for development of an application that uses the TI products described in the resource. Other reproduction and display of these resources is prohibited. No license is granted to any other TI intellectual property right or to any third party intellectual property right. TI disclaims responsibility for, and you will fully indemnify TI and its representatives against, any claims, damages, costs, losses, and liabilities arising out of your use of these resources.

TI's products are provided subject to TI's Terms of Sale ([www.ti.com/legal/termsofsale.html](http://www.ti.com/legal/termsofsale.html)) or other applicable terms available either on [ti.com](http://ti.com) or provided in conjunction with such TI products. TI's provision of these resources does not expand or otherwise alter TI's applicable warranties or warranty disclaimers for TI products.