



12500 TI Boulevard, MS 8640, Dallas, Texas 75243

PCN#20260522001.1
Qualification of RFAB as an additional Fab site
and TI Chengdu as additional Assembly site
options for select devices
Change Notification / Sample Request

Date: May 26, 2026

To: MOUSER PCN

Dear Customer:

This is an announcement of a change to a device that is currently offered by Texas Instruments. The details of this change are on the following pages.

Texas Instruments requires acknowledgement of receipt of this notification within 60 days of the date of this notice. Lack of acknowledgement of this notice within 60 days constitutes acceptance and approval of this change. If samples or additional data are required, requests must be received within 60 days of this notification.

The changes discussed within this PCN will not take effect any earlier than the proposed first ship date on Page 3 of this notification, unless customer agreement has been reached on an earlier implementation of the change.

This notice does not change the end-of-life status of any product. Should product affected be on a previously issued product withdrawal/discontinuance notice, this notification does not extend the life of that product or change the life time buy offering/discontinuance plan.

For questions regarding this notice or to provide acknowledgement of this PCN, you may contact your local Field Sales Representative or the change management team.

For sample requests or sample related questions, contact your local Field Sales Representative.

TI values customer engagement and feedback related to TI changes. Customers should contact TI if there are questions or concerns regarding a change notification.

Sincerely,

Change Management Team
SC Business Services

20260522001.1
Attachment: 1

Products Affected:

The devices listed on this page are a subset of the complete list of affected devices. According to our records, you have recently purchased these devices. The corresponding customer part number is also listed, if available.

| DEVICE | CUSTOMER PART NUMBER |
|---------------|-----------------------------|
| INA215AIDCKT | INA215AIDCKT |
| INA210AIDCKR | INA210AIDCKR |
| INA214AIDCKR | INA214AIDCKR |
| INA214BIDCKR | INA214BIDCKR |
| INA214BIDCKT | INA214BIDCKT |
| INA210AIDCKT | INA210AIDCKT |
| INA214AIDCKT | INA214AIDCKT |
| INA213CIDCKR | INA213CIDCKR |
| INA213BIDCKR | INA213BIDCKR |
| INA213AIDCKT | INA213AIDCKT |
| INA213CIDCKT | INA213CIDCKT |
| INA212BIDCKR | INA212BIDCKR |
| INA215CIDCKR | INA215CIDCKR |
| INA215AIDCKR | INA215AIDCKR |

Technical details of this Product Change follow on the next page(s).

| PCN Number: | 20260522001.1 | PCN Date: | May 26, 2026 | | | | | | | | | | | | | | | | | | | | | | | | |
|---|---|---|---|------------------|----------------|-----|---------------------|------|------|---------------------|-----------|----------------|---------------------|-----------|----------------|----------------|----------|----------|----------|----------|---------|---------------|----------|------------|----------|------------|---------|
| Title: | Qualification of RFAB as an additional Fab site and TI Chengdu as additional Assembly site options for select devices | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Customer Contact: | Change Management Team | Dept: | Quality Services | | | | | | | | | | | | | | | | | | | | | | | | |
| Proposed 1st Ship Date: | August 24, 2026 | Sample requests accepted until: | July 25, 2026* | | | | | | | | | | | | | | | | | | | | | | | | |
| *Sample requests received after July 25, 2026 will not be supported. | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Change Type: | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| <input checked="" type="checkbox"/> | Assembly Site | <input type="checkbox"/> | Design | | | | | | | | | | | | | | | | | | | | | | | | |
| <input checked="" type="checkbox"/> | Assembly Process | <input type="checkbox"/> | Data Sheet | | | | | | | | | | | | | | | | | | | | | | | | |
| <input checked="" type="checkbox"/> | Assembly Materials | <input type="checkbox"/> | Part number change | | | | | | | | | | | | | | | | | | | | | | | | |
| <input type="checkbox"/> | Mechanical Specification | <input type="checkbox"/> | Test Site | | | | | | | | | | | | | | | | | | | | | | | | |
| <input checked="" type="checkbox"/> | Packing/Shipping/Labeling | <input type="checkbox"/> | Test Process | | | | | | | | | | | | | | | | | | | | | | | | |
| <input type="checkbox"/> | | <input type="checkbox"/> | Wafer Bump Material | | | | | | | | | | | | | | | | | | | | | | | | |
| <input type="checkbox"/> | | <input type="checkbox"/> | Wafer Bump Process | | | | | | | | | | | | | | | | | | | | | | | | |
| <input checked="" type="checkbox"/> | | <input checked="" type="checkbox"/> | Wafer Fab Site | | | | | | | | | | | | | | | | | | | | | | | | |
| <input type="checkbox"/> | | <input checked="" type="checkbox"/> | Wafer Fab Material | | | | | | | | | | | | | | | | | | | | | | | | |
| <input type="checkbox"/> | | <input type="checkbox"/> | Wafer Fab Process | | | | | | | | | | | | | | | | | | | | | | | | |
| PCN Details | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Description of Change: | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Texas Instruments is pleased to announce the qualification of RFAB as an additional Fab site option & TI Chengdu as additional Assembly site options for the devices listed below. | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| <table border="1" style="width: 100%; border-collapse: collapse;"> <thead> <tr> <th colspan="3" style="text-align: center;">Current Fab Site</th> <th colspan="3" style="text-align: center;">Additional Fab site</th> </tr> <tr> <th style="text-align: center;">Current Fab Site</th> <th style="text-align: center;">Process</th> <th style="text-align: center;">Wafer Diameter</th> <th style="text-align: center;">Additional Fab site</th> <th style="text-align: center;">Process</th> <th style="text-align: center;">Wafer Diameter</th> </tr> </thead> <tbody> <tr> <td style="text-align: center;">AIZU</td> <td style="text-align: center;">50HPA07</td> <td style="text-align: center;">200mm</td> <td style="text-align: center;">RFAB</td> <td style="text-align: center;">50HPA07</td> <td style="text-align: center;">300mm</td> </tr> </tbody> </table> | | | | Current Fab Site | | | Additional Fab site | | | Current Fab Site | Process | Wafer Diameter | Additional Fab site | Process | Wafer Diameter | AIZU | 50HPA07 | 200mm | RFAB | 50HPA07 | 300mm | | | | | | |
| Current Fab Site | | | Additional Fab site | | | | | | | | | | | | | | | | | | | | | | | | |
| Current Fab Site | Process | Wafer Diameter | Additional Fab site | Process | Wafer Diameter | | | | | | | | | | | | | | | | | | | | | | |
| AIZU | 50HPA07 | 200mm | RFAB | 50HPA07 | 300mm | | | | | | | | | | | | | | | | | | | | | | |
| Construction differences are as follows: | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| <table border="1" style="width: 100%; border-collapse: collapse;"> <thead> <tr> <th></th> <th style="text-align: center;">HFTF</th> <th style="text-align: center;">HNA</th> <th style="text-align: center;">TFME</th> <th style="text-align: center;">UTL2</th> <th style="text-align: center;">CDAT</th> </tr> </thead> <tbody> <tr> <td>Wire bond diam/type</td> <td style="text-align: center;">1.0mil Au</td> <td style="text-align: center;">1.0mil Au</td> <td style="text-align: center;">1.0mil Au</td> <td style="text-align: center;">1.0mil Au</td> <td style="text-align: center;">0.8mil Cu</td> </tr> <tr> <td>Mount compound</td> <td style="text-align: center;">SID#A-09</td> <td style="text-align: center;">SID#A-09</td> <td style="text-align: center;">SID#A-09</td> <td style="text-align: center;">SID#A-09</td> <td style="text-align: center;">4226215</td> </tr> <tr> <td>Mold compound</td> <td style="text-align: center;">SID#R-27</td> <td style="text-align: center;">SID#450179</td> <td style="text-align: center;">SID#R-07</td> <td style="text-align: center;">SID#450179</td> <td style="text-align: center;">4222198</td> </tr> </tbody> </table> | | | | | HFTF | HNA | TFME | UTL2 | CDAT | Wire bond diam/type | 1.0mil Au | 1.0mil Au | 1.0mil Au | 1.0mil Au | 0.8mil Cu | Mount compound | SID#A-09 | SID#A-09 | SID#A-09 | SID#A-09 | 4226215 | Mold compound | SID#R-27 | SID#450179 | SID#R-07 | SID#450179 | 4222198 |
| | HFTF | HNA | TFME | UTL2 | CDAT | | | | | | | | | | | | | | | | | | | | | | |
| Wire bond diam/type | 1.0mil Au | 1.0mil Au | 1.0mil Au | 1.0mil Au | 0.8mil Cu | | | | | | | | | | | | | | | | | | | | | | |
| Mount compound | SID#A-09 | SID#A-09 | SID#A-09 | SID#A-09 | 4226215 | | | | | | | | | | | | | | | | | | | | | | |
| Mold compound | SID#R-27 | SID#450179 | SID#R-07 | SID#450179 | 4222198 | | | | | | | | | | | | | | | | | | | | | | |
| Qual details are provided in the Qual Data Section. | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Reason for Change: | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Continuity of supply | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Anticipated impact on Form, Fit, Function, Quality or Reliability (positive / negative): | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Review the SDP for full evaluation of the change based on the customer use case. | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Impact on Environmental Ratings | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Checked boxes indicate the status of environmental ratings following implementation of this change. If below boxes are checked, there are no changes to the associated environmental ratings. | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| RoHS | REACH | Green Status | IEC 62474 | | | | | | | | | | | | | | | | | | | | | | | | |
| <input checked="" type="checkbox"/> No Change | <input checked="" type="checkbox"/> No Change | <input checked="" type="checkbox"/> No Change | <input checked="" type="checkbox"/> No Change | | | | | | | | | | | | | | | | | | | | | | | | |
| Changes to product identification resulting from this PCN: | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Fab Site Information: | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Chip Site | Chip Site Origin Code (20L) | Chip Site Country Code (21L) | Chip Site City | | | | | | | | | | | | | | | | | | | | | | | | |

| | | | |
|-------------|------------|------------|-------------------|
| AIZU | CU2 | JPN | Aizuwakamatsu-shi |
| RFAB | RFB | USA | Richardson |

Assembly Site Information:

| Assembly Site | Assembly Site Origin (22L) | Assembly Country Code (23L) | Assembly City |
|-------------------|----------------------------|-----------------------------|----------------|
| HFTF | HFT | CHN | Hefei |
| HNA | HNT | THA | Ayutthaya |
| TFME | NFM | CHN | Chongchuan |
| UTL2 | NS2 | THA | Bangpakong |
| TI Chengdu | CU3 | CHN | Chengdu |

Sample product shipping label (not actual product label):

TEXAS INSTRUMENTS
 MADE IN: Malaysia
 2DC: 20:
 MSL 2 /260C/1 YEAR SEAL DT
 MSL 1 /235C/UNLIM 03/29/04
 OPT: 39
 ITEM: LBL: 5A (L)T0:1750
 G4
 (1P) SN74LS07NSR
 (Q) 2000 (D) 0336
 (31T) LOT: 3959047MLA
 (4W) TKY (1T) 7523483S12
 (P)
 (2P) REV: 0033317
 (20L) CSO: SHE (21L) CCO:USA
 (22L) ASO:MLA (23L) ACO:MYS

Product Affected:

| | | |
|--------------|--------------|--------------|
| BQ500100DCKR | INA211CIDCKR | INA214AIDCKT |
| BQ500100DCKT | INA212BIDCKR | INA214BIDCKR |
| INA210AIDCKR | INA212CIDCKR | INA214BIDCKT |
| INA210AIDCKT | INA213AIDCKT | INA215AIDCKR |
| INA210BIDCKR | INA213BIDCKR | INA215AIDCKT |
| INA210BIDCKT | INA213BIDCKT | INA215BIDCKR |
| INA210CIDCKT | INA213CIDCKR | INA215BIDCKT |
| INA211BIDCKR | INA213CIDCKT | INA215CIDCKR |
| INA211BIDCKT | INA214AIDCKR | |

Qualification Report
 Approve Date 10-October-2025

Qualification Results

Data Displayed as: Number of lots / Total sample size / Total failed

| Type | # | Test Name | Condition | Duration | Qual Device: INA210AIDCKR | QBS Reference: CD3232A1YFFR | QBS Reference: INA210BQDCKRQ1 |
|-------|----|-------------------------------|--|------------|---------------------------|-----------------------------|-------------------------------|
| HAST | A2 | Biased HAST | 130C/85%RH | 96 Hours | - | 3/231/0 | - |
| UHAST | A3 | Unbiased HAST | 130C/85%RH | 96 Hours | - | 3/231/0 | 1/77/0 |
| TC | A4 | Temperature Cycle | -55C/125C | 700 Cycles | - | 3/231/0 | - |
| TC | A4 | Temperature Cycle | -65C/150C | 500 Cycles | - | - | 1/77/0 |
| HTSL | A6 | High Temperature Storage Life | 150C | 1000 Hours | - | - | 1/45/0 |
| HTSL | A6 | High Temperature Storage Life | 170C | 420 Hours | - | 3/231/0 | - |
| HTOL | B1 | CL (FF) | 125C | 1000 Hours | - | 1/45/0 | - |
| HTOL | B1 | CL (FS) | 125C | 1000 Hours | - | 1/32/0 | - |
| HTOL | B1 | CL (SF) | 125C | 1000 Hours | - | 1/32/0 | - |
| HTOL | B1 | CL (SS) | 125C | 1000 Hours | - | 1/45/0 | - |
| HTOL | B1 | Life Test | 125C | 1000 Hours | - | - | 1/77/0 |
| HTOL | B1 | Life Test | 140C | 480 Hours | - | 2/154/0 | - |
| ELFR | B2 | ELFR | 125C | 48 Hours | - | 2/2000/0 | - |
| ELFR | B2 | Early Life Failure Rate | 125C | 48 Hours | - | - | 3/2400/0 |
| SD | C3 | PB-Free Solderability | Precondition w/155C Dry Bake (4 hrs +/- 15 minutes); PB-Free Solder: | - | - | 3/6/0 | - |
| PD | C4 | Physical Dimensions | (per mechanical drawing) | - | - | 3/6/0 | - |
| PD | C4 | Physical Dimensions | Cpk>=1.67 | - | - | - | 1/1/0 |
| ESD | E2 | ESD CDM | - | 200 Volts | - | 3/9/0 | - |
| ESD | E2 | ESD CDM | - | 250 Volts | 1/3/0 | - | - |
| ESD | E2 | ESD CDM | - | 500 Volts | - | - | 1/3/0 |
| ESD | E2 | ESD HBM | - | 1000 Volts | 1/3/0 | 3/9/0 | - |
| ESD | E2 | ESD HBM | - | 2000 Volts | - | - | 1/3/0 |
| LU | E4 | LU | Per JESD78 | - | - | 3/9/0 | - |
| LU | E4 | Latch-Up | Per JESD78 | - | 1/3/0 | - | 1/3/0 |
| CHAR | E5 | Electrical Characterization | Per Datasheet Parameters | - | 1/3/0 | 1/3/0 | - |
| CHAR | E5 | Electrical Distributions | Cpk>=1.67 Ploom, hot, and cold | - | - | - | 3/9/0 |

QBS: Qual By Similarity, also known as Generic Data

Qual Device INA210AIDCKR is qualified at MSL1 260C

Preconditioning was performed for Autoclave, Unbiased HAST, THB/Biased HAST, Temperature Cycle, Thermal Shock, and HTSL, as applicable

The following are equivalent HTOL options based on an activation energy of 0.7eV : 125C/1k Hours, 140C/480 Hours, 150C/300 Hours, and 155C/240 Hours

The following are equivalent HTSL options based on an activation energy of 0.7eV : 150C/1k Hours, and 170C/420 Hours

The following are equivalent Temp Cycle options per JESD47 : -55C/125C/700 Cycles and -65C/150C/500 Cycles

Quality and Environmental data is available at TI's external Web site: <http://www.ti.com/>

TI Qualification ID: R-CHG-2405-058

Automotive Qualification Summary (As per AEC-Q100 Rev. J and JEDEC Guidelines)

Approve Date 06-December-2024

Product Attributes

| Attributes | Qual Device: INA210BQDCKRTL | QBS Process Reference: INA215AQDCKRQ1 | QBS Package Reference: TPS3840PH30DBVRQ1 | QBS Package Reference: LM74703QDDFRQ1 | QBS Package Reference: TXS0101QDCKRQ1 |
|--------------------------|--|--|---|--|--|
| Automotive Grade Level | Grade 1 | Grade 1 | Grade 1 | Grade 1 | Grade 1 |
| Operating Temp Range (C) | -40 to 125 | -40 to 125 | -40 to 125 | -40 to 125 | -40 to 125 |
| Product Function | Signal Chain | Signal Chain | Power Management | Power Management | Logic |
| Wafer Fab Supplier | AIZU | AIZU | RFAB | RFAB | RFAB |
| Assembly Site | CDAT | TFME | CDAT | CDAT | CDAT |
| Package Group | SOT | SOT | SOT | SOT | SOT |
| Package Designator | DCK | DCK | DBV | DDF | DCK |
| Pin Count | 6 | 6 | 5 | 8 | 6 |

QBS: Qual By Similarity, also known as Generic Data

Qual Device INA210BQDCKRTL is qualified at MSL1 260C

Note 1: Qual device and affected devices in PCN have justification to use Package QBS references for HAST, AC/UHAST and TC-BP based on AEC-100J A1.3 assembly site and package attributes were qualified.

Note 2: Qual device and affected devices in PCN have justification to use Process QBS references for HTOL and ELFR based on AEC-100J A1.2 silicon wafer fab and process attributes were qualified. Group B tests purpose is for silicon defects, they do not get influenced by assembly site or BOM differences.

Note 3: Qual device and affected devices in PCN have justification to use SD QBS based on AEC-100J A1.3 leadframe attributes are qualified.

Note 4: One lot is allowed per AEC-Q100J A1.5.1 Multiple Sites - When the specific product or process attribute to be qualified or requalified will affect more than one wafer fab site or assembly site, a minimum of one lot of testing per affected site is required.

Qualification Results

Data Displayed as: Number of lots / Total sample size / Total failed

| Type | # | Test Spec | Min Lot Qty | SS / Lot | Test Name | Condition | Duration | Qual Device: | QBS Process Reference: | QBS Package Reference: | QBS Package Reference: | QBS Package Reference: |
|---|----|-------------------------------------|-------------|----------|-------------------------------------|---|------------|---|---|---|---|---|
| | | | | | | | | INA210BQDCKRTL | INA215AQDCKRQ1 | TPS3840PH30DBVRQ1 | LM74703QDDFRQ1 | TXS0101QDCKRQ1 |
| Test Group A - Accelerated Environment Stress Tests | | | | | | | | | | | | |
| PC | A1 | JEDEC J-STD-020 JESD22-A113 | 3 | 77 | Preconditioning | MSL1 260C | - | 1/Pass Note 4 | - | 3/Pass | 3/Pass | 3/Pass |
| HAST | A2 | JEDEC JESD22-A110 | 3 | 77 | Biased HAST | 130C/85%RH | 96 Hours | Note 1 | - | 3/231/0 | 3/231/0 | 3/231/0 |
| AC/UHAST | A3 | JEDEC JESD22-A102/JEDEC JESD22-A118 | 3 | 77 | Autoclave | 121C/15psig | 96 Hours | - | - | 3/231/0 | - | - |
| AC/UHAST | A3 | JEDEC JESD22-A102/JEDEC JESD22-A118 | 3 | 77 | Unbiased HAST | 130C/85%RH | 96 Hours | 1/77/0 Note 4 | - | - | 3/231/0 | 3/231/0 |
| TC | A4 | JEDEC JESD22-A104 and Appendix 3 | 3 | 77 | Temperature Cycle | -65C/150C | 500 Cycles | 1/77/0 Note 4 | - | 3/231/0 | 3/231/0 | 3/231/0 |
| TC-BP | A4 | MIL-STD883 Method 2011 | 1 | 5 | Post Temp Cycle Bond Pull | - | - | Note 1 | - | 1/5/0 | 1/5/0 | 1/5/0 |
| HTSL | A6 | JEDEC JESD22-A103 | 1 | 45 | High Temperature Storage Life | 150C | 1000 Hours | 1/45/0 Note 4 | - | 3/135/0 | 1/45/0 | 3/135/0 |
| Test Group B - Accelerated Lifetime Simulation Tests | | | | | | | | | | | | |
| HTOL | B1 | JEDEC JESD22-A108 | 3 | 77 | Life Test | 125C | 1000 Hours | Note 2 | 3/231/0 | 3/231/0 | - | 1/77/0 |
| HTOL | B1 | JEDEC JESD22-A108 | 3 | 77 | Life Test | 150C | 300 Hours | Note 2 | - | - | 1/77/0 | - |
| ELFR | B2 | AEC Q100-008 | 3 | 800 | Early Life Failure Rate | 125C | 48 Hours | Note 2 | 3/2400/0 | - | - | - |
| Test Group C - Package Assembly Integrity Tests | | | | | | | | | | | | |
| WBS | C1 | AEC Q100-001 | 1 | 30 | Wire Bond Shear | Minimum of 5 devices, 30 wires Cpk>1.67 | Wires | 1/30/0 Note 4 | 1/30/0 | 3/90/0 | 3/90/0 | 3/90/0 |
| WBP | C2 | MIL-STD883 Method 2011 | 1 | 30 | Wire Bond Pull | Minimum of 5 devices, 30 wires Cpk>1.67 | Wires | 1/30/0 Note 4 | 1/30/0 | 3/90/0 | 3/90/0 | 3/90/0 |
| SD | C3 | JEDEC J-STD-002 | 1 | 15 | PB Solderability | >95% Lead Coverage | - | Note 3 | - | 1/15/0 | 1/15/0 | - |
| SD | C3 | JEDEC J-STD-002 | 1 | 15 | PB-Free Solderability | >95% Lead Coverage | - | Note 3 | - | 1/15/0 | 1/15/0 | 1/15/0 |
| PD | C4 | JEDEC JESD22-B100 and B108 | 3 | 10 | Physical Dimensions | Cpk>1.67 | - | 1/10/0 Note 4 | - | 3/30/0 | 3/30/0 | 3/30/0 |
| Test Group D - Die Fabrication Reliability Tests | | | | | | | | | | | | |
| EM | D1 | JESD61 | - | - | Electromigration | - | - | Completed Per Process Technology Requirements | Completed Per Process Technology Requirements | Completed Per Process Technology Requirements | Completed Per Process Technology Requirements | Completed Per Process Technology Requirements |
| TDDB | D2 | JESD35 | - | - | Time Dependent Dielectric Breakdown | - | - | Completed Per Process Technology Requirements | Completed Per Process Technology Requirements | Completed Per Process Technology Requirements | Completed Per Process Technology Requirements | Completed Per Process Technology Requirements |
| HCI | D3 | JESD60 & 28 | - | - | Hot Carrier Injection | - | - | Completed Per Process Technology Requirements | Completed Per Process Technology Requirements | Completed Per Process Technology Requirements | Completed Per Process Technology Requirements | Completed Per Process Technology Requirements |
| BTI | D4 | - | - | - | Bias Temperature Instability | - | - | Completed Per Process Technology Requirements | Completed Per Process Technology Requirements | Completed Per Process Technology Requirements | Completed Per Process Technology Requirements | Completed Per Process Technology Requirements |
| SM | D5 | - | - | - | Stress Migration | - | - | Completed Per Process Technology Requirements | Completed Per Process Technology Requirements | Completed Per Process Technology Requirements | Completed Per Process Technology Requirements | Completed Per Process Technology Requirements |
| Test Group E - Electrical Verification Tests | | | | | | | | | | | | |
| ESD | E2 | AEC Q100-002 | 1 | 3 | ESD HBM | - | 2000 Volts | 1/3/0 Note 4 | - | - | - | - |
| ESD | E3 | AEC Q100-011 | 1 | 3 | ESD CDM | - | 500 Volts | 1/3/0 Note 4 | - | - | - | - |
| ED | E5 | AEC Q100-009 | 3 | 30 | Electrical Distributions | Cpk>1.67 Room, hot, and cold | - | 1/30/0 Note 4 | - | - | - | - |

Preconditioning was performed for Autoclave, Unbiased HAST, THB/Biased HAST, Temperature Cycle, Thermal Shock, and HTSL, as applicable

The following are equivalent HTOL options based on an activation energy of 0.7eV : 125C/1k Hours, 140C/480 Hours, 150C/300 Hours, and 155C/240 Hours

The following are equivalent HTSL options based on an activation energy of 0.7eV : 150C/1k Hours, and 170C/420 Hours

The following are equivalent Temp Cycle options per JESD47 : -55C/125C/700 Cycles and -65C/150C/500 Cycles

Ambient Operating Temperature by Automotive Grade Level:

Grade 0 (or E): -40C to +150C

Grade 1 (or Q): -40C to +125C

Grade 2 (or T): -40C to +105C

Grade 3 (or I) : -40C to +85C

E1 (TEST): Electrical test temperatures of Qual samples (High temperature according to Grade level):

Room/Hot/Cold : HTOL, ED

Room/Hot : THB / HAST, TC / PTC, HTSL, ELFR, ESD & LU

Room : AC/uHAST

Quality and Environmental data is available at TI's external Web site: <http://www.ti.com/>

TI Qualification ID: R-CHG-2405-062

In performing change qualifications, Texas Instruments follows integrated circuit industry standards in performing defect mechanism analysis and failure mechanism-based accelerated environmental testing to ensure wafer fab process, assembly process and product quality and reliability. As encouraged by these standards, TI uses both product-specific and generic (family) data in qualifying its changes. For devices to be categorized as a 'product qualification family' for generic data purposes, they must share similar product, wafer fab process and assembly process elements. The applicability of generic data (also known at TI as Qualification by Similarity (QBS)) is determined by the Reliability Engineering function following these industry standards. Generic data is shown in the qualification report in columns titled "QBS Process" (for wafer fab process), "QBS Package" (for assembly process) and "QBS Product" (for product family).

For questions regarding this notice, e-mails can be sent to the Change Management team or your local Field Sales Representative.

IMPORTANT NOTICE AND DISCLAIMER

TI PROVIDES TECHNICAL AND RELIABILITY DATA (INCLUDING DATASHEETS), DESIGN RESOURCES (INCLUDING REFERENCE DESIGNS), APPLICATION OR OTHER DESIGN ADVICE, WEB TOOLS, SAFETY INFORMATION, AND OTHER RESOURCES "AS IS" AND WITH ALL FAULTS, AND DISCLAIMS ALL WARRANTIES, EXPRESS AND IMPLIED, INCLUDING WITHOUT LIMITATION ANY IMPLIED WARRANTIES OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE OR NON-INFRINGEMENT OF THIRD PARTY INTELLECTUAL PROPERTY RIGHTS.

These resources are intended for skilled developers designing with TI products. You are solely responsible for (1) selecting the appropriate TI products for your application, (2) designing, validating and testing your application, and (3) ensuring your application meets applicable standards, and any other safety, security, or other requirements. These resources are subject to change without notice. TI grants you permission to use these resources only for development of an application that uses the TI products described in the resource. Other reproduction and display of these resources is prohibited. No license is granted to any other TI intellectual property right or to any third party intellectual property right. TI disclaims responsibility for, and you will fully indemnify TI and its representatives against, any claims, damages, costs, losses, and liabilities arising out of your use of these resources.

TI's products are provided subject to TI's Terms of Sale (www.ti.com/legal/termsofsale.html) or other applicable terms available either on ti.com or provided in conjunction with such TI products. TI's provision of these resources does not expand or otherwise alter TI's applicable warranties or warranty disclaimers for TI products.