



# STYCAST<sup>®</sup> 5952 A/B

## Thermally Conductive Silicone Encapsulant

| Key Feature:                            | Benefit:                                       |
|-----------------------------------------|------------------------------------------------|
| • Good thermal conductivity             | • Dissipation of heat from embedded components |
| • Easy 1 to 1 mix ratio                 | • Ease of use                                  |
| • Reversion resistant and non-corrosive | • High reliability of encapsulated assemblies  |

### Product Description:

STYCAST 5952 A/B is a filled, addition cured, silicone encapsulant. It features good thermal conductivity, excellent electrical insulation properties, a convenient mix ratio and can be cured over a wide range of temperatures. STYCAST 5952 A/B can be cured in thick sections and is non-corrosive and reversion resistant.

### Applications:

STYCAST 5952 A/B was designed for encapsulating heat generating electronic devices such as bridge rectifiers, power supplies, thermistors, transformers, thermal probes and sensors. Other applications include pour-in-place thermal pads and heat sinks.

### Instructions For Use:

Thoroughly read the information concerning health and safety contained in this bulletin before using. Observe all precautionary statements that appear on the product label and/or contained in individual Material Safety Data Sheets (MSDS).

To ensure the long term performance of the potted or encapsulated electrical / electronic assembly, complete cleaning of components and substrates should be performed to remove contamination such as dust, moisture, salt, and oils which can cause electrical failure, poor adhesion or corrosion in an embedded part.

The cure of this silicone product may be inhibited through contact with certain contaminants. Avoid contact with butyl and chlorinated rubbers, amines, sulfur or sulfur containing materials, tin

containing compounds, or heavy metal salts. Substrates in question should be evaluated for compatibility before application of this product. In addition, molds, mixing equipment, ovens, and other apparatus that will be used in the preparation and curing of this product should be free of inhibiting contaminants.

Some filler settling is common during shipping and storage. For this reason, it is recommended that the contents of the shipping container be thoroughly mixed prior to use. Power mixing is preferred to ensure a homogeneous product.

Accurately weigh resin and hardener into a clean container in the recommended ratio. Weighing apparatus having an accuracy in proportion to the amounts being weighed should be used.

Blend components by hand, using a kneading motion, for 2-3 minutes. Scrape the bottom and sides of the mixing container frequently to produce a uniform mixture. If possible, power mix for an additional 2-3 minutes. Avoid high mixing speeds which could entrap excessive amounts of air or cause overheating of the mixture resulting in reduced working life.

To ensure a void-free embedment, vacuum deairing or degassing should be performed to remove any entrapped air introduced during the mixing operation. Pump-down or pull vacuum on the mixture to achieve an ultimate vacuum or absolute pressure of 1-5 torr or mm Hg. The foam will rise several times the liquid height and then subside. Continue vacuum deairing until most of the bubbling has ceased. This usually requires 3-10 minutes.

In general, silicone materials exhibit outstanding release properties and will not adhere to most substrates. If adhesion is required, apply a thin, uniform coating of PRIMER S 11 to the desired clean, dry substrates. Allow the PRIMER S 11 to dry for 30-60 minutes at room temperature before applying this silicone material.

Pour mixture into cavity or mold. Further vacuum deairing in the mold may be required for critical applications.

### Properties of Material As Supplied:

| Property             | Test Method    | Unit              | Value - Part A | Value - Part B |
|----------------------|----------------|-------------------|----------------|----------------|
| Chemical Type        |                |                   | Silicone       | Silicone       |
| Appearance           | Visual         |                   | Red liquid     | White liquid   |
| Density              | TP-13          | g/cm <sup>3</sup> | 2.05           | 2.05           |
| Brookfield Viscosity | TP-10 or TP-11 | Pa.s<br>cP        | 65<br>65,000   | 18<br>18,000   |

**Properties of Material As Mixed:**

| Property                                             | Test Method    | Unit                | Value        |
|------------------------------------------------------|----------------|---------------------|--------------|
| Mix Ratio - Amount of Part B per 100 parts of Part A |                | By Weight or Volume | 100          |
| Working Life (100 g @ 25°C)                          | ERF 13-70      | minutes             | 100          |
| Density                                              | TP-13          | g/cm <sup>3</sup>   | 2.05         |
| Brookfield Viscosity                                 | TP-10 or TP-11 | Pa.s<br>cP          | 40<br>40,000 |

**Cure Schedule:**

Cure at any one of the recommended cure schedules. This product may be cured in large castings with no adverse heat or exotherm effects. There is essentially no limit on casting size due to shrinkage or exotherm.

| Temperature | Cure Time   |
|-------------|-------------|
| °C          | Time        |
| 25          | 2 - 7 days  |
| 65          | 1 - 4 hours |
| 150         | 20 minutes  |

**Properties of Material After Application:**

| Property                         | Test Method | Unit                                   | Value             |
|----------------------------------|-------------|----------------------------------------|-------------------|
| Hardness                         | TP-311      | Shore A                                | 75                |
| Tensile Strength                 | TP-239      | mPa<br>psi                             | 3.4<br>500        |
| Tear Strength                    | ASTM-D-624  | N/m<br>pli                             | 3,500<br>20       |
| Elongation                       | TP-239      | %                                      | 50                |
| Linear Shrinkage                 | TP-320      | cm/cm                                  | 0.002             |
| Coefficient of Thermal Expansion | TMA         | 10 <sup>-6</sup> /°C                   | 200               |
| Glass Transition Temperature     | DSC / TMA   | °C                                     | -120              |
| Thermal Conductivity             | ASTM-D-2214 | W/m.K<br>Btu-in/hr-ft <sup>2</sup> -°F | 0.85<br>6.0       |
| Temperature Range of Use         |             | °C                                     | -65 to +260       |
| Dielectric Strength              | TP-297      | kV/mm<br>V/mil                         | 17.7<br>450       |
| Dielectric Constant @ 1 mHz      | TP-184      | -                                      | 5.0               |
| Dissipation Factor @ 1 mHz       | TP-184      | -                                      | 0.01              |
| Volume Resistivity @ 25°C        | TP-183      | Ohm-cm                                 | >10 <sup>14</sup> |

*TPs are internal test procedures typically derived from ASTM or other norms. Copies of these procedures can be obtained upon request.*

**Storage and Handling:**

The shelf life of STYCAST 5952 Parts A and B is 6 months at 25°C. For best results, store in original, tightly covered containers. Storage in cool, clean and dry areas is recommended.

**Health and Safety:**

The STYCAST 5952 Parts A and B, like most industrial compounds, possess the ability to cause skin and eye irritation upon contact. Handling these products at elevated temperatures may also generate vapors irritating to the respiratory system.

Good industrial hygiene and safety practices should be followed when handling these products. Proper eye protection and appropriate chemical

resistant clothing should be worn to minimize direct contact. Consult the Material Safety Data Sheet (MSDS) for detailed recommendations on the use of engineering controls and personal protective equipment.

*This information is only a brief summary of the available safety and health data. Thoroughly review the MSDS for more complete information before using this product.*

**Attention Specification Writers:**

The values contained herein are considered typical properties only and are not intended to be used as specification limits.

**Medical Implantable Disclaimer**

"In the event this product is intended by you for use in implantation in the human body, you are hereby advised that Henkel Corporation has not performed clinical testing of these materials for implantation in the human body nor has Henkel Corporation sought, nor received, approval from the FDA for the use of these material in implantation in the human body. It is YOUR responsibility, as a manufacturer of any such device, to ensure that all materials and processes relating to the manufacture of any medical device fully comply with all applicable federal, state and local laws, rules, regulations and requirements as well as any such laws, rules, regulations, directives or other orders of any foreign country where such product is sold. If you have not undertaken the necessary investigations to ensure compliance you are advised NOT TO USE this product in the manufacture of any device which is to be implanted in the human body. No representative of ours has any authority to change the foregoing provisions."

Revised 9/2003

**Note**

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.**

The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

**Trademark usage**

Except as otherwise noted, all trademarks in this document are trademarks of Henkel and/or its affiliates in Germany and elsewhere.

