

3M™ Scotchcast™ Electrical Resin 251

Two-Part, Oven-Curing, Class F, Rigid, Filled,
Epoxy Liquid Resin

Data Sheet

April 2013

Description

3M™ Scotchcast™ Electrical Resin 251 is a medium viscosity, rigid, Class F (155°C) resin system widely used where physical strength and excellent properties at elevated temperatures are required. An easy 1:1 mix ratio and good handling characteristics have contributed to the product's popularity. Warming this resin to 120°C (248°F) will lower its viscosity below 200 centipoise for maximum impregnating ability.

- High temperature
- Excellent electrical properties

Handling Properties

Mix Ratio (A-B)	Wt 1:1 Vol. (%) 50:50
Viscosity @ 23°C (73°F)	A = 175,000 cps B = 10,000 cps Mixed = 19,000 cps
Density	A = 1.53 kg/l (12.71 lbs/gal) B = 1.48 kg/l (12.32 lbs/gal)
Flash Point	A = 202°C (395°F) B = 152°C (305°F)
Gel Time	20 min. @ 121°C (250°F)
Curing Guide	75°C (167°F) 15 - 20 hrs 95°C (203°F) 6 - 8 hrs 120°C (250°F) 2 - 3 hrs

3M™ Scotchcast™ Electrical Resin 251

Typical Properties

Not for specifications. Values are typical, not to be considered minimum or maximum.
Properties measured at room temperature 73°F (23°C) unless otherwise stated.

Physical Properties (*See Test Method Table)	Typical Value US units (metric)
Color	Brown
Hardness (Barcol)	40
Specific Gravity (cured)	1.50
Compressive Strength*⁴ 10% Compression	17,500 psi (1230 kg/cm ²)
Tensile Strength*⁵	5280 psi (371 kg/cm ²)
Elongation*⁵ (% at break)	.7
Flexural Strength*⁶ 1/2" x 1/2" sample	9500 psi (668 kg/cm ²)
Electric Strength*¹ 1/8" (3,75 mm) sample	425 v/mil (16,8 kV/mm)
Thermal Conductivity*² Cal • cm/cm ² • sec • °C	8.0 x 10 ⁻⁴
Coefficient of Linear Thermal Expansion*² (23-113°C (73.4-235.4°F) (length/unit length/°C)	5 x 10 ⁻⁵ X 10 ⁻⁶
Thermal shock*² 10 cycles – 55-105°C (131-221°F) 1/4" (6,35 mm) Olyphant Inserts	Passes
Moisture Absorption*² % Weight increases (240 hrs @ 96% R.H.)	.25
Heat Distortion Point*³ (264 psi)	130°C (266 °F)
Flammability*²	Self-Extinguishing
Water Immersion (sample cured 2 hrs. @ 120°C) % Weight Gain 1000 hrs @ 23°C - % weight gain 500 hrs @ 70°C - % weight gain 200 hrs @ 100°C	 .366 1.94 3.27
Thermal Aging 1000 hrs @ 130°C - % Weight Loss Hardness Change, Barcol Dielectric Constant* ⁷ , 100 Hz @ 23°C Dissipation Factor* ¹ , (100 Hz @ 23°C) Volume Resistivity* ⁸ , (Ohm-cm @ 23°C)	 .01 +7 4.35 .48 1 x 10 ¹⁵

* See test method table next page

3M™ Scotchcast™ Electrical Resin 251

Typical Properties, *continued*

Not for specifications. Values are typical, not to be considered minimum or maximum.
Properties measured at room temperature 73°F (23°C) unless otherwise stated.

Physical Properties, <i>continued</i> (See Test Method Table)	Typical Value US units (metric)
Thermal Aging 1000 hrs @ 155°C - % Weight Loss	.46
Hardness Change, Barcol	+8
Dielectric Constant* ⁷ , 100 Hz @23°C)	5.61
Dissipation Factor* ¹ , (100 Hz @23°C)	.54
Volume Resistivity* ⁸ , (Ohm-cm @23°C	1 x 10 ¹⁵
Thermal Aging 1000 hrs @ 180°C - % Weight Loss	1.09
Hardness Change, Barcol	+8
Dielectric Constant* ⁷ , 100 Hz @23°C)	4.80
Dissipation Factor* ¹ , (100 Hz @23°C)	.42
Volume Resistivity* ⁸ , (Ohm-cm @23°C	1 x 10 ¹⁵

Test Methods

¹ – Fed. Std. No. 406, Method 4031	⁵ – Fed. Std. No. 406, Test Method 1011
² – MIL-I-16923E	⁶ – Fed. Std. No. 406, Test Method 1031
³ – ASTM D-648	⁷ – Fed. Std. No. 406, Test Method 4021
⁴ – Fed. Std. No. 406, Method 1021	⁸ – Fed. Std. No. 406, Test Method 4041

Usage Information

Mixing

Mix the separate parts before removing them from their containers. They may be warmed to aid mixing. In the event of crystallization, warm part B to 95 °C (302 °F) and mix to dissolve the crystals. Weigh the correct proportions of the separate parts to within 2% accuracy and combine them. Thoroughly blend the mixture until the color is absolutely uniform or a homogeneous mixture is attained.

De-aerating

Entrained air can be removed by evacuating for 5 -15 minutes at 5-10mm of mercury (Hg) absolute pressure. Warming the resin to 60°C (140°F) aids air removal. The container sidewalls should be four times the height of the liquid resin to contain the foaming that takes place under vacuum.

Casting and Impregnating

Pour the warm resin into the preheated 60-100°C (140-212°F) mold. If no mold is used, dip the preheated part into the resin. Heating the resin and mold aids impregnation. For good impregnation of tightly wound coils, warm the resin to 120°C (248°F), thus lowering its viscosity below 200 centipoise. For maximum impregnation, evacuate for 5-15 minutes at 5mm of mercury (Hg) absolute pressure, or pour under vacuum and hold for several minutes before releasing.

3M™ Scotchcast™ Electrical Resin 251

Usage

Information, *continued*


Curing

Cure using one of the cycles shown under **Handling Properties**. Intermediate cycles may be used if desired. Allow enough time for the resin to reach the curing temperature. For maximum resistance to thermal shock, the resin should be gelled at 75°C (167°F) to minimize stresses in the resin. After gelation, the resin can be post-cured using any of the cure cycles shown under Handling Properties. For critical applications requiring optimum physical and electrical properties, especially at elevated temperatures, a 16-hour post-cure at 150°C (302°F) is suggested.

Handling and Safety Precautions



Read all Health Hazard, Precautionary and First Aid statements found in the Material Safety Data Sheet (MSDS) and/or product label of chemicals prior to handling or use.

Brookfield Viscosity vs. Time
@77°C (170°F) & 93°C (200°F)




3M™ Scotchcast™ Electrical Resin 251

Brookfield Viscosity vs. Time
@23°C (73°F)




DIELECTRIC CONSTANT
Fed. Std. 406, Method 4021
(Test Frequencies in Hertz)



DISSIPATION FACTOR
Fed. Std. 406, Method 4021
(Test Frequencies in Hertz)

VOLUME RESISTIVITY
(OHM-CM)
Fed. Std. 406, Method 4041



3M™ Scotchcast™ Electrical Resin 251

Shelf Life & Storage	All resins have a 2 year shelf life following the date of manufacture when stored in a humidity controlled storage (10°C/50°F to 27°C/80°F and <75% relative humidity). It is 3M's standard procedure to ship any resin product with at least 50% of its shelf life remaining. Any special request for a specific shelf life requirement may require a larger than stated MOQ that justifies a non-scheduled product run. Contact your 3M sale representative or Customer Service for specific shelf life MOQ requirements. No product returns will be accepted on special shelf life request orders.
---------------------------------	-------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------

Availability	Please contact your local distributor; available from 3M.com/electrical/oem [Where to Buy] or call 1-800-676-8381.
---------------------	---------------------------------------------------------------------------------------------------------------------------------------------------------------

Important Notice	All statements, technical information, and recommendations related to 3M's products are based on information believed to be reliable, but the accuracy or completeness is not guaranteed. Before using this product, you must evaluate it and determine if it is suitable for your intended application. You assume all risks and liability associated with such use. Any statements related to the product, which are not contained in 3M's current publications, or any contrary statements contained on your purchase order, shall have no force or effect unless expressly agreed upon, in writing, by an authorized officer of 3M.
-------------------------	-----------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------

Warranty; Limited Remedy; Limited Liability	This product will be free from defects in material and manufacture at the time of purchase. 3M MAKES NO OTHER WARRANTIES INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. If this product is defective within the warranty period stated above, your exclusive remedy shall be, at 3M's option, to replace or repair the 3M product or refund the purchase price of the 3M product. Except where prohibited by law, 3M will not be liable for any indirect, special, incidental or consequential loss or damage arising from this 3M product, regardless of the legal theory asserted.
----------------------------------------------------	-----------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------

3M and Scotchcast are trademarks of 3M Company.



Electrical Markets Division
6801 River Place Blvd.
Austin, TX 78726-9000
800.676.8381
FAX: 800.828.0329
www.3M.com/electrical/oem

Please recycle
© 3M 2013 All rights reserved
78-8124-5681-8 Rev E

Mouser Electronics

Authorized Distributor

Click to View Pricing, Inventory, Delivery & Lifecycle Information:

3M:

7000057523