

#### **Product Description**

3M™ Thermally Conductive Acrylic Interface Pad 5578H is designed to provide a preferential heat transfer path between heat generating components like integrated circuit (IC) chips and heat spreaders such as aluminum heat sinks. 3M pad 5578H consists of a highly conformable slightly tacky acrylic elastomeric sheet filled with conductive ceramic particles.

#### **Key Features**

- · High thermal conductivity
- Good softness and conformability even to non-flat IC surfaces and heat spreading blocks
- Good flame retardant, UL 94 V-0 equivalent material
- No siloxane gas / oil bleeding, which often causes electric connection failure
- Soft compliant material allows for pressure relaxation, preventing high pressure zones on components
- Good electrical insulation properties
- Slight tack allows pre-assembly
- · Good wettability for better thermal conductivity

#### **Product Construction/Material Description**

**Note:** The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

3M™ Thermally Conductive Acrylic Interface Pad 5578H			
Property	Value		
Color	White with light gray dots		
Base resin	Acrylic		
Pad thickness	0.5, 1.0, 1.5, 2.0mm		
Primary filler type	Ceramic		
Product liner	PET film		

### 3M™ Thermally Conductive Acrylic Interface Pad 5578H

PET liner				
Thermally conductive firm layer (less tack)				
Thermally conductive conformable layer				
PET liner				

#### **Applications**

- Integrated circuit (IC) chip packaging heat conduction
- Heat sink interface
- Chip on film (COF) heat conduction
- LED board thermal interface material (TIM)
- HDTV IC chip
- General gap filling in electronic devices

#### **Application Techniques**

Note: Be sure to follow manufacturer's safety precautions and directions for use when using solvents.

Substrate surfaces should be clean and dry prior to the thermal pad application to ensure best thermal performance. A clean surface can improve the thermal performance of an application.

- Isopropyl alcohol (isopropanol) applied with a lint-free wipe or swab should be adequate for removing surface
  contamination such as dust or fingerprints. Do not use "denatured alcohol" or glass cleaners, which often
  contain oily components. Allow the surface to dry for several minutes before applying the thermal pad. More
  aggressive solvents (such as acetone, methyl ethyl ketone (MEK) or toluene) may be required to remove heavier
  contamination (grease, machine oils, solder flux, etc.) but should be followed by a final isopropanol wipe as
  described above.
- Apply the thermal pad to one substrate at a modest angle with the use of a squeegee, rubber roller or finger pressure to help reduce the potential for air entrapment under the thermal pad during its application.
- Remove the release liner before application.
- Assemble the part by applying compression to the substrates to ensure a good wetting of the substrate surfaces
  with the thermal pads. Rigid substrates are more difficult to assemble without air entrapment as most rigid parts
  are not flat. Flexible substrates can be assembled to rigid or flexible parts with much less concern about air
  entrapment because one of the flexible substrate can conform to the other substrates during application.

### **Typical Physical Properties and Performance Characteristics**

Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes. Final product specifications and testing methods will be outlined in the products Certificate of Analysis (COA) that is provided once the product is approved by 3M for general commercialization and development work is completed.

3M™ Thermally Conductive Acrylic Interface Pad 5578H						
Property	Method <sup>a</sup>	Typical Value				
Thickness (mm)	-	0.5, 1.0, 1.5, 2.0				
Thermal conductivity (W/mK) <sup>b</sup>	3M method	3.5				
Hardness (Shore 00)	TS-KOR-217	70				
Density (grams/cm³)	3M method	2.5				
Flammability	UL94	V-0				
Dielectric Strength (kV/mm)	JIS K6249	19				
Volume Resistivity (Ω-cm)	JIS K6249	1.7 x 10 <sup>12</sup>				
Relative Temperature Index (RTI)	UL registration: file no. E239181	140°C (Electric Grade)				

<sup>\*</sup>Note: Tolerances of 1 mm and 1.5 mm =  $\pm$ 1.5 mm =  $\pm$ 1.5 mm.

#### Typical Operating Temperature Range for Acrylic-Based PSAs

3M acrylic conductive pressure sensitive adhesives (CPSAs) contain conductive fillers. The grounding and/or substrate interconnection performance of the conductive fillers within the acrylic PSA in an application will vary based on many factors including substrate types, contact grounding area, surface geometry in the bond line, flexibility of substrates, bonding conditions, applied voltage/current, application environment and environmental aging conditions/exposure.

In general, the acrylic PSA polymer itself used in acrylic CPSAs have good short term and long term environmental stability with respect to the PSAs macro-adhesion performance to many substrates. The acrylic polymers typical long term (days-weeks) performance and short term performance (minutes-hours) based on an adhesion test method is generally 85°C (185°F) long term and 121°C (250°F) short term.

3M CPSAs should be tested in the desired application to ensure the product is appropriate for use based on the application's specific requirements, including substrate types, contact grounding area, surface geometry in the bond line, flexibility of substrates, bonding conditions, applied voltage/current, application environment and environmental aging conditions/exposure.

#### **Heat Resistance**

**Note:** The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

3M™ Thermally Conductive Acrylic Interface Pad 5578H							
Duration (hrs)	Initial	500	1000	2000			
Hardness (Shore 00)	70	70	71	71			
Appearance	-	No effect	No effect	No effect			

<sup>&</sup>lt;sup>1</sup>Aged by dwelling at 130°C high temperature chamber.

### Storage and Shelf Life

The shelf life of 3M<sup>™</sup> Thermally Conductive Acrylic Interface Pad 5578H is 12 months from the date of manufacture when stored in the original packaging materials and stored at 21°C (70°F) and 50% relative humidity.

### **Certificate of Analysis (COA)**

The 3M Certificate of Analysis (COA) for this product is established when the product is commercially available from 3M. The commercially available product will have a COA specification established. The COA contains the 3M specifications and test methods for the products performance limits that the product will be supplied against. The 3M product is supplied to 3M COA test specifications and the COA test methods. Contact your local 3M representative for this product's COA.

This technical data sheet may contain preliminary data and may not match the COA specification limits and/or test methods that may be used for COA purposes.

Final product specifications and testing methods will be outlined in the products Certificate of Analysis (COA) that is shipped with the commercialized product.

<sup>&</sup>lt;sup>2</sup>The end use customer application, design and verification testing will determine the final in use effective temperature range based on each application's environmental conditions.

Safety Data Sheet: Consult Safety Data Sheet before use.

Regulatory: For regulatory information about this product, contact your 3M representative.

Technical Information: The technical information, recommendations and other statements contained in this document are based upon tests or experience that 3M believes are reliable, but the accuracy or completeness of such information is not guaranteed.

Product Use: Many factors beyond 3M's control and uniquely within user's control can affect the use and performance of a 3M product in a particular application. Given the variety of factors that can affect the use and performance of a 3M product, user is solely responsible for evaluating the 3M product and determining whether it is fit for a particular purpose and suitable for user's method of application.

Warranty, Limited Remedy, and Disclaimer: Unless an additional warranty is specifically stated on the applicable 3M product packaging or product literature, 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY OR CONDITION ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OR TRADE. If the 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

Limitation of Liability: Except where prohibited by law, 3M will not be liable for any loss or damage arising from the 3M product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.



Electronics Materials Solutions Division 3M Center, Building 224-3N-11 St. Paul, MN 55144-1000 1-800-251-8634 phone 651-778-4244 fax www.3M.com/electronics

3M is a trademark of 3M Company. Please recycle. ©3M 2018. All rights reserved. 60-5002-0688-7

## **Mouser Electronics**

**Authorized Distributor** 

Click to View Pricing, Inventory, Delivery & Lifecycle Information:

3M:

5578H-05