Primary lithium battery

LS 14500

3.6 V Primary lithium-thionyl chloride (Li-SOCl₂) High energy density AA-size bobbin cell



Benefits

- Enhanced capacity
- High voltage response, stable during most of the lifetime of the application
- Wide operating temperature range (-60°C/+85°C)
- Easy integration into compact system
- Superior resistance to atmospheric corrosion

Key features

- Stainless steel container and end caps (low magnetic signature)
- Hermetic glass-to-metal sealing
- Non-flammable electrolyte
- Low self-discharge rate (less than 1 % after 1 year of storage at + 20°C)
- Compliant with IEC 60079-11 intrinsic safety standard
- Underwriters Laboratories (UL)
 Component Recognition
 (File Number MH 12609)
- Non-restricted for transport


Main applications

- Utility metering
- Automatic meter reading
- Alarms and security devices
- Tollgate systems
- Memory back-up
- Tracking systems
- Automotive electronics
- Professional electronics

Cell size refer	ences		R6 - AA
Electrical charac	teristics		
(typical values relativ	ve to cells stored for one year o	or less at +30°C max	.]
Nominal capacity (at 2 mA + 20°C 2.0 V cut-off. The capacity restored by the cell varies according to current drain, temperature and cut-off)			2.6 Ah
Open circuit voltage	(at +20°C)		3.67 V
Nominal voltage	(at 0.2 mA +20°C)		3.6 V
undischarged cells v 3.0 V. The readings temperature, and th	ically up to 280 mA and pulses, drained every 2 mn a with 10 µA base current, yield wa a may vary according to the puls are cell's previous history. Fitting and in severe conditions. Consult	oltage readings above se characteristics, the the cell with a capaci	9
Maximum recomme (Higher currents pos	nded continuous current ssible, consult Saft)		70 mA
Storage	(recommended) (for more severe conditions, consult Saft)		+ 30°C (+ 86°F) max
Operating temperature range (Operation above ambient T may lead to reduced capacity and lower voltage readings at the beginning of pulses. Consult Saft)			-60°C/+85°C (-76°F/+185°F)
Physical charact	eristics		
Diameter (max)			14.65 mm (0.58 in)
Height (max)			50.3 mm (1.98 in)
Typical weight			16.7 g (~ 0.6 oz)
Li metal content			approx. 0.7 g
Available termination	n suffix CN, CNR 2 PF, 3 PF, 3 PF RP, 4 PF CNA (AX) FL	radial tabs radial pins axial leads flying leads <i>etc</i> .	



LS 14500




Dimensions in mm.

3.8 3.6 3.4 3.2 3.2 3.0 +20°C -40°C 2.4 2.2 0.1 1 10 100 1000

Current (mA)

Voltage plateau versus Current and Temperature (at mid-discharge)




Storage

 The storage area should be clean, cool (preferably not exceeding + 30°C), dry and ventilated.

Warning

- Fire, explosion and burn hazard.
- Do not recharge, short circuit, crush, disassemble, heat above 100°C (212°F), incinerate, or expose contents to water.
- Do not solder directly to the cell (use tabbed cell versions instead).

Restored Capacity versus Current and Temperature (2.0 V cut-off)



Saft Specialty Battery Group

12, rue Sadi Carnot 93170 Bagnolet - France Tel.:+33 (0)1 49 93 19 18 Fax:+33 (0)1 49 93 19 69

www.saftbatteries.com

Doc. Nº 31064-2-0408

Information in this document is subject to change without notice and becomes contractual only after written confirmation by Saft.

For more details on primary lithium technologies please refer to Primary Lithium Batteries Selector Guide Doc N° 31048-2.

Published by the Communications Department.

Photo credit: Saft.

Société anonyme au capital de 31 944 000€

RCS Bobigny B 383 703 873

Produced by Arthur Associates Limited.



Mouser Electronics

Authorized Distributor

Click to View Pricing, Inventory, Delivery & Lifecycle Information:

<u>LS14500 BA</u> <u>LS14500 AX</u> <u>LS14500 ST</u> <u>LS14500-BA</u>