
Low Charging Clear Zipper Overall Width (OW) STATSHIELD® ESD Shielding Bag Contents Metal In Construction Static Sensitive Handling Precautions Required Length (L) DescoIndustries com Lead-free RoHS compliant Bag Date & Lot Code Printed for QC Traceablility Weld Weld

** Bags are printed (hot stamp or thermal) with an ESD protective symbol and a lot code for traceability. **

Side Weld Seals 3/8 in. (±0.10)





Mixed Unsortable Plastic Scrap

Mixed unsortable plastic scrap shall contain assorted plastics of multiple grades that are co-extruded, bonded or laminated together which are unsortable into individual grades

Protektive Pak's bags are recyclable

STATSHIELD® METAL-IN SERIES

Specifications:

Standard Document

ANSI/ESD S541 (ANSI/ESD S20.20) ANSI/ESD S11.4

Electrical Properties

Surface Resistance: Outer Surface Inner Surface Discharge Shielding Charge Generation

Physical Properties

Width (Inside Dimensions)

Length (Inside Dimensions)

Film Thickness

Capacitance Probe (to dissipate 1 KV)

Typical Values

<20 nJ Teflon: 0.09 nC/sq. in.

<30 volts

Nominal 0.0030" (0.0762mm) ±10%

Nominal -0" / + 0.125" Nominal ± 0.125"

Light Transmission >40% (Tobias) Heat Seal >10 lbs/in Tensile Strenath 4600 PSI, 32 MPa Puncture Resistance >10 lbs

Silicone Not detected Marking Adhesion Pass

 $1 \times 10^4 \text{ to} < 1 \times 10^{11} \text{ ohms}$ 1×10^4 to $< 1 \times 10^{11}$ ohms

Quartz: 0.01 nC/sq. in.

Meets Requirements of:

ESD Protective Packaging Level 3 Technical Requirements

Test Procedures/Method

ANSI/ESD STM11.11 ANSI/ESD STM11.11 ANSI/ESD STM11.31, EIA 541

Modified Incline Plane Modified Incline Plane

ANSI/EIA-541/Appendix E, 1kV Discharge

MIL-STD-3010, 1003

ASTM D-1003 375°F, 1/2 sec 60 psi **ASTM 882**

MIL-STD-3010, 2065 ASTM E168

IPC-TM-650 2.4.1

Chemical Properties

No effect on aluminum, copper, silver, Sn-Pb coated foil, Corrosion

stainless steel. low carbon steel

ANSI/ESD S541 Section 6.2 Outside an EPA

"Transportation of sensitive products outside of an EPA shall require packaging that provides:

- 1. Low charge generation
- 2. Dissipative or conductive materials for intimate contact
- 3. A structure that provides electrostatic discharge shielding."

RoHS. REACH and Conflict Minerals Statement

See the Desco Industries RoHS, REACH, and Conflict Minerals Statement: Regulatory Statement Statshield Bags.pdf

See Protektive Pak's Limited Warranty: ProtektivePak.com/Limted-Warranty

Statshield[®] and Statfree[®] are Registered Trademarks of Desco Industries Inc. See Bag Selection Chart Click HERE.


Made in the United States of America

Specifications and procedures subject to change without notice.

Statshield® bags are packaged 100 per package in an oversized shielding bag. See Shielding Bag Storage at TB-7057.

Soft Fold Bottom

STATSHIELD® BAG, SHIELDING, METAL-IN, ZIPPER



13520 MONTE VISTA AVENUE, CHINO, CA 91710 PHONE (909) 627-2578 ProtektivePak.com

DRAWING NUMBER 48720

DATE: September 2021

PROTEKTIVE PAK

Mouser Electronics

Authorized Distributor

Click to View Pricing, Inventory, Delivery & Lifecycle Information:

Protektive Pak: 48720 48724 48731