

2-Layer

Grounding & Cleaning

If the material is used on top of an already properly grounded surface, grounding hardware may not be necessary. Where no properly grounded surface is available, grounding hardware is required to provide a path-to-ground. Rtg compliance verification measurements must be made as outlined in ESD TR53 with a surface resistance meter.

See Tech Bulletin <u>TB-7000</u> for Reztore[®] Surface & Mat Cleaner Application Instructions.

Limited Lifetime Warranty:

Desco warrants for one year that Statfree[®] matting products will be free of defects in materials and workmanship and will guarantee dissipative/conductive mat properties for the life of the mat. Damage to matting caused by misuse of any kind, including using inappropriate cleaners is not covered by <u>Desco Limited Warranty</u>.

RoHS 3, REACH, and Conflict Minerals Statement
See the Desco Industries RoHS 3, REACH, and Conflict Minerals
Statement:

http://www.descoindustries.com/ROHS3.aspx

See the Desco Limited Warranty:

http://desco.descoindustries.com/Limited-Warranty.aspx

See the Desco Disclaimer:

http://desco.descoindustries.com/Disclaimer.aspx

Specifications and procedures subject to change without notice.

DESCO

STATFREE® T2 PLUS DISSIPATIVE RUBBER



Specifications

Standard Document Meets Requirements of:

ANSI/ESD S20.20 Worksurface

Electrical Properties Typical Values
Dissipative Surface Laver

Rtt Resistance: 1×10^6 to $< 1 \times 10^9$ ohms ANSI/ESD S4.1 and ESD TR53 Rtg Resistance: 1×10^6 to $< 1 \times 10^9$ ohms ANSI/ESD S4.1 and ESD TR53

Ground Plane Layer

Rtt Resistance: < 1 x 10⁶ ohms ANSI/ESD S4.1 and ESD TR53

Physical Properties

Construction: Dual-layer rubber material¹

Thickness: 0.060" (1.5mm)

Color:² Blue (Top), Dark Blue (Top), Dark Grey (Top), Green (Top), Black (Bottom)

Embossing:² Slight Texture

Weight: 0.43 lbs./sq. ft. (0.2g/cm2)

Hardness: 65 ± 5 Shore "A", per ASTM-D2240

Other Properties

Heat Resistance: Does not melt or burn when coming into contact with hot solder and soldering irons.

Chemical Resistance: Resistance to degradation by inorganic acids, organic acids, reducing agents, aliphatic

Test Procedures/Method

hydrocarbons, mineral oil, aldehydes, and amines.

Oil Absorption Resistance: Resists oil absorption to maintain physical and electrical properties.

Tolerances:

Width ± 0.250"

Length ± 0.250" every 1 linear foot of running material.

Thickness ±10%

Matting materials have a tendency to shrink slightly when first unrolled. In applications where length is critical, allow the material to condition for at least 4 hours before cutting to size. Always using care trim with a sharp knife or razor blade.

*Color and texture may vary between lots and mills.

For product listings, Click Here

**Tray liners have 3/4" radius corners and do not include grounding hardware.



Made in the United States of America

STATFREE® T2 PLUS DISSIPATIVE, RUBBER, 2-LAYER, 0.060" (1.5mm)

DESCO WEST: 3651 WALNUT AVE., CHINO, CA 91710 WEB SITE: <u>Desco.com</u> PHONE (909) 627-8178

DESCO EAST: ONE COLGATE WAY, CANTON, MA 02021-1407 PHONE (781) 821-8370

MATERIAL STATFREE® T2 Plus DRAWING PM-132

DATE: March 2021

¹Rubber material is vulcanized and may contain sulfur ²Color and texture may vary between lots and mills

Mouser Electronics

Authorized Distributor

Click to View Pricing, Inventory, Delivery & Lifecycle Information:

Desco:

66406 66407 66412 66413 66414 66415 66416 66417