

## Electrical Details

Maximum Capacitance	5.6μF
Temperature Coefficient of Capacitance (TCC)	±15% from -55°C to +125°C
Dissipation Factor	≤ 0.025
Insulation Resistance (IR)	100GΩ or 500secs (whichever is the less)
Dielectric Withstand Voltage (DWV)	Voltage applied for 5 ±1 seconds, 50mA charging current maximum
Ageing Rate	<2% per decade

Size	Length (L1)	Width (W)	Max Thickness (T)	Band (L2)
1812	4.5 ± 0.40	3.2 ± 0.3	3.5	0.25 - 1.1
2220	5.7 ± 0.4	5.0 ± 0.4	4.5	0.25 - 1.1
2225	5.7 ± 0.4	6.3 ± 0.4	4.5	0.25 - 1.1
3640	9.2 ± 0.5	10.16 ± 0.5	4.5	0.50 - 1.5

The StackiCap™ range offers a significant reduction in 'PCB real estate' for an equivalent capacitance value when board space is at a premium.

Knowles unique patented\* construction and FlexiCap™ termination material make the StackiCap™ range suitable for applications including: power supplies, lighting, aerospace electronics and high voltage applications where a large amount of capacitance is required. Further developments are on-going, please contact the Sales Office for details of the full range

Recent material development has enabled these parts to offer significant cost savings against conventional stacked and leaded capacitors, reflected by their application in commercial and automotive applications.

\* StackiCap™ technology is protected by international patents (pending) GB2502971 A, EP2847776, TW201405604 A, US2015-0146343 A1 & CN104471660 A

## Available Range and Comparison Chart – StackiCap™ Capacitors

Chip Size	Suffix Code Applied	Voltage	StackiCap™ Range Maximum (nF)	Non-StackiCap™ Range (nF)	Replaces Case Size
1812	WS2	200/250V	1000	680	2220
	WS2	500V	470	330	2220
	WS2	630V	330	180	2220
	WS2	1kV	180	100	2225/3640
	WS3	1.2kV	100	33	2225
	WS3	1.5kV	56	22	2225
2220	WS2	200V/250V	2200	1500	3640
	WS2	500V	1200	680	3640
	WS2	630V	1000	330	5550
	WS2	1kV	470	120	8060
	WS3	1.2kV	220	82	5550
	WS3	1.5kV	150	47	5550
	WS3	2kV	100	33	8060
2225	WS2	200V/250V	2200	1800	3640
	WS2	500V	1200	1000	3640
	WS2	630V	1000	680	5550
3640	WS2	200/250V	5600	3300	5550
	WS2	500V	2700	1200	8060
	WS2	630V	2200	680	8060
	WS2	1kV	1000	220	8060
	WS3	1.2kV	470	180	8060
	WS3	1.5kV	330	100	8060
	WS3	2kV	150	56	8060

**Yellow highlighted ranges are available with AEC-Q200 qualification**

The performance of StackiCap range parts with a voltage rating  $\geq 1.2kV$  can be demonstrated to significantly improve if the parts and boards are coated after assembly. We therefore recommend that this is done wherever possible, and especially when used in high-reliability applications, for those parts identified with suffix code WS3.

Note : AEC-Q200 qualification of parts with a voltage rating  $\geq 1.2kV$  was completed with parts coated after mounting to test boards. Lower voltage parts may also benefit from coating post assembly to maximise reliability.

Knowles have an application note on product coating and board design for high voltage applications available on our website or on request. AN0045 Design and coating of circuit board assemblies to limit flashover of MLCCs

## Ordering Information – StackiCap™ Range

1812	Y	500	0474	K	J	T	WS2
Chip Size	Termination	Voltage d.c. (marking code)	Capacitance in Pico farads (pF)	Capacitance Tolerance	Dielectric Codes	Packaging	Suffix Code
<b>1812</b> <b>2220</b> <b>2225</b> <b>3640</b> <b>5550</b> <b>8060</b> (refer to factory)	<b>Y</b> = FlexiCap™ termination base with nickel barrier (100% matte tin plating). RoHS compliant.  <b>H</b> = FlexiCap™ termination base with nickel barrier (tin/lead plating with min. 10% lead). Not RoHS compliant.  <b>7</b> = FlexiCap™ Polymer termination, Nickel barrier, Sn/Pb Plated Solder (5-20% Lead, non RoHS)	<b>200/250</b> = 200V/250V <b>500</b> = 500V <b>630</b> = 630V <b>1K0</b> = 1kV <b>1K2</b> = 1.2kV <b>1K5</b> = 1.5kV <b>2K0</b> = 2kV	First digit is 0. Second and third digits are significant figures of capacitance code. The fourth digit is the number of zeros following. e.g., <b>0474</b> = 470nF Values are E12 series	<b>J</b> : ± 5% <b>K</b> : ± 10% <b>M</b> : ± 20%	<b>X</b> = X7R  <b>E</b> = X7R (2R1) AEC- Q200  <b>J</b> = X7R (2R1) - Ni Electrode Stackicap  <b>S</b> = X7R (2R1) AEC- Q200	<b>T</b> = 178mm (7") reel <b>R</b> = 330mm (13") reel  <b>B</b> = Bulk pack – tubs or trays	<b>WS2</b> <b>WS3</b>

\*WS3 – coating after assembly to board should be considered essential for these higher voltage components. Knowles application note AN0045 gives advice and recommendations on coating of circuit boards and circuit board design for high voltage components

## Reeled Quantities – StackiCap™ Capacitors

	1812	2220	2225	3640
178mm (7") Reel	500	500	500	-
330mm (13") Reel	2,000	2,000	2,000	500

## Soldering Information

Knowles (Syfer) MLCCs are compatible with all recognised soldering/mounting methods for chip capacitors. A detailed application note is available at [www.knowlesc capacitors.com/syfer](http://www.knowlesc capacitors.com/syfer)

### Reflow Soldering

Knowles (Syfer) recommend reflow soldering as the preferred method for mounting MLCCs. Knowles (Syfer) MLCCs can be reflow soldered using a reflow profile generally defined in IPC/FEDEC J-STD-020. Sn plated termination chip capacitors are compatible with both conventional and lead free soldering with peak temperatures of 260 to 270°C acceptable.

The heating ramp rate should be such that components see a temperature rise of 1.5 to 4°C per second to maintain temperature uniformity through the MLCC.

The time for which the solder is molten should be maintained at a minimum, so as to prevent solder leaching. Extended times above 230°C can cause problems with oxidation of Sn plating. Use of an inert atmosphere can help if this problem is encountered. Palladium/Silver (Pd/Ag) terminations can be particularly susceptible to leaching with free lead, tin rich solders and trials are recommended for this combination.

Cooling to ambient temperature should be allowed to occur naturally, particularly if larger chip sizes are being soldered. Natural cooling allows a gradual relaxation of thermal mismatch stresses in the solder joints. Forced cooling should be avoided as this can induce thermal breakage.

### Wave Soldering

Wave soldering is generally acceptable, but the thermal stresses caused by the wave have been shown to lead to potential problems with larger or thicker chips. Particular care should be taken when soldering SM chips larger than size 1210 and with a thickness greater than 1.0mm for this reason. Maximum permissible wave temperature is 270°C for SM chips.

The total immersion time in solder should be kept to a minimum. It is strongly recommended that Sn/Ni plated terminations are specified for wave soldering applications.


### Solder Leaching

Leaching is the term for the dissolution of silver into the solder causing a failure of the termination system which causes increased ESR, tan  $\delta$  and open circuit faults, including ultimately the possibility of the chip becoming detached.

Leaching occurs more readily with higher temperature solders and solders with a high tin content. Pb free solders can be very prone to leaching certain termination systems. To prevent leaching, exercise care when choosing solder allows and minimize both maximum temperature and dwell time with the molten solder.

Plated terminations with nickel or copper anti-leaching barrier layers are available in a range of top coat finishes to prevent leaching occurring. These finishes also include Knowles (Syfer) FlexiCap™ for improved stress resistance post soldering.

### Multilayer ceramic chip with nickel or copper barrier termination



## Rework of Chip Capacitors

Knowles (Syfer) recommend hot air/gas as the preferred method of applying heat for rework. Apply even heat surrounding the component to minimise internal thermal gradients. Soldering irons or other techniques that apply direct heat to the chip or surrounding area, should not be used as these can result in micro cracks being generated.

Minimise the rework heat duration and allow components to cool naturally after soldering.

### Use of Silver Loaded Epoxy Adhesives

Chip capacitors can be mounted to circuit boards using silver loaded adhesive provided the termination material of the capacitor is selected to be compatible with the adhesive. This is normally PdAg. Standard tin finishes are often not recommended for use with silver loaded epoxies as there can be electrical and mechanical issues with the joint integrity due to material mismatch.

## Handling & Storage

Components should never be handled with fingers; perspiration and skin oils can inhibit solderability and will aggravate cleaning.

Chip capacitors should never be handled with metallic instruments. Metal tweezers should never be used as these can chip the product and leave abraded metal tracks on the product surface. Plastic or plastic coated metal types are readily available and recommended – these should be used with an absolute minimum of applied pressure.

Incorrect storage can lead to problems for the user. Rapid tarnishing of the terminations, with an associated degradation of solderability, will occur if the product comes into contact with industrial gases such as sulphur dioxide and chlorine. Storage in free air, particularly moist or polluted air, can result in termination oxidation.

Packaging should not be opened until the MLCs are required for use. If opened, the pack should be re-sealed as soon as practicable. Alternatively, the contents could be kept in a sealed container with an environmental control agent.

Long term storage conditions, ideally, should be temperature controlled between -5 and +40°C and humidity controlled between 40% and 60% R.H.

Taped product should be stored out of direct sunlight, which might promote deterioration in tape or adhesive performance.

Product, stored under the conditions recommended above, in its "as received" packaging, has a minimum shelf life of 2 years.

## SM Pad Design

Knowles (Syfer) conventional 2-terminal chip capacitors can generally be mounted using pad designs in accordance with IPC-7351, Generic Requirements for Surface Mount Design and Land Pattern Standards, but there are some other factors that have been shown to reduce mechanical stress, such as reducing the pad width to less than the chip width. In addition, the position of the chip on the board should also be considered.

3-terminal components are not specifically covered by IPC-7351, but recommended pad dimensions are included in the Knowles (Syfer) catalogue/website for these components.


## FlexiCap™ Termination

FlexiCap™ has been developed as a result of listening to customer's experiences of stress damage to MLCCs from many manufacturers, often caused by variations in production processes.

Our answer is a proprietary flexible epoxy polymer termination material that is applied to the device under the usual nickel barrier finish. FlexiCap™ will accommodate a greater degree of board bending than conventional capacitors.

Ranges are available with FlexiCap™ termination material offering increased reliability and superior mechanical performance (board flex and temperature cycling) when compared with standard termination materials. Refer to Knowles (Syfer) application note reference AN0001. FlexiCap™ capacitors enable the board to be bent almost twice as much as before mechanical cracking occurs. Refer to application note AN0002.

FlexiCap™ is also suitable for space applications having passed thermal vacuum outgassing tests. Refer to Knowles (Syfer) application note reference AN0026.



FlexiCap™ MLCC cross section

Knowles (Syfer) has delivered millions of FlexiCap™ components and during that time has collected substantial test and reliability data, working in partnership with customers world wide, to eliminate mechanical cracking.

An additional benefit of FlexiCap™ is that MLCCs can withstand temperature cycling from -55 to 125°C in excess of 1,000 times without cracking.

FlexiCap™ termination has no adverse effect on any electrical parameters, nor affects the operation of the MLCC in any way.

### Application Notes

FlexiCap™ may be handled, stored and transported in the same manner as standard terminated capacitors. The requirements for mounting and soldering FlexiCap™ are the same as for standard SMD capacitors.

For customers currently using standard terminated capacitors there should be requirement to change the assembly process when converting to FlexiCap™.

Based upon the board bend tests in accordance with IEC 60384-1 the amount of board bending required to mechanically crack a FlexiCap™ terminated capacitor is significantly increased compared with standard terminated capacitors.

Product: X7R	Typical bend performance under AEC-Q200 test conditions
Standard Termination	2mm to 3mm
FlexiCap™	Typically 8mm to 10mm

## REACH (Registration, Evaluation, Authorisation and restriction of Chemicals) Statement

The main purpose of REACH is to improve the protection of human health and the environment from the risks arising from the use of chemicals.

Knowles (UK) Ltd maintains both ISO 14001, Environmental Management System and OHSAS 18001 Health & Safety Management System approvals that require and ensure compliance with corresponding legislation such as REACH.

For further information, please contact the sales office at [SyferSales@knowles.com](mailto:SyferSales@knowles.com)

## RoHS Compliance

Knowles (Syfer) routinely monitors world wide material restrictions (e.g., EU/China and Korea RoHS mandates) and is actively involved in shaping future legislation.

All standard C0G/NPO, X7R, X5R and High Q Knowles (Syfer) MLCC products are compliant with the EU RoHS directive (see below for special exemptions) and those with plated terminations are suitable for soldering common lead free solder alloys (refer to 'Soldering Information' for more details on soldering limitations). Compliance with EU RoHS directive automatically signifies compliance with some other legislation (e.g., Korea RoHS). Please refer to the Sales Office for details of compliance with other materials legislation.

Breakdown of material content, SGS analysis reports and tin whisker test results are available on request.

Most Knowles (Syfer) MLCC components are available with non-RoHS compliant tin/lead (SnPb) Solderable termination finish for exempt applications and where pure tin is not acceptable. Other tin free termination finishes may also be available – please refer to the Sales Office for further details.

X8R ranges <250Vdc are not RoHS 2011/65/EU compliant.

115Vac 400Hz ranges are not RoHS 2011/65/EU compliant.

Check the website, [www.knowlesc capacitors.com/syfer](http://www.knowlesc capacitors.com/syfer) for latest RoHS update.

## Export Controls and Dual-use Regulations

Certain Knowles (Syfer) catalogue components are defined as 'dual-use' items under international export controls – those that can be used for civil and military purposes which meet certain specified technical standards.

The defining criteria for a dual-use component with respect to Knowles (Syfer) products is one with a voltage rating of >750V and a capacitance value >250nF and a series inductance <10nH.

Components defined as 'dual-use' under the above criteria automatically require a licence for export outside the EU, and may require a licence for export with the EU.

The application for a licence is routine, but customers for these products will be asked to supply further information.

Please refer to the sales office if you require any further information on export restrictions.

Other special components may additionally need to comply with export regulations.

## Ageing of Ceramic Capacitors

Capacitor ageing is a term used to describe the negative, logarithmic capacitance change which takes place in ceramic capacitors with time. The crystalline structure for barium titanate based ceramics changes on passing through its Curie temperature (known as the Curie Point) at about 125°C. The domain structure relaxes with time and in doing so, the dielectric constant reduces logarithmically; this is known as the ageing mechanism of the dielectric constant. The more stable dielectrics have the lowest ageing rates.

The ageing process is reversible and repeatable. Whenever the capacitor is heated to a temperature above the Curie Point the ageing process starts again from zero.

The ageing constant, or ageing rate, is defined as the percentage loss of capacitance due to the ageing process of the dielectric which occurs during a decade of time (a tenfold increase in age) and is expressed as percent per logarithmic decade of hours. As the law of decrease of capacitance is logarithmic, this means that for a capacitor with an ageing rate of 1% per decade of time, the capacitance will decrease at a rate of:

- 1% between 1 and 10 hours
- An additional 1% between the following 10 and 100 hours
- An additional 1% between the following 100 and 1000 hours
- An additional 1% between the following 1000 and 10000 hours
- The ageing rate continues in this manner throughout the capacitor's life.

Typical values of the ageing constant for our MLCCs are

Dielectric Class	Typical Values
Ultra Stable C0G/NP0	Negligible capacitance loss through ageing
Stable X7R	<2% per decade of time

## Capacitance Measurements


Because of ageing it is necessary to specify an age for reference measurements at which the capacitance shall be within the prescribed tolerance. This is fixed at 1000 hours, since for all practical purposes there is not much further loss of capacitance after this time.

All capacitors shipped are within their specified tolerance at the standard reference age of 1000 hours after having cooled through their Curie temperature.

The ageing curve for any ceramic dielectric is a straight line when plotted on semi-log paper.

## Capacitance vs. Time

(Ageing X7R @ 1% per decade)



© Knowles 2014

## Tight Tolerance

One of the advantages of Knowles (Syfer)'s unique 'wet process' of manufacture is the ability to offer capacitors with exceptionally tight capacitance tolerances.

The accuracy of the printing screens used in the fully automated, computer controlled manufacturing process allows for tolerance as close as  $\pm 1\%$  on C0G/NP0 parts greater than or equal to 10pF. For capacitance value less than 4.7pF tolerances can be as tight as  $\pm 0.05\text{pF}$ .

## Periodic Tests Conducted and Reliability Data

For standard surface mount capacitors components are randomly selected on a sample basis and the following routine tests conducted:

- Load Test. 1,000 hours @ 125°C (150°C for X8R). Applied voltage depends on components tested
- Humidity Test. 168 hours @ 85°C/85%RH
- Board Deflection (bend test)

Test results are available on request.


## Conversion Factors

From	To	Operation
FITs	MTBF (hours)	$10^9 \div \text{FITs}$
FITs	MTBF (years)	$10^9 \div (\text{FITs} \times 8760)$

FIT = Failures In Time. 1 FIT = 1 failure in  $10^9$  hours

MTBF = Mean Time Between Failure

## Example of FIT Data Available



Component type: 0805 (C0G/NP0 and X7R)


Testing Location: Knowles (Syfer) reliability test department

Results based on: 16,622,000 component test hours



## Packaging Information


Tape and reel packing of surface mounting chip capacitors for automatic placement are in accordance with IEC60286-3.



## Peel Force


The peel force of the top sealing tape is between 0.2 and 1.0 Newton at 180°. The breaking force of the carrier and sealing tape in the direction of unreeling is greater than 10 Newton.

## Reel Dimensions



Symbol	Description	178mm Reel	330mm Reel
A	Reel diameter	178 (7)	330 (13)
G	Reel inside width	8.4 (0.33)	12.4 (0.49)
T	Reel outside width	14.4 (0.56) max	18.4 (0.72) max

## Tape Dimensions



		Dimensions mm (inches)	
Symbol	Description	8mm Tape	12mm Tape
A <sub>0</sub>	Width of cavity	Dependent on chip size to minimize rotation	
B <sub>0</sub>	Length of cavity		
K <sub>0</sub>	Depth of cavity		
W	Width of tape	8.0 (0.315)	12.0 (0.472)
F	Distance between drive hole centres and cavity centres	3.5 (0.138)	5.5 (0.213)
E	Distance between drive hole centres and tape edge	1.75 (0.069)	
P <sub>1</sub>	Distance between cavity centres	4.0 (0.156)	8.0 (0.315)
P <sub>2</sub>	Axial distance between drive hole centres and cavity centres	2.0 (0.079)	
P <sub>0</sub>	Axial distance between drive hole centres	4.0 (0.156)	
D <sub>0</sub>	Drive hole diameter	1.5 (0.059)	
D <sub>1</sub>	Diameter of cavity piercing	1.0 (0.039)	1.5 (0.059)
T	Carrier tape thickness	0.3 (0.012) ±0.1 (0.04)	0.4 (0.016) ±0.1 (0.04)
t <sub>1</sub>	Top tape thickness	0.1 (0.004) max	

## Packing Information

### Missing Components

The number of missing components in the tape may not exceed 0.25% of the total quantity with not more than three consecutive components missing. This must be followed by at least six properly placed components

### Identification



Each reel is labelled with the following information: manufacturer, chip size, capacitance, tolerance, rated voltage, dielectric type, batch number, date code and quantity of components.

### Component Orientation

Tape and reeling is in accordance with IEC 60286 parts 3, which defines the packaging specifications for leadless components on continuous tapes.

- Notes:
- 1) IEC60286-3 states A0 <B0
  - 2) Regarding the orientation of 1825 and 2225 components, the termination bands are right to left, NOT front to back. Please see diagram.

## Leader Trailer




Orientation of 1825 & 2225 components

## Outer Packaging

Outer carton dimensions mm (inches) max

Reel Size	No. of Reels	L	W	T
178 (7)	1	185 (7.28)	185 (7.28)	25 (0.98)
178 (7)	4	190 (7.48)	195 (7.76)	75 (2.95)
330 (13)	1	335 (13.19)	335 (13.19)	25 (0.98)



Note: Labelling of box and reel with bar codes (Code 39) available by arrangement.

## Reel Quantities

Chip Size		1812	2220	2225	3640
Reel Quantities	178mm (7")	500	500	500	
	330mm (13")	2000	2000	2000	500

### Notes:


- 1) The above quantities per reel are for the maximum manufactured chip thickness. Thinner chips can be taped in larger quantities per reel.
- 2) Where two different quantities are shown for the same case size, please contact the sales office to determine the exact quantity for any specific part number.

## Bulk Packing – Tubs

Chips are supplied in rigid re-sealable plastic tubs together with impact cushioning wadding. Tubs are labelled with the details: chip size, capacitance, tolerance, rated voltage, dielectric type, batch number, date code and quantity of components.

### Dimensions mm (inches)

H	60mm (2.36")
D	50mm (1.97")





# Mouser Electronics

Authorized Distributor

Click to View Pricing, Inventory, Delivery & Lifecycle Information:

[Knowles:](#)

<a href="#"><u>1812Y1K00154KXTWS2</u></a>	<a href="#"><u>1812Y5000474KXTWS2</u></a>	<a href="#"><u>1812Y2000105KXTWS2</u></a>	<a href="#"><u>2220Y1K00474KXTWS2</u></a>
<a href="#"><u>2220Y2K00104KXTWS2</u></a>	<a href="#"><u>2220Y2K00104KXRWS2</u></a>	<a href="#"><u>2220Y1K00474KXRWS2</u></a>	<a href="#"><u>2220Y2K00104KXBWS2</u></a>
<a href="#"><u>1812Y1K00104KJTWS2</u></a>	<a href="#"><u>1812Y5000394KJTWS2</u></a>	<a href="#"><u>1812Y6300224KJTWS2</u></a>	<a href="#"><u>2220Y6300474KJTWS2</u></a>
<a href="#"><u>2220Y5000105KJTWS2</u></a>	<a href="#"><u>1812Y1K00154KJTWS2</u></a>	<a href="#"><u>2220Y1K00474KJTWS2</u></a>	<a href="#"><u>2220Y2500225KJTWS2</u></a>
<a href="#"><u>1812Y1K20104KJTWS2</u></a>	<a href="#"><u>1812Y2500105KJTWS2</u></a>	<a href="#"><u>2220Y1K20224KXTWS2</u></a>	<a href="#"><u>1812Y6300334KETWS2</u></a>
<a href="#"><u>1812Y5000474KETWS2</u></a>	<a href="#"><u>1812Y1K00184KETWS2</u></a>	<a href="#"><u>2220Y6300105KETWS2</u></a>	<a href="#"><u>2220Y1K00474KETWS2</u></a>
<a href="#"><u>1812Y2500105KETWS2</u></a>	<a href="#"><u>3640Y1K00105KETWS2</u></a>	<a href="#"><u>1812Y1K00104KSTWS2</u></a>	<a href="#"><u>1812Y2500105KSTWS2</u></a>
<a href="#"><u>1812Y2500105KXTWS2</u></a>	<a href="#"><u>2220Y6300474KXTWS2</u></a>	<a href="#"><u>1812Y6300224KXTWS2</u></a>	<a href="#"><u>1812Y1K20104KXTWS2</u></a>
<a href="#"><u>1812Y1K00104KETWS2</u></a>	<a href="#"><u>1812Y6300224MXTWS2</u></a>	<a href="#"><u>2220Y1K00474KETWS3</u></a>	<a href="#"><u>2220Y1K00474KJTWS3</u></a>
<a href="#"><u>2220Y1K00474KXRWS3</u></a>	<a href="#"><u>2220Y1K00474KXTWS3</u></a>	<a href="#"><u>2220Y2500225KJTWS3</u></a>	<a href="#"><u>2220Y2K00104KXBWS3</u></a>
<a href="#"><u>2220Y2K00104KXRWS3</u></a>	<a href="#"><u>2220Y5000105KJTWS3</u></a>	<a href="#"><u>2220Y5000105KXTWS3</u></a>	<a href="#"><u>2220Y6300105KETWS3</u></a>
<a href="#"><u>2220Y6300474KJTWS3</u></a>	<a href="#"><u>2220Y6300474KXTWS3</u></a>	<a href="#"><u>2220Y2K00104KXTWS3</u></a>	<a href="#"><u>2220Y1K20224KXTWS3</u></a>
<a href="#"><u>2220Y1K50154KXTWS3</u></a>	<a href="#"><u>1812Y1K20104KXTWS3</u></a>	<a href="#"><u>2220H6300105KETWS2</u></a>	<a href="#"><u>2220Y1K00474JXTWS2</u></a>
<a href="#"><u>3640Y1K00105KXRWS2</u></a>	<a href="#"><u>2220Y5000105JXTWS2</u></a>		