

QD-2000



SEMI-RIGID, ADHESIVE LINED HEAT SHRINKABLE TUBING **FLAME RETARDANT SHRINK RATIO 4:1**

Features/Applications

Specially designed to protect splices and joint of wire harness, and components against environmental damage. 4:1 shrink ratio allows it to easily fit a wide range of components, and thicker adhesive coated layer forms an effective barrier against fluids and moisture.

• Operating temperature: -40°C to +130°C • Minimum shrink temperature: 110°C • Minimum Full recovery temperature: 135°C

• Meets: Flame Retardant and UV Resistant (Black only)

• Standard colors: Black and Clear

• RoHS Compliant



Property	Test Method	Test Requirements		
Tensile Strength	ASTM D 2671	>10.4 MPa		
Ultimate Elongation	ASTM D 2671	250% minimum		
Secant Modulus	ASTM D 2671	137MPa minimum		
Heat Shock	225°C, 4 hrs.	No cracking, no dropping		
Flammability	ISO 6722-1	Self extinguish in 30 seconds		
Cold Bend (-30°C, 4 hr.)	UL 224	No cracking		
Heat aging 130°C for 3000Hrs followed by immersion leak resistance	GMW 17136	Max. 5µA		
Volume Resistance	ASTM D 2671	>10 ¹² Ω.cm		
Resistance to Liquid Chemicals Water Tightness	GMW 17136	Max. 5µA		

Product Dimensions									
Size	As Supplied (mm)	After Recovered (mm)				Standard Packaging			
	Inside Diameter (min.)	Inside Diameter (max.)	Wall Thickness (min.)	Adhesive Thickness (nom.)	Cut to Length Pcs. (QB)* Qty per bag				
					6"	48"			
1	5.72	1.27	1.20	0.56	20	5			
2	7.44	1.65	1.52	0.76	16	5			
3	10.85	2.41	1.91	1.02	14	5			
4	17.78	4.45	2.41	1.37	12	5			

Notes:

1. * See Part Number Guide for standard packaging codes.

Cross Reference Guide available.

Special sizes, packaging, colors and cut pieces are available upon request.

Mouser Electronics

Authorized Distributor

Click to View Pricing, Inventory, Delivery & Lifecycle Information:

Qualtek:

QD-2000-1-01-QB48IN-5 QD-2000-2-01-QB48IN-5 QD-2000-4-01-QB48IN-5 QD-2000-3-01-QB48IN-5