

SPECIFICATION CONTROL DRAWING		FLHT+0311	
TITLE	HIGH TEMPERATURE HOOKUP WIRE, RADIATION-CROSSLINKED, MODIFIED ETFE-INSULATED, 600 VOLT	Date 7-21-14	Revision Z
The complete requirements for procuring the wire described herein shall consist of this document and the issue in effect of Raychem Specification WCD 3106, UL Subject 758, Style 3557, File E303150 and carries UL labels to this effect.			




TABLE I. CONSTRUCTION DETAILS								
PART NUMBER 1/	WIRE SIZE (AWG)	CONDUCTOR STRANDING (number x AWG) or (number x SEOD) (inch) (mm)	NOMINAL CONDUCTOR DIAMETER (inch) (mm)	FINISHED WIRE				
				MAXIMUM RESISTANCE AT 20°C (ohms/1000 ft.) (ohms/km)	DIAMETER (inch) (mm)			NOMINAL WEIGHT (lbs/1000 ft.) (kg/km)
					MINIMUM	NOMINAL	MAXIMUM	
FLHTB0311-18-*	18	7 x 26	.047 (1.19)	7.06 (23.2)	.0584 (1.48)	.0601 (1.53)	.0618 (1.57)	5.95 (8.85)
FLHTB0311-16-*	16	7 x 24	.060 (1.52)	4.45 (14.6)	.0731 (1.86)	.0750 (1.91)	.0769 (1.95)	9.75 (14.5)
FLHTB0311-14-*	14	7 x .0242 (.615)	.073 (1.85)	2.90 (9.51)	.0865 (2.20)	.0886 (2.25)	.0907 (2.30)	14.6 (21.7)
FLHTC0311-26-*	26	19 x 38	.019 (.483)	45.8 (150.)	.0301 (.765)	.0315 (.800)	.0329 (.836)	1.27 (1.89)
FLHTC0311-24-*	24	19 x 36	.024 (.610)	28.7 (94.2)	.0351 (.892)	.0365 (.927)	.0379 (.963)	1.85 (2.75)
FLHTC0311-22-*	22	19 x 34	.030 (.762)	18.1 (59.4)	.0411 (1.04)	.0425 (1.08)	.0439 (1.12)	2.74 (4.08)
FLHTC0311-20-*	20	19 x 32	.038 (.965)	11.4 (37.4)	.0491 (1.25)	.0505 (1.28)	.0519 (1.32)	4.17 (6.21)
FLHTC0311-18-*	18	19 x 30	.047 (1.19)	7.15 (23.5)	.0583 (1.48)	.0600 (1.52)	.0617 (1.57)	6.34 (9.43)
FLHTC0311-16-*	16	19 x 29	.053 (1.35)	4.82 (15.8)	.0656 (1.67)	.0675 (1.71)	.0694 (1.76)	8.09 (12.0)
FLHTC0311-14-*	14	19 x 27	.066 (1.68)	3.05 (10.0)	.0799 (2.03)	.0820 (2.08)	.0841 (2.14)	12.5 (18.6)
FLHTC0311-12-*	12	19 x 25	.090 (2.29)	1.92 (6.30)	.1035 (2.63)	.1060 (2.69)	.1085 (2.76)	22.4 (33.3)
FLHTD0311-14-*	14	37 x 30	.068 (1.73)	3.22 (10.6)	.0819 (2.08)	.0840 (2.13)	.0861 (2.19)	14.5 (21.6)
FLHTD0311-12-*	12	37 x 28	.085 (2.16)	2.01 (6.59)	.0984 (2.50)	.1010 (2.57)	.1036 (2.63)	19.3 (28.7)
FLHTD0311-10-*	10	37 x 26	.107 (2.72)	1.26 (4.13)	.121 (3.07)	.125 (3.18)	.129 (3.28)	30.7 (45.7)
FLHTE0311-8-*	8	133 x 29	.160 (4.06)	.701 (2.30)	.175 (4.45)	.180 (4.57)	.185 (4.70)	54.9 (81.7)

Due to UL limitations on the usage of small strand bare and tin plated conductors, products with conductor strand diameters less than .015 inch (.381 mm) are intended for dry locations only. For wet locations, other UL recognized products are available.

Users should evaluate the suitability of this product for their application. Specifications are subject to change without notice. Tyco Electronics Corporation also reserves the right to make changes in materials or processing, which do not affect compliance with any specification, without notification to Buyer.			
1/ COLORS AND COLOR CODE DESIGNATORS SHALL BE IN ACCORDANCE WITH MIL-STD-681. OTHER CODES AND SUFFIXES MAY BE ADDED TO THE PART NUMBER, AS NECESSARY, TO CAPTURE ANY ADDITIONAL REQUIREMENTS IMPOSED BY THE PURCHASE ORDER.			
Page 1 of 2	Raychem, TE Connectivity, TE connectivity (logo), and TE (logo) are trademarks.		 Raychem Wire & Cable 501 Oakside Avenue Redwood City, CA 94063-3800 Phone: 1-800-227-8816 Fax: 1-650-361-6297
	DIMENSIONS ARE IN INCHES AND, UNLESS OTHERWISE DESIGNATED, ARE NOMINAL.		
	THIS SPECIFICATION SHEET TAKES PRECEDENCE OVER DOCUMENTS REFERENCED HEREIN. REFERENCED DOCUMENTS SHALL BE OF THE ISSUE IN EFFECT ON DATE OF INVITATION FOR BID.		

TABLE II. PERFORMANCE DETAILS

PART NUMBER <u>1/</u>	BEND TESTING	
	MANDREL DIAMETER (inch) (mm) (± 3%)	WEIGHT (lb) (kg) (± 3%)
	CROSSLINK VERIFICATION	CROSSLINK VERIFICATION
FLHTB0311-18-*	.500 (12.7)	1.00 (.454)
FLHTB0311-16-*	.750 (19.1)	1.50 (.680)
FLHTB0311-14-*	1.00 (25.4)	2.00 (.907)
FLHTC0311-26-*	.375 (9.53)	.125 (.057)
FLHTC0311-24-*	.375 (9.53)	.500 (.227)
FLHTC0311-22-*	.500 (12.7)	.750 (.340)
FLHTC0311-20-*	.500 (12.7)	1.00 (.454)
FLHTC0311-18-*	.500 (12.7)	1.00 (.454)
FLHTC0311-16-*	.750 (19.1)	1.50 (.680)
FLHTC0311-14-*	1.00 (25.4)	2.00 (.907)
FLHTC0311-12-*	1.50 (38.1)	3.00 (1.36)
FLHTD0311-14-*	1.00 (25.4)	2.00 (.907)
FLHTD0311-12-*	1.50 (38.1)	3.00 (1.36)
FLHTD0311-10-*	2.00 (50.8)	3.00 (1.36)
FLHTE0311-8-*	3.00 (76.2)	4.00 (1.81)

WIRE RATINGS AND ADDITIONAL REQUIREMENTS

TEMPERATURE RATING: 200°C

VOLTAGE RATING: 600 volts (rms) at sea level

CROSSLINK VERIFICATION: 300 ± 3°C for 1 hour

FLAME RATING: VW-1

INSULATION ELONGATION AND TENSILE STRENGTH:

Elongation, 100% (minimum)

Tensile Strength, 5470 lbf/in² (minimum)

INSULATION FLAWS:

Spark Test, 6.0 kV (rms)

Impulse Dielectric Test, 8.0 kV (peak)

INSULATION THICKNESS:

AWG 26-16: .0055 inch (.140 mm) (minimum), .006 inch (.152 mm) (minimum average)

AWG 14: .006 inch (.152 mm) (minimum), .0065 inch (.165 mm) (minimum average)

AWG 12: .0065 inch (.165 mm) (minimum), .007 inch (.178 mm) (minimum average)

AWG 10: .007 inch (.178 mm) (minimum), .0075 inch (.191 mm) (minimum average)

AWG 8: .0075 inch (.191 mm) (minimum), .008 inch (.203 mm) (minimum average)

SHRINKAGE: 200°C for 1 hour, 0.125 inch (3.18 mm) (maximum) per end

THERMAL STABILITY: 232°C for 168 hours,

Elongation, 60% (minimum)

Tensile Strength, 5000 lbf/in² (minimum)

VOLTAGE WITHSTAND (Post Environmental): 2500 volts (rms), 60 Hz, 5 minutes

SPOOL LABEL: All spool/reel labels containing conductor strand diameters less than .015 inch (.381 mm) shall include " For Dry Locations Only "

1/ PART NUMBER:

The "+" in the part number in the upper right hand corner of pages 1 and 2 shall be replaced with a letter designator to define conductor stranding (see part numbers in table).

B = 7 Strands C = 19 Strands D = 37 Strands E = Rope Lay

The "*" in the part numbers in Tables I and II shall be replaced by a color code designator.

Example: AWG 18, 19 strands, white: FLHTC0311-18-9

AWG 18, 19 strands, white with a black stripe: FLHTC0311-18-90

1/ See footer section on page 1

Mouser Electronics

Authorized Distributor

Click to View Pricing, Inventory, Delivery & Lifecycle Information:

[TE Connectivity:](#)

[FLHTC0311-22-8](#)