

## CRN Raychem

# Semirigid, flame-retardant, polyolefin heat-shrinkable tubing

Heat-shrinkable CRN tubing is ideally suited for wire strain-relief applications. It provides excellent strain-relief and insulation of weak points such as wire splices and terminations. CRN tubing helps ensure a reliable connection because it transfers the flex stress away from typically sensitive points such as solder and crimp joints.

CRN tubing has a broad range of uses including component protective covering and packaging. The flame-retardant material is fabricated from radiation-crosslinked polyolefin and exhibits excellent mechanical and chemical properties. It meets major military and industrial specifications for an all-purpose, semirigid tubing.

CRN tubing is abrasion-resistant. It's superior chemical properties permit satisfactory performance after exposure to common chemicals and solvents.

Only a few sizes of CRN tubing are required to cover a wide range of substrate diameters.

#### Temperature rating

Full recovery temperature:	135°C
Continuous operating temperature:	-55°C to 135°C

#### Specifications\* **(P**: 91 UL CSA Туре Raychem Military AMS-DTL-23053/6 Cl. 1 CRN Type 1 (colors) RT-360 Type 1 E35586 LR31929 (Black only) AMS-DTL-23053/6 Cl. 2 CRN Type 2 (clear) RT-360 Type 2

#### Dimensions (millimeters/inches)



Inside diameter			Wall thickness		
D (min.)		d (max.)		W	
Expan	ded	Reco	vered after	Recovered a	fter
as sup	plied	heatir	ng	heating**	
1.2	0.046	0.6	0.023	0.51 ± 0.08	0.020 ± 0.003
1.6	0.063	0.8	0.031	0.51 ± 0.08	0.020 ± 0.003
2.4	0.093	1.2	0.046	0.51 ± 0.08	0.020 ± 0.003
3.2	0.125	1.6	0.062	0.51 ± 0.08	0.020 ± 0.003
4.8	0.187	2.4	0.093	0.64 ± 0.08	0.025 ± 0.003
6.3	0.250	3.2	0.125	0.64 ± 0.08	0.025 ± 0.003
9.5	0.375	4.8	0.187	0.76 ± 0.08	0.030 ± 0.003
12.7	0.500	6.4	0.250	0.76 ± 0.08	0.030 ± 0.003
19.0	0.750	9.5	0.375	0.89 ± 0.12	0.035 ± 0.005
	D (min Expan as sup 1.2 1.6 2.4 3.2 4.8 6.3 9.5	D (min.) Expanded as supplied  1.2	D (min.)         d (maximum)           Expanded as supplied         Record           1.2         0.046         0.6           1.6         0.063         0.8           2.4         0.093         1.2           3.2         0.125         1.6           4.8         0.187         2.4           6.3         0.250         3.2           9.5         0.375         4.8           12.7         0.500         6.4	D (min.)     d (max.)       Expanded as supplied     Recovered after       1.2     0.046     0.6     0.023       1.6     0.063     0.8     0.031       2.4     0.093     1.2     0.046       3.2     0.125     1.6     0.062       4.8     0.187     2.4     0.093       6.3     0.250     3.2     0.125       9.5     0.375     4.8     0.187       12.7     0.500     6.4     0.250	D (min.)         d (max.)         W           Expanded as supplied         Recovered after heating         Recovered a heating**           1.2 0.046         0.6 0.023         0.51 ± 0.08           1.6 0.063         0.8 0.031         0.51 ± 0.08           2.4 0.093         1.2 0.046         0.51 ± 0.08           3.2 0.125         1.6 0.062         0.51 ± 0.08           4.8 0.187         2.4 0.093         0.64 ± 0.08           6.3 0.250         3.2 0.125         0.64 ± 0.08           9.5 0.375         4.8 0.187         0.76 ± 0.08           12.7 0.500         6.4 0.250         0.76 ± 0.08

<sup>\*\*</sup>Wall thickness will be less if tubing recovery is restricted during shrinkage.

#### Ordering information

Colors	Standard	Black	
	Nonstandard	Clear (not flame-retardant)	
Size selection	Always order the largest size that will shrink snugly over the component being covered.		
Standard packaging	4-foot lengths		
Ordering description	Specify product name, size, and color; for example, CRN 1/4-0 (0 = Black).		

<sup>\*</sup>When ordering, always specify latest issue.

Doning Oakoa
145 4055
Delated in 15.
Oceanorogy
Plantening
JOOT COOK
0000

	Property	Unit	Requirement Type 1 (Colors)	Requirement Type 2 (Clear)	Method of test
Physical	Dimensions	mm (inches)	See reverse	See reverse	ASTM D 2671
<b>,</b>	Longitudinal change	percent	5 maximum	5 maximum	ASTM D 2671
	Tensile strength	psi (MPa)	2000 <i>(13.8)</i> minimum	2000 <i>(13.8)</i> minimum	ASTM D 2671
	Ultimate elongation	percent	200 minimum	200 minimum	ASTM D 2671
	Secant modulus (expanded)	psi <i>(MPa)</i>	2.5 x 10 <sup>4</sup> (172) minimum	2.5 x 10 <sup>4</sup> (172) minimum	ASTM D 2671
	Specific gravity		1.35 maximum	1.0 maximum	ASTM D 792
	Low-temperature flexibility (4 hours at –55°C/–67°F)		No cracking	No cracking	AMS-DTL 23053 ASTM D 2671 Procedure C
	Heat shock (4 hours at 250°C/482°F)		No dripping, flowing, or cracking	No dripping, flowing, or cracking	AMS-DTL 23053 ASTM D 2671
	Heat resistance (168 hours at 175°C/347°F) Followed by test for:				ASTM D 2671
	Ultimate elongation	percent	150 minimum	150 minimum	ASTM D 2671
Electrical	Dielectric strength	volts/mil (volts/mm)	500 <i>(19,680)</i> minimum	500 <i>(19,680)</i> minimum	ASTM D 2671
	Volume resistivity	ohm-cm	10 <sup>14</sup> minimum	10 <sup>16</sup> minimum	ASTM D 2671
Chemical	Copper mirror corrosion (16 hours at 150°C/302°F)		No removal of copper	No removal of copper	ASTM D 2671 Procedure A
	Copper contact corrosion (168 hours at 150°C/302°F)		No pitting or blackening of copper	No pitting or blackening of copper	ASTM D 2671 Procedure B
	Flammability		Self-extinguishing within 1 minute; 25% of indicator burned or charred; no falling, burning particles.	Not applicable	ASTM D 2671 Procedure B
	Fungus resistance				ISO 846
	Followed by tests for:				Method B
	Tensile strength	psi (MPa)	2000 (13.8) minimum	2000 (13.8) minimum	ASTM D 2671
	Ultimate elongation	percent	200 minimum	200 minimum	ASTM D 2671
	Dielectric strength	volts/mil (volts/mm)	500 <i>(19,680)</i> minimum	500 <i>(19,680)</i> minimum	ASTM D 2671
	Water absorption (24 hours at 23°C/73°F)	percent	0.5 maximum	0.2 maximum	ASTM D 2671
	Fluid resistance (24 hours at 23°C/73°F) in: JP-8 Fuel (MIL-T-5624) Skydrol* 500 Hydraulic fluid (MIL-H-5606) Aviation gasoline (100/130) (MIL-G-5572) Water Followed by tests for:				ASTM D 2671
	Dielectric strength	volts/mil (volts/mm)	400 <i>(15,760)</i> minimum	400 <i>(15,760)</i> minimum 1600 <i>(11.0)</i> minimum	ASTM D 2671

Note: Consult RT-360 for specific details about test procedures.

Raychem is a trademark of Tyco Electronics Corporation.

#### Users should independently evaluate the suitability of the product for their application.

### Tyco Electronics Corporation

300 Constitution Drive Menlo Park, CA 94025-1164 USA

Tel: (800) 926-2425 (US & Canada) Tel: +1 (650) 361-3860 (All other countries) Faraday Road Dorcan, Swindon, SN3 5HH United Kingdom Tel: +44 1793 528171 3816 Noborito, Tama-ku Kawasaki, Kanagawa 214-8533 Japan Tel: +81 44 900 5102 Asia Pacific Headquarters 26 Ang Mo Kio, Industrial Park 2 Singapore 569507 Tel: +65 4866 151

All information, including illustrations, is believed to be reliable. Users, however, should independently evaluate the suitability of each product for their application. Tyco Electronics Corporation makes no warranties as to the accuracy or completeness of the information, and disclaims any liability regarding its use. Tyco Electronics Corporation's only obligations are those in the Standard Terms and Conditions of Sale for these products and in no case will Tyco Electronics Corporation be liable for any incidental, indirect, or consequential damages arising from the sale, resale, use, or misuse of the product. Tyco Electronics Corporation's Specifications are subject to change without notice. In addition, Tyco Electronics Corporation reserves the right to make changes in materials or processing without notification to the Buyer which do not affect compliance with any applicable specification.

<sup>\*</sup>Trademark of the Monsanto Company.

## **Mouser Electronics**

**Authorized Distributor** 

Click to View Pricing, Inventory, Delivery & Lifecycle Information:

TE Connectivity: