

**Electronics** 

## Versafit

# Raychem

Highly flame-retardant, low recovery temperature, heat-shrinkable tubing



Versafit heat-shrinkable tubing is a cost-effective choice for many commercial and military applications. Versafit tubing is made from a specially formulated, crosslinked polyolefin to provide high flame-retardance (VW-1), excellent flexibility, and a low shrink temperature (to reduce installation time).

Versafit tubing performs a variety of functions in commercial and military applications:

- Electrically insulates and protects in-line components, disconnect terminals, and splices.
- Bundles wires for very flexible light-duty harnesses.
- Identifies or color-codes wires, cables, terminals, and components.
   Versafit tubing hot-stamps extremely well.

Compared to noncrosslinked materials, Versafit tubing has a higher temperature rating and exhibits better

thermal stability and resistance to physical abuse.

\A/-!! 4l-!-!...

Unlike other typical flame-retardant tubings, Versafit tubing is free of polybrominated biphenyls (PBBs) and polybrominated biphenyl oxides and ethers (PBBOs/PBBEs). In Europe, these chemicals are classified as environmentally hazardous substances.

# Temperature rating Full recovery temperature: 90°C

Continuous operating temperature: -55°C to 135°C

| Specifications | *       | <b>.71</b>  | <b>⊕</b>     |                 |
|----------------|---------|-------------|--------------|-----------------|
| Туре           | Raychem | UL          | CSA          | Military        |
| Versafit       | RW-3009 | E35586 VW-1 | LR31929 VW-1 | AMS-DTL-23053/5 |
|                |         | 600V, 125°C | 600V, 125°C  | Classes 1 and 3 |

\*When ordering, always specify latest issue.

### Dimensions (millimeters/inches)



|       | Inside diame     | ter           |       |                     | Wall thicknes   | SS             |
|-------|------------------|---------------|-------|---------------------|-----------------|----------------|
|       | D                |               | d (ma | x.)                 | W               |                |
| Size  | Expanded as      | supplied      | Reco  | vered after heating | Recovered a     | fter heating** |
| 3/64  | 1.63 ± 0.2       | 0.064 ± 0.008 | 0.6   | 0.023               | $0.40 \pm 0.08$ | 0.016 ± 0.003  |
| 1/16  | 1.85 ± 0.2       | 0.073 ± 0.007 | 0.8   | 0.031               | 0.43 ± 0.08     | 0.017 ± 0.003  |
| 3/32  | 2.79 ± 0.2       | 0.110 ± 0.007 | 1.2   | 0.046               | 0.51 ± 0.08     | 0.020 ± 0.003  |
| 1/8   | $3.43 \pm 0.2$   | 0.135 ± 0.007 | 1.6   | 0.062               | 0.51 ± 0.08     | 0.020 ± 0.003  |
| 3/16  | 5.21 ± 0.3       | 0.205 ± 0.010 | 2.4   | 0.093               | 0.51 ± 0.08     | 0.020 ± 0.003  |
| 1/4   | 7.11 ± 0.3       | 0.280 ± 0.010 | 3.2   | 0.125               | 0.64 ± 0.08     | 0.025 ± 0.003  |
| 3/8   | 10.16 ± 0.4      | 0.400 ± 0.015 | 4.8   | 0.187               | $0.64 \pm 0.08$ | 0.025 ± 0.003  |
| 1/2   | 13.72 ± 0.4      | 0.540 ± 0.015 | 6.4   | 0.250               | 0.64 ± 0.08     | 0.025 ± 0.003  |
| 5/8   | 16.90 ± 0.4      | 0.665 ± 0.015 | 8.0   | 0.315               | 0.76 ± 0.08     | 0.030 ± 0.003  |
| 3/4   | $20.45 \pm 0.4$  | 0.805 ± 0.015 | 9.5   | 0.375               | 0.76 ± 0.08     | 0.030 ± 0.003  |
| 1     | 25.53 ± 0.4      | 1.055 ± 0.015 | 12.7  | 0.500               | 0.89 ± 0.13     | 0.035 ± 0.005  |
| 1 1/4 | 33.40 ± 0.7      | 1.315 ± 0.025 | 15.9  | 0.625               | 1.02 ± 0.15     | 0.040± 0.006   |
| 1 1/2 | 39.88 ± 0.8      | 1.570 ± 0.030 | 19.1  | 0.750               | 1.02 ± 0.15     | 0.040 ± 0.006  |
| 2     | 52.83 ± 1.0      | 2.080 ± 0.040 | 25.4  | 1.000               | 1.14 ± 0.16     | 0.045 ± 0.007  |
| 3     | 78.49 ± 1.0      | 3.090 ± 0.040 | 38.1  | 1.500               | 1.27 ± 0.20     | 0.050 ± 0.008  |
| 4     | 104.14 ± 1.3     | 4.100 ± 0.050 | 50.8  | 2.000               | 1.40 ± 0.23     | 0.055 ± 0.009  |
| ***** | 111.1 1 16.1 1.1 |               |       |                     |                 |                |

<sup>\*\*</sup>Wall thickness will be less if tubing recovery is restricted during shrinkage.

### Ordering information

| <b>3</b>             |   |  |
|----------------------|---|--|
| Colors               | Standard  | Black, white, red, blue, yellow and green                    |
|                      | Nonstandard   | Brown, orange, violet, and gray                              |
| Size selection       | e selection Always order the largest size that will shrink snugly over the component being covered. |  |
|                      | A variety of specia   | al order sizes are available.                                |
| Standard packaging   | On spools.  |  |
| Ordering description | Specify product na  | ame, size, and color; for example, Versafit 1/4-0 (0=Black). |

# © 1994, 1997, 2002 Tyco Electronics Corporation Printed in USA 1654051 Revised 04/04

### Specification values

|            | Property   | Unit              | Requirement   | Method of test |
|------------|--|-------------------|---|----------------|
| Physical   | Dimensions   | mm (inches)       | See reverse   | ASTM D 2671    |
|            | Longitudinal change                                  |                   |   |                |
|            | ASTM D 2671  | percent           | +1, -5  | ASTM D 2671    |
|            | UL 224   | percent           | +3, -3  | UL224          |
|            | Eccentricity (recovered)                             | percent           | 30 maximum  | ASTM D 2671    |
|            | Tensile strength                                     | psi <i>(MPa)</i>  | 1500 <i>(10.3)</i> minimum  | ASTM D 2671    |
|            | Ultimate elongation                                  | percent           | 200 minimum   | ASTM D 2671    |
|            | Secant modulus (expanded)                            | psi <i>(MPa)</i>  | 2.5 X 10 <sup>4</sup> <i>(172)</i> maximum  | ASTM D 2671    |
|            | Low-temperature flexibility (1 hour at -45°C/-49°F)  |                   | No cracking   | UL 224         |
|            | Heat shock<br>(1 hour at 136°C/277°F)                |                   | No cracking   | UL 224         |
|            | Heat resistance<br>(7 days at 158°C/316°F)           |                   |   | ASTM D 2671    |
|            | Followed by tests for:                               |                   |   |                |
|            | Tensile strength                                     | psi <i>(MPa)</i>  | 70% minimum of unaged specimens   | UL 224         |
|            | Ultimate elongation                                  | percent           | 100 minimum   | UL 224         |
|            | Flexibility  |                   | No cracking   | UL 224         |
|            | Dielectric withstand at 2500 V                       | seconds           | 60 minimum  | UL 224         |
|            | Dielectric breakdown                                 | volts             | 50% minimum of unaged specimens   | ASTM D 2671    |
|            | Dielectric strength                                  | volts/mil (kV/mm) | 500 <i>(19.7)</i> minimum   | ASTM D 2671    |
|            | Restricted shrinkage                                 |                   | Pass  | UL 224         |
| Electrical | Dielectric strength                                  | volts/mil (kV/mm) | 500 <i>(19.7)</i> minimum   | ASTM D 2671    |
|            | Dielectric withstand at 2500 V                       | seconds           | 60 minimum  | UL 224         |
|            | Volume resistivity                                   | ohm-cm            | 10 <sup>14</sup> minimum  | ASTM D 2671    |
| Chemical   | Corrosive effect<br>(7 days at 158°C/316°F)          |                   | No corrosion  | ASTM D 2671    |
|            | Copper stability (7 days at 158°C/316°F)             |                   | No brittleness, glazing, cracking,<br>or severe discoloration of tubing.<br>No pitting or blackening of copper. | ASTM D 2671    |
|            | Followed by test for:                                |                   |   |                |
|            | Ultimate elongation                                  | percent           | 100 minimum   | ASTM D 2671    |
|            | Flammability   |                   | Pass  | UL 224, VW-1   |
|            | Water absorption (recovered) (24 hours at 23°C/73°F) | percent           | 0.5 maximum   | ASTM D 2671    |
|            | Fungus resistance                                    |                   |   | ISO 846        |
|            | Followed by tests for:                               |                   |   | Method B       |
|            | Tensile strength                                     | psi (MPa)         | 1500 <i>(10.3)</i> minimum  | ASTM D 2671    |
|            | Ultimate elongation                                  | percent           | 200 minimum   | ASTM D 2671    |
|            | Dielectric strength                                  | volts/mil (kV/mm) | 500 <i>(19.7)</i> minimum   | ASTM D 2671    |

Note: Consult RW-3009 for specific details about test procedures.

Versafit and Raychem are trademarks of Tyco Electronics Corporation.

### Users should independently evaluate the suitability of the product for their application.

Tyco Electronics Corporation 300 Constitution Drive Menlo Park, CA 94025-1164

Tel: (800) 926-2425 (US & Canada) Tel: +1 (650) 361-3860 (All other countries) Faraday Road Dorcan, Swindon, SN3 5HH United Kingdom Tel: +44 1793 528171 3816 Noborito, Tama-ku Kawasaki, Kanagawa 214-8533 Japan Tel: +81 44 900 5102 Asia Pacific Headquarters 26 Ang Mo Kio, Industrial Park 2 Singapore 569507 Tel: +65 4866 151

All information, including illustrations, is believed to be reliable. Users, however, should independently evaluate the suitability of each product for their application. Tyco Electronics Corporation makes no warranties as to the accuracy or completeness of the information, and disclaims any liability regarding its use. Tyco Electronics Corporation's only obligations are those in the Standard Terms and Conditions of Sale for these products and in no case will Tyco Electronics Corporation be liable for any incidental, indirect, or consequential damages arising from the sale, resale, use, or misuse of the product. Tyco Electronics Corporation's Specifications are subject to change without notice. In addition, Tyco Electronics Corporation reserves the right to make changes in materials or processing without notification to the Buyer which do not affect compliance with any applicable specification.

# **Mouser Electronics**

**Authorized Distributor** 

Click to View Pricing, Inventory, Delivery & Lifecycle Information:

TE Connectivity: VERSAFIT-1-0-SP-SM