



BERGQUIST® LIQUI FORM TLF 10000

January 2024

PRODUCT DESCRIPTION

BERGQUIST® LIQUI FORM TLF 10000 is a thermally conductive, one-part liquid formable gel material.

Technology	Silicone
Appearance	Red gel
Application	Thermal management, Gel (1K)
Application method	Dispensing
Operating temperature range	-60°C to 200°C
Product benefits	<ul style="list-style-type: none">• Excellent thermal cycling performance• High gap stability• Minimal resin bleed• Low thermal impedance• Excellent dispense properties• Low stress• Bondline thickness control

Features and benefits

- Thermal conductivity: 10 W/m-K
- Dispensable pre-cured gel
- Stable viscosity in storage and in applications
- Excellent chemical stability and mechanical stability

BERGQUIST® LIQUI FORM TLF 10000 thermally conductive gel interface material is designed to meet the demanding requirements in certain telecom and other demanding applications. Its unique formulation assures a balanced mix of high thermal conductivity, excellent dispensing efficiency, and high thermal stability.

This material is specially designed to provide effective electronic component cooling capability for 5G base station and remote antenna assembly where a highly reliable vertical gap stability is required. It is most effective for gaps as narrow as $\leq 2.5\text{mm}$. BERGQUIST® LIQUI FORM TLF 10000 is pre-cured, requiring no mixing or refrigeration.

Typical applications

- RRU/AAU/BBU in wireless in telecom wireless infrastructure
- Filling various gaps between heat-generating devices to heat sink
- Devices requiring low assembly pressure
- High value assemblies where rework is required

TYPICAL PROPERTIES

Density, ASTM D792, g/cc	3.1
Shelf life @ 25°C, days	270

Physical Properties

Viscosity, Pa-s

Low shear rate 1.0 s^{-1} 1,492

High shear rate 100 s^{-1} 349

Dispense rate, EFD 30cc syringe, 90psi⁽¹⁾, grams/minute⁽¹⁾ 22

Outgassing, % % total mass loss, STME E595, % 0.5

Flammability rating, UL 94 UL 94 V-0

Electrical properties

Volume resistivity, 500 V DC, ASTM D257, ohm-meter $9.0 \times 10^{+11}$

Dielectric strength, ASTM D149, V/mm 7,084

Dielectric constant, @ 1 MHz 8.4

Thermal properties

Thermal conductivity, ASTM D5470, W/mK 10

(1) 30cc syringe, 90 psi (621 kPa), 0.100" orifice no attachment

GENERAL INFORMATION

For safe handling information on this product, consult the Safety Data Sheet (SDS).

CONFIGURATIONS AVAILABLE

BERGQUIST® LIQUI FORM TLF 10000 is supplied in:

Cartridges	150cc
Pail	1 gallon

Storage:

Store product in an unopened container in a dry location. Storage information may be indicated on the product container labeling.

Optimal Storage: 25 °C (± 3), 50% RH (± 10) for a 270 days shelf life in sealed containers with moisture barrier packaging.

Not for product specifications

The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on the specifications of this product.

Approval and certificate

Please contact a Henkel representative for related approval or certificate of this product.



Data ranges

The data contained herein may be reported as a typical value. Values are based on actual test data and are verified on a periodic basis.

Temperature/Humidity Ranges: 23°C / 50% RH = 23±2°C / 50±5% RH

Conversions

(°C x 1.8) + 32 = °F
 kV/mm x 25.4 = V/mil
 mm / 25.4 = inches
 µm / 25.4 = mil
 N x 0.225 = lb
 N/mm x 5.71 = lb/in
 N/mm² x 145 = psi
 MPa x 145 = psi
 N·m x 8.851 = lb·in
 N·m x 0.738 = lb·ft
 N·mm x 0.142 = oz·in
 mPa·s = cP

Disclaimer

The information provided in this Technical data sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical data sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Trademark usage Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 2

Mouser Electronics

Authorized Distributor

Click to View Pricing, Inventory, Delivery & Lifecycle Information:

[Bergquist Company:](#)

[TLF10000L0.8GALLON](#) [TLF10000L150CC](#) [TLF10000L300CC](#)