

LOCTITE ECCOBOND FP4502

December 2016

PRODUCT DESCRIPTION

LOCTITE ECCOBOND FP4502 provides the following product characteristics:

Technology	Epoxy
Appearance	Gray
Product Benefits	• One component • Low CTE • Improved toughness • Forms a rigid, low stress seal • Dissipates stress on solder joints • Extends thermal cycling performance • No-clean flux compatible • Improved crack and fracture resistance
Filler content, ignition (ITM3A), %	65
Cure	Heat cure
Application	Underfill
Typical Applications	Encapsulant for flip chip devices

LOCTITE ECCOBOND FP4502 is a high purity, liquid epoxy designed as an underfill for flip chip devices.

TYPICAL PROPERTIES OF UNCURED MATERIAL

Viscosity, Brookfield CP52	
Speed 20 rpm, @ 25°C	35,000
, ASTM D2393, mPa·s (cP):	
Speed 20 rpm, @ 25°C	35,000
Flow Rate, @ 500mil flow, 2mil gap @ 100°C, seconds	30
Specific Gravity	1.68
Pot life (Time required to double viscosity), @ 25°C, hours	24
Gel Time @ 121°C, minutes	21
Shelf Life @ -40°C (from date of manufacture), months	9
Flash Point - See SDS	

TYPICAL CURING PERFORMANCE Recommended Cure Schedule

30 minutes @ 165°C

Alternate Cure Schedule

2 minutes, hours @ 150°C

The above cure profile is a guideline recommendation. Cure conditions (time and temperature) may vary based on customers' experience and their application requirements, as well as customer curing equipment, oven loading and actual oven temperatures.

TYPICAL PROPERTIES OF CURED MATERIAL

Physical Properties :

Glass Transition Temperature (Tg) by TMA, °C	115
Coefficient of Linear Thermal Expansion :	
Alpha 1, ppm/°C	22
Alpha 2, ppm/°C	84
Extractable Ionic Content, :	
Chloride (Cl-)	20
Sodium (Na+)	10

TYPICAL PERFORMANCE OF CURED MATERIAL

Miscellaneous:

Flexural Modulus, ASTM D790	N/mm ² 9,500
	(psi) (1,377,859)

GENERAL INFORMATION

For safe handling information on this product, consult the Safety Data Sheet, (SDS).

Not for product specifications

The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on specifications for this product.

THAWING:

1. Frozen packages must be completely thawed before use.
2. Store tip down and warm at room temperature until no longer cool to the touch (normally 60 to 90 minutes).
3. DO NOT thaw in an oven.

Directions for use

1. To encapsulate flip chips by capillary action, the chip and substrate must be thoroughly cleaned.
2. A bead of LOCTITE ECCOBOND FP4502 is then applied to one or two sides (L-shape) of the chip perimeter.
3. For best results, the material should be dispensed onto a substrate that has been preheated to approximately 100 to 120°C and held at that temperature until flow stops.
4. After the material has completely flowed under the chip, the device must be promptly cured according to suggested cure to achieve full properties.
5. Devices with wet encapsulant should not be exposed to humidity in the air.
6. If the material cannot be initially gelled to a hard finish within 1 hour after dispensing, storage in desiccator cabinet is suggested until full curing is possible.

STORAGE:

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

Optimal Storage : -40 °C

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

Conversions

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$
 $\text{kV/mm} \times 25.4 = \text{V/mil}$
 $\text{mm} / 25.4 = \text{inches}$
 $\text{N} \times 0.225 = \text{lb/F}$
 $\text{N/mm} \times 5.71 = \text{lb/in}$
 $\text{psi} \times 145 = \text{N/mm}^2$
 $\text{MPa} = \text{N/mm}^2$
 $\text{N} \cdot \text{m} \times 8.851 = \text{lb} \cdot \text{in}$
 $\text{N} \cdot \text{m} \times 0.738 = \text{lb} \cdot \text{ft}$
 $\text{N} \cdot \text{mm} \times 0.142 = \text{oz} \cdot \text{in}$
 $\text{mPa} \cdot \text{s} = \text{cP}$

Disclaimer**Note:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or

compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage: [Except as otherwise noted] All trademarks in this document are trademarks and/or registered trademarks of Henkel and its affiliates in the U.S. and elsewhere.

Reference 2

Mouser Electronics

Authorized Distributor

Click to View Pricing, Inventory, Delivery & Lifecycle Information:

[Loctite:](#)

[528062](#)