

LOCTITE EDAG 451SS E&C

January 2017

PRODUCT DESCRIPTION

LOCTITE EDAG 451SS E&C provides the following product characteristics:

Technology	Acrylate
Appearance	Green
Product Benefits	 Screen printable Suitable for high speed flexographic printing UV curable Dielectric Fast cure Smooth film surface Compatible with other LOCTITE silver and carbon inks
Operating Temperature- Maximum	177°C
Cure	Ultraviolet (UV) light
Application	Dielectric ink
Typical Assembly Applications	 Insulating coatings Insulating crossovers Protective tail coatings for membrane switches
Key Substrates	Treated polyester film

LOCTITE EDAG 451SS E&C dielectric coating is designed for use as an insulative and/or protective coating for printed circuitry.

TYPICAL PROPERTIES OF UNCURED MATERIAL

Solids Content by Weight, %	100
Viscosity, Brookfield - RVT, mPa·s (cP):	
Spindle 5, speed 20 rpm	9,000
Density, kg/l	1.08
Shelf Life (from date of manufacture), days	730
Flash Point, °C	102

TYPICAL CURING PERFORMANCE

Recommended UV Cure Condition

Light Source and Condition

H Type UV curing bulb
Light Intensity, watts 200 to 300
Wavelength, nanometers 250 to 400
Cure @ 25µm, EIT Radiometer, Joule/cm² 0.3 to 0.7

At thicknesses greater than 25µm, more exposure (lower belt speeds and/or higher light intensities) may be needed.

The above cure profile is a guideline recommendation. Cure conditions (time and temperature) may vary based on customers' experience and their application requirements, as well as customer curing equipment, oven loading and actual oven temperatures.

TYPICAL PROPERTIES OF CURED MATERIAL

Physical Properties

Coverage @ $25\mu m$ dry coating thickness, m^2 /kg $\qquad 36.45$ wet product

Electrical Properties

Dielectric Strength @ 25µm thickness, volts AC 1,500 Dielectric Constant 5.31

GENERAL INFORMATION

For safe handling information on this product, consult the Safety Data Sheet, (SDS).

DIRECTIONS FOR USE

Mixing/Dilution

- LOCTITE EDAG 451SS E&C is supplied ready for use and does not require dilution.
- · Gently stir prior to use.

Application Details

Screen Mesh, Polyester 160 to 300

Emulsion Diazo sensitized direct photo film

Film thickness, µm:

 160 mesh screen
 28

 200 mesh screen
 18 to 20

 300 mesh screen
 10

Used as a Crossover

- Recommended thickness when used as a crossover is 20 to 25
 µm. Use either one coat with 160 mesh or two coats with 300
 mesh
- When using LOCTITE EDAG 451SS E&C as a crossover, be sure to cure the links that are printed over it within five minutes. Do not allow the inks printed over LOCTITE EDAG 451SS E&C to air dry for extended time periods.
- All LOCTITE inks adhere well to LOCTITE EDAG 451SS E&C and is designed to pass the tape pull test. This allows the material to be used as an insulator for crossovers. Maximum adhesion is gained by using LOCTITE EDAG 479SSC (silver) or LOCTITE EDAG 423SS (graphite).
- When using two coats, cure first coat with minimum exposure necessary to gain adhesion. Cure second coat with slightly more exposure.

CLEAN-UP

To clean screen and equipment, use Methylethylketone (MEK), MIBK, Acetone or similar solvents



STORAGE:

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

Optimal Storage: 5 to 25 °C

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

Not for product specifications

The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on specifications for this product.

Conversions

 $(^{\circ}C \times 1.8) + 32 = ^{\circ}F$ kV/mm x 25.4 = V/mil mm / 25.4 = inches N x 0.225 = lb N/mm x 5.71 = lb/in psi x 145 = N/mm² MPa = N/mm² MPa = N/mm² N·m x 8.851 = lb·in N·m x 0.738 = lb·ft N·mm x 0.142 = oz·in mPa·s = cP

Disclaimer Note:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada, Inc.the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits. The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference N/A

Mouser Electronics

Authorized Distributor

Click to View Pricing, Inventory, Delivery & Lifecycle Information:

Loctite:

1223950 1263445