

LOCTITE EDAG PR 406 E&C

August 2021

PRODUCT DESCRIPTION

LOCTITE EDAG PR 406 E&C provides the following product characteristics:

Technology	Thermoset Resin
Appearance	Black
Filler Type	Carbon
Operating Temperature-Maximum, continuous	150°C
Cure	Heat cure
Product Benefits	- One component - Low electrical resistance - Alternative to gold plating for copper contact protection - Resistant to wave/hot air levelling soldering - Optimum viscosity - Resistant to common industry solvents - Compatible with most commonly used fluxes
Application	Conductive Ink
Typical Assembly Applications	Copper contact protection, Conductive pads and jumpers and Printed resistors
Surfaces	Copper, Phenolic paper (FR2), Epoxy paper (FR3) and Glass epoxy (FR4)

LOCTITE EDAG PR 406 E&C carbon polymer thick film ink is suitable for application on most rigid substrates.

TYPICAL PROPERTIES OF UNCURED MATERIAL

Solids Content by Weight, %	58
Viscosity Brookfield - RVT, 20 rpm @ 20°C, mPa·s (cP)	30,000
Density, kg/m³	1,240
Theoretical coverage, m²/kg:	
@ 10 coating thickness	38
Shelf Life @ 5 to 30°C (from date of manufacture), year	1
Flash Point °C	54

TYPICAL SCREEN PRINTING PROCESS

Emulsion Thickness	
Emulsion Thickness, µm	30
Recommended Screen Type	
Monofilament polyester screen, threads/cm	75.5
Stainless steel screen, threads/cm	93.5
Recommended Squeegee	
Polyurethane, durometer	72.5
Printing Equipment Type	
Manual	
Semi-automatic	

Applied Dry Coating Thickness

Applied Dry Coating Thickness, µm	13.5
-----------------------------------	------

TYPICAL CURING PERFORMANCE Cure Schedule

30 minutes @ 150°C or higher if the substrate will allow

LOCTITE EDAG PR 406 E&C can be cured in conventional air circulated ovens.

Higher temperatures result in better characteristics.

This product can also be cured using infrared.

The above cure profile is a guideline recommendation. These cure conditions (time and temperature) may vary based on customers' experience and specific application requirements, as well as customer curing equipment, oven loading and actual oven temperatures.

TYPICAL PROPERTIES OF CURED MATERIAL

Physical Properties

Adhesion, grade	5B
-----------------	----

Electrical Properties

Sheet Resistivity, Ω/sq/25µm	<10
------------------------------	-----

GENERAL INFORMATION

For safe handling information on this product, consult the Safety Data Sheet, (SDS).

DIRECTIONS FOR USE

- LOCTITE EDAG PR 406 E&C is supplied ready for use and does not require dilution.
- Should thinning become necessary, dilute with 2 to 6% Electrodag Diluent 2 (diethylene glycol monon-butyl ether).
- LOCTITE EDAG PR 406 E&C should be thoroughly stirred prior to use. Avoid rapid stirring as this causes air entrapment.

CLEAN-UP

To clean screen and equipment, use Methyl ethyl ketone (MEK), MIBK, Acetone or similar solvents

Storage

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

Store in a cool, well ventilated area.

Optimal Storage : 5 to 30 °C

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Henkel Representative.

Not for product specifications

The technical data contained herein are intended as reference only. Please contact your local Henkel representative for assistance and recommendations on the specifications of this product.

Conversions

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$

$\text{kV/mm} \times 25.4 = \text{V/mil}$

$\text{mm} / 25.4 = \text{inches}$

$\text{N} \times 0.225 = \text{lb/F}$

$\text{N/mm} \times 5.71 = \text{lb/in}$

$\text{psi} \times 145 = \text{N/mm}^2$

$\text{MPa} = \text{N/mm}^2$

$\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$

$\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$

$\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$

$\text{mPa}\cdot\text{s} = \text{cP}$

Disclaimer

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 0.2

Mouser Electronics

Authorized Distributor

Click to View Pricing, Inventory, Delivery & Lifecycle Information:

[Loctite:](#)

[1239104](#)