

LOCTITE ABLESTIK ECF 564AHF

November 2019

PRODUCT DESCRIPTION

LOCTITE ABLESTIK ECF 564AHF provides the following product characteristics:

Technology	Epoxy Film
Appearance	Silver
Cure	Heat cure
Product Benefits	<ul style="list-style-type: none"> Electrically conductive Low outgassing Isotropic electrical conductivity
Application	Assembly
Filler Type	Silver
Carrier Type	Glass fabric
pH	6.0
Typical Package Application	Hybrid packages

LOCTITE ABLESTIK ECF 564AHF adhesive film is designed for use in hybrid packages where outgassing and ionic contamination must be kept to a minimum. This material is the highest flow version of the ABLESTIK ECF 564A series.

MIL-STD-883C

LOCTITE ABLESTIK ECF 564AHF meets the requirements of MIL-STD-883C, Method 5011.

TYPICAL PROPERTIES OF UNCURED MATERIAL

Work Life @ 25°C, days	3
Shelf Life @ -40°C (from date of manufacture), days	365

TYPICAL CURING PERFORMANCE Cure Schedule

2 hours @ 150°C

The above cure profiles are guideline recommendations. Cure conditions (time and temperature) may vary based on customers' experience and their application requirements, as well as customer curing equipment, oven loading and actual oven temperatures.

TYPICAL PROPERTIES OF CURED MATERIAL

Physical Properties :

Water Extract Conductivity, $\mu\text{mhos/cm}$	5
Glass Transition Temperature (T_g) by TMA, °C	122
Coefficient of Thermal Expansion, TMA:	
Below T_g , in/in/°C	80×10^{-6}
Above T_g , in/in/°C	33×10^{-5}
Extractable Ionic Content, :	
Chloride (Cl ⁻)	5
Sodium (Na ⁺)	5
Potassium (K ⁺)	N/D
Weight Loss @ 300°C, TGA, %	0.15

Thermal Conductivity @ 121°C, BTU ft⁻¹ hr⁻¹ °F⁻¹ 3.0

Electrical Properties:

Volume Resistivity, ohms-cm 0.0004
Electrical Resistance Measured through gold joints, 0.0005 ohm/0.5 sq. in.

TYPICAL PERFORMANCE OF CURED MATERIAL

Lap Shear Strength :

Al to Al	N/mm ² 17 (psi) (2,500)
Au to Au	N/mm ² 20 (psi) (2,900)

Die Shear Strength:

@ 25°C	N/mm ² 36 (psi) (5,300)
--------	---------------------------------------

TYPICAL ENVIRONMENTAL RESISTANCE

Outgassing Properties

Outgassing , NASA Outgassing:	
TML, %	0.3
CVCM, %	<0.01
WVR, %	0.25

GENERAL INFORMATION

For safe handling information on this product, consult the Safety Data Sheet, (SDS).

THAWING:

1. Allow container to reach room temperature before use.
2. DO NOT open the container before contents reach 25°C temperature. Any moisture that collects on the thawed container should be removed prior to opening the container.
3. DO NOT re-freeze. Once thawed, the adhesive should not be re-frozen.

DIRECTIONS FOR USE

1. Clean all surfaces to be bonded.
2. Precut adhesive to the same size as, or slightly smaller than, the substrate.
3. Place in position in the package (header).
4. Place in a preheated oven at 150°C for 4 minutes to allow removal of absorbed moisture and traces of retained solvent.
5. If no clamping pressure is used during the curing, mount the substrate either while hot or after cooling to ambient.

6. Place on a heating block at 150°C.
7. Press or scrub the substrate until an acceptable fillet is obtained.
8. Place in pre-heated oven and cure at the recommended cure schedule.
9. If clamping pressure is used during cure, mount the substrate either while hot or after cooling to ambient. Apply spring loaded clamp to provide continuous pressure of 10psi during the cure cycle. Place in pre-heated oven and cure at the recommended cure schedule.

AVAILABILITY

1. LOCTITE ABLESTIK ECF 564AHF adhesive is available in sheet stock or die cut preforms.
2. This material is only available with 5011 certification.

Not for product specifications

The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on specifications for this product.

STORAGE:

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

LOCTITE ABLESTIK ECF 564AHF adhesive may be stored up to 1 year at -40°C.

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

Conversions

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$
 $\text{kV/mm} \times 25.4 = \text{V/mil}$
 $\text{mm} / 25.4 = \text{inches}$
 $\text{N} \times 0.225 = \text{lb/F}$
 $\text{N/mm} \times 5.71 = \text{lb/in}$
 $\text{psi} \times 145 = \text{N/mm}^2$
 $\text{MPa} = \text{N/mm}^2$
 $\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$
 $\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$
 $\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$
 $\text{mPa}\cdot\text{s} = \text{cP}$

Disclaimer

Note:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage: [Except as otherwise noted] All trademarks in this document are trademarks and/or registered trademarks of Henkel and its affiliates in the U.S. and elsewhere.

Reference 0.2

Mouser Electronics

Authorized Distributor

Click to View Pricing, Inventory, Delivery & Lifecycle Information:

[Loctite:](#)

[1198985](#) [1200264](#) [1202968](#) [1202971](#) [1202995](#) [1286061](#)