

LOCTITE ECCOBOND 3781UV

September 2018

PRODUCT DESCRIPTION

LOCTITE ECCOBOND 3781UV provides the following product characteristics:

Technology	Acrylate
Appearance	Translucent amber liquid
Product Benefits	<ul style="list-style-type: none"> One component, requires no mixing
Cure	Ultraviolet (UV) light
Application	Device assembly, Structural bonding

LOCTITE ECCOBOND 3781UV is a single component, UV light curable sealant for LCD end-sealing applications.

TYPICAL PROPERTIES OF UNCURED MATERIAL

Brookfield Viscosity, RVT, mPa·s (cP):

Spindle 5, Speed 20 rpm @ 25°C 12,000

Flash Point - See SDS

TYPICAL CURING PERFORMANCE

Recommended UV Cure Condition

Light Source and Condition:

High pressure mercury UV lamp:

Light Intensity, mW/cm² 100

Tack Free Time

Tack Free Time, seconds 2

Depth of Cure

Depth of Cure, cured 20 seconds @ 100 mW/cm², mm 3.7

UV intensities where quoted are measured at 365 nm using an USHIO UIT-101 UV meter

LOCTITE ECCOBOND 3781UV can be cured by irradiation with ultraviolet of sufficient intensity. To obtain full cure on surfaces exposed to air, the intensity of UV radiation at 220 to 260 nm will accelerate the tack free cure of surface. The cure rate and ultimate depth of cure will depend on light intensity, the spectral distribution of the light source, the exposure time and the light transmittance of the substrates.

The above cure profile is a guideline recommendation. Cure rate and ultimate depth of cure depend on light intensity, spectral distribution of light source, exposure time and the light transmittance of the substrate.

TYPICAL PROPERTIES OF CURED MATERIAL

Sample cured 120 seconds @ 100 mW/cm², using a high pressure mercury lamp

Physical Properties

Hardness, Shore D	82
Glass Transition Temperature (T _g) by DMTA, °C	68
Coefficient of Thermal Expansion :	
@ 25°C, °C	140×10 ⁻⁶
@ 80 to 120°C, °C	180×10 ⁻⁶
Water Absorption, 24 hours @ 25°C, %	1.7

Electrical Properties

Dielectric Constant / Loss:	
@ 10 kHz	3.9/0.03
@ 1 MHz	3.5/0.04
@ 10 MHz	3.3/0.05
Volume Resistivity, ohm-cm	1.3×10 ¹⁶
Surface Resistivity, ohms	4.0×10 ¹⁵
Dielectric Strength, kV/mm	27

TYPICAL PERFORMANCE OF CURED MATERIAL

Samples cured using a high pressure mercury light source

Shear Strength :

Tensile Shear Strength, cured 40 seconds @ 100 mW/cm², 365 nm UV wavelength:

Grit blasted mild steel pin to glass N/mm² 11
(psi) (16,099)

Bonded Torque Strength, cured 300 seconds @ 6 mW/cm², 365 nm UV wavelength:

Grit blasted aluminum hex button N/mm² 150
to glass (psi) (21,755)

GENERAL INFORMATION

For safe handling information on this product, consult the Safety Data Sheet, (SDS).

Not for product specifications

The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on specifications for this product.

STORAGE:

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

Optimal Storage : 10 to 27 °C

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

Conversions

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$
 $\text{kV/mm} \times 25.4 = \text{V/mil}$
 $\text{mm} / 25.4 = \text{inches}$
 $\text{N} \times 0.225 = \text{lb}$
 $\text{N/mm} \times 5.71 = \text{lb/in}$
 $\text{psi} \times 145 = \text{N/mm}^2$
 $\text{MPa} = \text{N/mm}^2$
 $\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$
 $\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$
 $\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$
 $\text{mPa}\cdot\text{s} = \text{cP}$

Disclaimer**Note:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage: [Except as otherwise noted] All trademarks in this document are trademarks and/or registered trademarks of Henkel and its affiliates in the U.S. and elsewhere.

Reference 1

Mouser Electronics

Authorized Distributor

Click to View Pricing, Inventory, Delivery & Lifecycle Information:

[Loctite:](#)

[330048](#)