

# LOCTITE ECCOBOND 50500 D

May 2015

## PRODUCT DESCRIPTION

LOCTITE ECCOBOND 50500 D provides the following product characteristics:

<b>Technology</b>	Epoxy
<b>Appearance</b>	Black
<b>Components</b>	One-component
<b>Product Benefits</b>	<ul style="list-style-type: none"> <li>• Low modulus of elasticity</li> <li>• Low stress</li> <li>• High purity</li> <li>• Non-sag</li> <li>• Low warpage</li> </ul>
<b>Filler Weight, %</b>	73 to 77
<b>Percent Solids by Weight</b>	100
<b>Cure</b>	Heat Cure
<b>Application</b>	Encapsulant
<b>Operating Temperature</b>	-65 to 150 °C
<b>Typical Assembly Applications</b>	Glob top applications, Protecting wire bonded bare IC's and BGA

LOCTITE ECCOBOND 50500 D is designed to be used as a dam encapsulant in combination with a "fill" encapsulant in glob top applications for protecting wire bonded bare IC's. This combination of materials is also suited for the protection of multiple chips and for encapsulating components where a well defined glob height and flat surface are required.

## TYPICAL PROPERTIES OF UNCURED MATERIAL

Viscosity @ 25 °C, mPa·s (cP):

@ 1.5 s <sup>-1</sup>	110,000 to 140,000
@ 15 s <sup>-1</sup>	20,000 to 40,000

Specific Gravity 1.75

Shelf Life:

@ -40 to 0°C, months	4
@ 25°C, days	3

Flash Point - See SDS

## TYPICAL CURING PERFORMANCE

### Recommended Cure Schedule

2 hours @ 150°C

### Low Stress Cure Schedule

1 hour @ 100°C + 1 hour @ 150°C

**Note:** For devices which are affected by higher levels of stress, a low temperature pre-cure at 100°C is recommended.

The above cure profiles are guideline recommendations. Cure conditions (time and temperature) may vary based on customers' experience and their application requirements, as well as customer curing equipment, oven loading and actual oven temperatures.

## TYPICAL PROPERTIES OF CURED MATERIAL

### Physical Properties

Coefficient of Thermal Expansion :

Below Tg, ppm/°C 80

Glass Transition Temperature, °C

70

Thermal Conductivity, W/(m·K)

0.6 to 0.65

Tensile Modulus, DMTA :

@ 25 °C	N/mm <sup>2</sup>	3,500 to 5,500
	(psi)	(507,500 to 797,500)
@ 50 °C	N/mm <sup>2</sup>	3,000 to 4,500
	(psi)	(435,000 to 652,500)
@ 70 °C	N/mm <sup>2</sup>	900 to 1,200
	(psi)	(130,500 to 174,000)
@ 150 °C	N/mm <sup>2</sup>	100 to 200
	(psi)	(14,500 to 29,000)

Extractable Ionic Content, ppm:

Chloride (Cl <sup>-</sup> )	20
Sodium (Na <sup>+</sup> )	10
Potassium (K <sup>+</sup> )	10
Hardness, Shore D	80

Water Absorption, %:

7days at room temperature by weight	0.07
24 hour boil test by weight	0.5

### Electrical Properties

Dielectric Constant / Dissipation Factor @ 25°C:

1kHz 3.7 / 0.01

## TYPICAL PERFORMANCE OF CURED MATERIAL

Tensile Lap Shear Strength, MPa 9

## GENERAL INFORMATION

For safe handling information on this product, consult the Safety Data Sheet, (SDS).

### THAWING:

1. Allow material to reach room temperature before use.

### DIRECTIONS FOR USE

1. The surfaces on which the adhesive has to be applied should be clean, dry and free from all dust.
2. The outline of the glob, the "dam" is first dispensed with LOCTITE ECCOBOND 50500 D.
3. The dam is then filled in with a fill encapsulant.
4. After dispensing, both materials can be co-cured.

**STORAGE:**

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

**Optimal Storage : -40 °C**

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

**Not for product specifications**

The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on specifications for this product.

**Conversions**

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$

$\text{kV/mm} \times 25.4 = \text{V/mil}$

$\text{mm} / 25.4 = \text{inches}$

$\text{N} \times 0.225 = \text{lb}$

$\text{N/mm} \times 5.71 = \text{lb/in}$

$\text{psi} \times 145 = \text{N/mm}^2$

$\text{MPa} = \text{N/mm}^2$

$\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$

$\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$

$\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$

$\text{mPa}\cdot\text{s} = \text{cP}$

**Disclaimer****Note:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:**

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

**In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada, Inc. the following disclaimer is applicable:**

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

**Trademark usage**

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 1

# Mouser Electronics

Authorized Distributor

Click to View Pricing, Inventory, Delivery & Lifecycle Information:

[Loctite:](#)

[1189613](#)