

# **LOCTITE EDAG 461SS E&C**

April 2020

#### PRODUCT DESCRIPTION

LOCTITE EDAG 461SS E&C provides the following product characteristics:

Technology	Polyester Resin		
Appearance	Silver		
Filler Type	Silver		
Solvent	Butyl cellosolve acetate		
Cure	Heat cure		
Operating Temperature- Maximum	149°C		
Product Benefits	<ul> <li>Conductive</li> <li>Screen printable</li> <li>Extremely flexible</li> <li>Low electrical resistance</li> <li>Dries at low temperatures</li> <li>Good adhesion</li> </ul>		
Application	Conductive Ink		
Typical Assembly Applications	ITO coated film, Membrane switches, Digitizers, Flexible circuits and Electroluminescent lamps		
Key Substrates	Polyester and ITO film		

LOCTITE EDAG 461SS E&C conductive ink is designed for display applications on ITO film. It consists of very finely divided silver particles dispersed in a thermoplastic resin.

### TYPICAL PROPERTIES OF UNCURED MATERIAL

Solids Content by Weight, %	75
Viscosity, Brookfield - RVT, mPa·s (cP):	
Spindle 6, speed 20 rpm	17,000
Density, kg/l	2.34
Shelf Life @ 8 to 28°C (from date of manufacture), days	365
Flash Point ASTM D93-71, Pensky-Martens Closed Cup Flash Tester°C	74

## **TYPICAL SCREEN PRINTING PROCESS**

Recommended Thickness	
Dry Film , μm	10.0 to 12.5
Emulsion Thickness	
Solvent resistant emulsion , µm	20 to 37.5
Recommended Screen Type	
Monofilament polyester screen, mesh	157 to 280
Stainless steel screen , mesh	165 to 250

Recommended	Squeege	e	
Polyurethane or	other solv	ent res	sistant material

Polyester screen , durometer	60
Stainless steel screen , durometer	70

#### **TYPICAL CURING PERFORMANCE Cure Schedule**

30 minutes @ 71°C or 15 minutes @ 93°C or 5 minutes @ 121°C

#### **Percent Volatiles**

VOC, g/l 576

Depending on the amount of air flow, curing may be faster.

The above cure profile is a guideline recommendation. Cure conditions (time and temperature) may vary based on customers' experience and their application requirements, as well as customer curing equipment, oven loading and actual oven temperatures.

### **TYPICAL PROPERTIES OF CURED MATERIAL**

# **Physical Properties:**

3B
6.1
<0.02

### **GENERAL INFORMATION**

For safe handling information on this product, consult the Safety Data Sheet, (SDS).

# **DIRECTIONS FOR USE**

- 1. Do not expose wet ink to direct sunlight.
- 2. Do not freeze.
- 3. Keep product container tightly closed when not in use.
- 4. LOCTITE EDAG 461SS E&C should be thoroughly stirred prior to use. Avoid rapid stirring as this causes air entrapment...
- LOCTITE EDAG 461SS E&C is supplied ready for use. Should thinning become necessary, dilute 5% by weight with butyl carbitol acetate...
- 6. If product dries too quickly in the screens, dilute the neat product 5% with butyl carbitol acetate to prolong drying time.

#### **CLEAN-UP**

To clean screen and equipment, use Methylethylketone (MEK), MIBK, Acetone or similar solvents



#### STORAGE:

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

Store in a cool, well ventilated area.

### Optimal Storage: 8 to 28 °C

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

#### Conversions

 $(^{\circ}C \times 1.8) + 32 = ^{\circ}F$  kV/mm x 25.4 = V/mil mm / 25.4 = inches N x 0.225 = lb/F N/mm x 5.71 = lb/in psi x 145 = N/mm² MPa = N/mm² N·m x 8.851 = lb·in N·m x 0.738 = lb·ft N·mm x 0.142 = oz·in mPa·s = cP

Reference 0.3

# **Mouser Electronics**

**Authorized Distributor** 

Click to View Pricing, Inventory, Delivery & Lifecycle Information:

# Loctite:

1224965 1224967