

Technical Data Sheet

LOCTITE EDAG 725A(6S54) E&C

September 2014

PRODUCT DESCRIPTION

LOCTITE EDAG 725A(6S54) E&C provides the following product characteristics:

| Technology | Thermoplastic | |
|-----------------------------------|--|--|
| Appearance | Silver | |
| Filler Type | Silver | |
| Product Benefits | Conductive Low electrical resistance Excellent adhesion No thinning required Process ease Excellent flexibility Good printability Good screen residence time Good shelf life | |
| Cure | Heat cure | |
| Application | Conductive Ink | |
| Operating Temperature- Maximum | 100°C | |
| Typical Assembly Applications | Membrane keyboards, membrane touch switches and Flexible circuits | |

LOCTITE EDAG 725A(6S54) E&C polymer thick film ink is designed for use in the production of low voltage circuitry on polyester film.

TYPICAL PROPERTIES OF UNCURED MATERIAL

| Solids Content (3 hours @ 110°C), % | 60 |
|---|--------|
| Viscosity, Brookfield, mPa·s (cP): | |
| Speed 20 rpm, @ 20°C | 12,500 |
| Density, kg/cm ³ | 2,140 |
| Theoretical coverage, m ² /kg: | |
| @ 10µm dry coating thickness | 11 |
| Shelf Life @ 4 to 8°C, year: | |
| From date of qualification in original seal | 1 |
| Fleek Deint, Ten Cleand Cun Fleek Tester % | 100 |
| Flash Point , Tag Closed Cup Flash Tester, °C | 100 |

TYPICAL SCREEN PRINTING PROCESS

| Emulsion Thickness | |
|---|-----------|
| Solvent resistant emulsion, µm | 10 to 40 |
| Recommended Squeegee | |
| Shore Hardness | 70 to 80 |
| Recommended Screen Type | |
| Monofilament polyester screen, threads/cm | 64 to 80 |
| Stainless steel screen , threads/cm | 68 to 130 |
| Printing Equipment Type | |
| Manual | |
| Semi-automatic | |
| High speed reel-to-reel | |

TYPICAL CURING PERFORMANCE

Recommended Drying Cycle

15 minutes @ 120°C

The above cure profile is a guideline recommendation. Cure conditions (time and temperature) may vary based on customers' experience and their application requirements, as well as customer curing equipment, oven loading and actual oven temperatures.

TYPICAL PROPERTIES OF CURED MATERIAL

Dry Coating on Polyester foil, dried 15 minutes @ 120°C

Physical Properties

| Adhesion , grade | 5B |
|--------------------------------------|----|
| Cohesion test (resistance change), % | <3 |
| | |

Electrical Properties

| Sheet Resistivity @ 25 | m, ohms/sq | ≤0.015 |
|------------------------|------------|--------|
| | | |

GENERAL INFORMATION

For safe handling information on this product, consult the Material Safety Data Sheet, (MSDS).

DIRECTIONS FOR USE

- Mix thoroughly with plastic spatula or mechanical stirrer from bottom of container, careful not to whip air in to the product. Using a plastic spatula will decrease the possibility of introducing plastic grindings from the container sidewalls into the product, which could damage the screen
- 2. Bring product to room temperature prior to use.
- LOCTITE EDAG 725A(6S54) E&C is supplied ready for use. Should thinning become necessary, dilute 1 to 3% by weight with Electrodag[™] DBE.

Clean-up

To clean screen and equipment, use Methylethylketone (MEK) or similar solvents

Storage

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

Optimal Storage : 4 to 8 °C

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.



Not for product specifications

The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on specifications for this product.

Conversions

 $(^{\circ}C x 1.8) + 32 = ^{\circ}F$ kV/mm x 25.4 = V/mil mm / 25.4 = inches N x 0.225 = lb N/mm x 5.71 = lb/in N/mm² x 145 = psi MPa x 145 = psi N·m x 8.851 = lb·in N·m x 0.738 = lb·ft N·m x 0.142 = oz·in mPa·s = cP

Disclaimer

Note:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada, Inc.the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including** warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits. The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. \circledast denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 0.2

Mouser Electronics

Authorized Distributor

Click to View Pricing, Inventory, Delivery & Lifecycle Information:

Loctite:

1239087 1263533