

LOCTITE EDAG 976SS HV E&C

September 2012

PRODUCT DESCRIPTION

LOCTITE EDAG 976SS HV E&C provides the following product characteristics:

Technology	Thermoset Resin
Appearance	Silver
Filler Type	Silver
Product Benefits	<ul style="list-style-type: none"> • Highly conductive • Screen printable • Excellent screen residence time • Very low sheet resistance • Excellent adhesion • Resistant to wave soldering • Solvent resistant
Cure	Heat cure
Application	Conductive Ink
Key Substrates	Phenolic paper, Epoxy paper, Glass epoxy, Copper laminated and Plain substrates
Typical Assembly Applications	Conductive tracks, pads and jumpers and Through-hole printing

LOCTITE EDAG 976SS HV E&C is designed for use in the production of rigid printed circuit boards.

TYPICAL PROPERTIES OF UNCURED MATERIAL

Solids Content, %	78
Viscosity, Brookfield , mPa·s (cP):	
Speed 20 rpm, @ 20°C	30,000
Density, kg/cm³	2,700
Theoretical coverage, m² /kg:	
@ 10µm dry coating thickness	18
Shelf Life @ 4 to 8°C , year:	
From date of qualification in original seal	1
Flash Point , °C	100

TYPICAL SCREEN PRINTING PROCESS

Emulsion Thickness

Direct emulsion when printing conductive jumpers	20 to 40
Capillary film for through-hole metallization	50 to 70

Recommended Squeegee

Polyurethane , Shore Hardness	60 to 75
-------------------------------	----------

Recommended Screen Type

Monofilament polyester & Stainless Steel , threads/cm	40 to 110
---	-----------

Printing Equipment Type

Manual	
Semi-automatic	

TYPICAL CURING PERFORMANCE

Recommended Cure Schedule

Conductive Tracks

Predry 15 minutes @ 70 °C
Cure 30 minutes @ 150 to 160 °C

Infrared curing can also be used successfully

Through Hole Printing

Dry 4 hours @ 70 °C
Cure 30 minutes @ 150 to 160 °C

The above cure profile is a guideline recommendation. Cure conditions (time and temperature) may vary based on customers' experience and their application requirements, as well as customer curing equipment, oven loading and actual oven temperatures.

TYPICAL PROPERTIES OF CURED MATERIAL

Cured as coating on FR4

Physical Properties

Adhesion , grade	5B
------------------	----

Electrical Properties

Sheet Resistivity @ 25µm, ohms/sq	<0.025
Hole Resistivity full hole, ohms	<0.02

GENERAL INFORMATION

For safe handling information on this product, consult the Material Safety Data Sheet, (MSDS).

DIRECTIONS FOR USE

1. Bring product to room temperature prior to use.

2. Mixing/Dilution

- Mix thoroughly with plastic spatula or mechanical stirrer from bottom of container , careful not to whip air in to the product. Using a plastic spatula will decrease the possibility of introducing plastic grindings from the container sidewalls into the product, which could damage the screen.
- Depending on the application, LOCTITE EDAG 976SS HV E&C can be diluted with 1 to 10% by weight with Electrodag™ Diluent 1 ("Carbitrol" acetate).
- Typical dilution ratios for printing conductive tracks is 4% and for printing through hole is 10%.

Clean-up

To clean screen and equipment, use Methylethylketone (MEK), MIBK or similar solvents

Storage

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

Optimal Storage : 4 to 8 °C

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

Not for product specifications

The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on specifications for this product.

Conversions

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$
 $\text{kV/mm} \times 25.4 = \text{V/mil}$
 $\text{mm} / 25.4 = \text{inches}$
 $\text{N} \times 0.225 = \text{lb}$
 $\text{N/mm} \times 5.71 = \text{lb/in}$
 $\text{N/mm}^2 \times 145 = \text{psi}$
 $\text{MPa} = \text{N/mm}^2$
 $\text{MPa} \times 145 = \text{psi}$
 $\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$
 $\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$
 $\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$
 $\text{mPa}\cdot\text{s} = \text{cP}$

Disclaimer**Note:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 0.2

Mouser Electronics

Authorized Distributor

Click to View Pricing, Inventory, Delivery & Lifecycle Information:

[Loctite:](#)

[1395610](#)