



# LOCTITE® SI 5699™

January 2019

**Product description**

LOCTITE® SI 5699™ provides the following product characteristics:

Technology	Silicone
Chemical Type	Oxime silicone
Appearance (uncured)	Grey paste <sup>LMS</sup>
Components	One component - requires no mixing
Thixotropic	Reduced migration of liquid product after application to substrate
Cure	Room temperature vulcanizing (RTV)
Application	Sealing
Specific Benefits	Non-corrosive

LOCTITE® SI 5699™ is designed primarily for flange sealing with excellent oil resistance on rigid flange sealing for example on transmissions and cast metal housings.


**NSF International**

**Registered to NSF Category P1** for use as a sealant where there is no possibility of food contact in and around food processing areas.

**Note:** This is a regional approval. Please contact your local Technical Service Center for more information and clarification.

**Cure speed**


The graph below shows shear strength developed with time on KTL lapshears at a bond gap of 0.5 mm. Cure condition 23±2°C, 60±5% RH. Strength is determined according to ISO 4587.



**Depth cure**

The depth of cure depends on temperature and humidity. Depth of cure was measured on strip pulled from a ramped PTFE mold (maximum depth 10 mm).

The graph below shows the increase in depth of cure with time at 23°C with increase in humidity.



**TYPICAL PROPERTIES OF UNCURED MATERIAL**

Specific Gravity @ 20°C	1.45
Extrusion rate, g/min	
Pressure 0.62 MPa, time 15 seconds, temperature 25°C:	
Semco Cartridge	≥200 <sup>LMS</sup>

Flash Point - See SDS

**TYPICAL CURING PERFORMANCE**

**Surface cure**

Tack Free Time is the time required to achieve a tack free surface	
Tack Free Time, minutes	
Cured @ 25°C / 50±5 % RH	≤30 <sup>LMS</sup>

**TYPICAL PROPERTIES OF CURED MATERIAL**

Cured for 1 week @ 50±5 % RH

**Physical Properties:**

Shore Hardness, ISO 868, Durometer A	45 to 75 <sup>LMS</sup>
Elongation, ISO 37, %	≥100 <sup>LMS</sup>
Tensile strength, ISO 37	N/mm² ≥2.4 <sup>LMS</sup> (psi) (≥348)



Electrical Properties:

Surface Resistivity, IEC 60093, Ω	2×10 <sup>15</sup>
Volume resistivity, IEC 60093, Ω·cm	2×10 <sup>15</sup>
Dielectric Constant / Dissipation Factor, IEC 60250:	
100Hz	2.8
10-kHz	4.0
10-MHz	4.1

TYPICAL PERFORMANCE OF CURED MATERIAL

Adhesive Properties

After 14 days @ 23°C / 60±5% RH and 0.5 mm gap

Lap Shear Strength:

Aluminum	N/mm <sup>2</sup>	0.1 to 0.7
	(psi)	(15 to 102)
Zinc dichromate	N/mm <sup>2</sup>	0.7 to 1.5
	(psi)	(102 to 213)
Mild steel (grit blasted)	N/mm <sup>2</sup>	1.3 to 2.1
	(psi)	(189 to 305)
Aluminum (abraded)	N/mm <sup>2</sup>	1.3 to 2.0
	(psi)	(189 to 290)

TYPICAL ENVIRONMENTAL RESISTANCE


Cured for 14 days @ 23°C / 60±5% RH

Lap shear strength:

Mild steel (grit blasted)


Hot Strength

Tested at temperature




Heat Aging

Aged at temperature indicated and tested @ 23°C.  
2 mm thick samples cured for 14days @ 23°C / 60±5% RH RH



Heat Aging

Aged at temperature indicated and tested @ 22°C.  
2 mm thick samples cured for 14days @ 23°C / 60±5% RH



Chemical/Solvent Resistance

Aged under conditions indicated and tested @ 22°C.

Environment	°C	% of initial strength		
		100 h	500 h	1000 h
Multi-grade	120	95	95	90
Multi-grade	150	80	80	75
ATF (Dextron II oil)	120	70	85	75
ATF (Dextron II oil) - Japanese Grade	150	75	65	35
Water/glycol 50/50	100	85	90	65

GENERAL INFORMATION

This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials.

For safe handling information on this product, consult the Safety Data Sheet (SDS).

NOTE: This product is not recommended for contact with gasoline.



## Directions for use

1. For best performance bond surfaces should be clean and free from grease.
2. Moisture curing begins immediately after the product is exposed to the atmosphere, therefore parts to be assembled should be mated within a few minutes after the product is dispensed.
3. The bond should be allowed to cure (e.g. seven days), before subjecting to heavy service loads.
4. Excess material can be easily wiped away with non-polar solvents, e.g. mineral spirits or naphtha based cleaners.
5. For full automatic applications a volumetric dispensing system is recommended.

## Loctite material specification<sup>LMS</sup>

LMS dated November 29, 1999. Test reports for each batch are available for the indicated properties. LMS test reports include selected QC test parameters considered appropriate to specifications for customer use. Additionally, comprehensive controls are in place to assure product quality and consistency. Special customer specification requirements may be coordinated through Henkel Quality.

## Storage

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

**Optimal storage: 8°C to 21°C. Storage below 8°C or greater than 28°C can adversely affect product properties.**

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Henkel representative.

## Conversions

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$   
 $\text{kV/mm} \times 25.4 = \text{V/mil}$   
 $\text{mm} / 25.4 = \text{inches}$   
 $\mu\text{m} / 25.4 = \text{mil}$   
 $\text{N} \times 0.225 = \text{lb}$   
 $\text{N/mm} \times 5.71 = \text{lb/in}$   
 $\text{N/mm}^2 \times 145 = \text{psi}$   
 $\text{MPa} \times 145 = \text{psi}$   
 $\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$   
 $\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$   
 $\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$   
 $\text{mPa}\cdot\text{s} = \text{cP}$

## Disclaimer

The information provided in this Technical data sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical data sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:**

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

**In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Corporation, or Henkel Canada Corporation, the following disclaimer is applicable:**

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

## Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 1.16

**For the most direct access to local sales and technical support visit: <https://www.henkel-adhesives.com>**

# Mouser Electronics

Authorized Distributor

Click to View Pricing, Inventory, Delivery & Lifecycle Information:

[Loctite:](#)

[2090260](#)