

# LOCTITE STYCAST ES 0614

April 2021

## PRODUCT DESCRIPTION

LOCTITE STYCAST ES 0614 provides the following product characteristics:

<b>Technology</b>	Epoxy
<b>Appearance (cured)</b>	Amber
<b>Components</b>	Two components - requires mixing
<b>Mix Ratio by volume: Part A: Part B</b>	100 : 33
<b>Mixing Ratio, by weight Component A: Component B</b>	100 : 30
<b>Cure</b>	Heat cure
<b>Application</b>	Potting and Encapsulating

LOCTITE STYCAST ES 0614 is an undiluted epoxy, low viscosity casting system that exhibits exceptional resistance to impact and thermal shock. This product is recommended for potting where high impact strength is required, and where rigid or flexible wire leads protrude directly from the encapsulation. This system eliminates microscopic cracking on flexing of leads. It adheres extremely well to lead materials, such as vinyl or neoprene.

## TYPICAL PROPERTIES OF UNCURED MATERIAL

### Part A Properties

Color	Gardner 4
Density, @ 25°C, g/cm <sup>3</sup>	1.15 to 1.17
Viscosity, Brookfield - RVF, 25 °C, mPa·s (cP):	
Spindle 5, speed 10 rpm	10,000 to 16,000

### Part B Properties

Color	Gardner 3
Density, @ 25°C, g/cm <sup>3</sup>	1.0 to 1.02
Viscosity, Brookfield - RVF, 25 °C, mPa·s (cP):	
Spindle 1, speed 20 rpm	14 to 25

### Mixed Properties

Pot Life @ 25°C, minutes:	
200 g mass	35
Peak Exotherm Temperature, °C:	
200 g mass	190
Viscosity @ 25 °C, mPa·s (cP)	600

## TYPICAL CURING PERFORMANCE Recommended Curing Conditions

3 hours @ 60 °C (Recommended cure)  
24 hours @ 22°C (Alternate cure)

## TYPICAL PROPERTIES OF CURED MATERIAL

### Physical Properties :

Coefficient of Thermal Expansion ASTM D7012, K <sup>-1</sup> :	
Pre Tg (Alpha 1)	54×10 <sup>-6</sup>
Post Tg (Alpha 2)	105×10 <sup>-6</sup>
Coefficient of Thermal Conductivity, ASTM C177, W/mK	0.209
Shore Hardness, ISO 868, Durometer D	75 to 80
Linear Shrinkage, ASTM D792, %	0.6
Heat Deflection Temperature @ 1.8 N/mm <sup>2</sup> , °C	84
Izod Impact Strength, N/mm of notch	0.25
Water Absorption, ISO 62, %:	
24 hours in water @ 25 °C	0.43
Elongation , ISO 527-2,%	4.1
Tensile Strength, ISO 527-2	N/mm <sup>2</sup> 53.8 (psi) (7,800)
Compressive Strength, ISO 604	N/mm <sup>2</sup> 200 (psi) (29,000)
Compressive Yield Strength, ISO 604	N/mm <sup>2</sup> 89.6 (psi) (13,000)
Flexural Strength, ISO 178	N/mm <sup>2</sup> 95.2 (psi) (13,800)

### Electrical Properties:

Dielectric Breakdown Strength IEC 60243-1, kV/mm	70.9
Arc Resistance, ASTM D495, seconds	94
Volume Resistivity, IEC 60093, Ω·cm	4×10 <sup>14</sup>
Dielectric Constant / Dissipation Factor, IEC 60250:	
@ 25 °C:	
100 Hz	4.96 / 0.007
1 kHz	5.0 / 0.008
10 kHz	4.84 / 0.022
100 kHz	4.57 / 0.048
@ 80 °C:	
100 Hz	5.6 / 0.029
1 kHz	5.6 / 0.012
10 kHz	5.17 / 0.014
100 kHz	4.92 / 0.027

## GENERAL INFORMATION

**For safe handling information on this product, consult the Safety Data Sheet, (SDS).**

### Not for product specifications

The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on specifications for this product.

### Storage

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

**Optimal Storage: 20 °C to 30 °C. Storage below 20 °C or greater than 30 °C can adversely affect product properties.**

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Henkel Representative.

#### Conversions

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$

$\text{kV/mm} \times 25.4 = \text{V/mil}$

$\text{mm} / 25.4 = \text{inches}$

$\text{N} \times 0.225 = \text{lb/F}$

$\text{N/mm} \times 5.71 = \text{lb/in}$

$\text{psi} \times 145 = \text{N/mm}^2$

$\text{MPa} = \text{N/mm}^2$

$\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$

$\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$

$\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$

$\text{mPa}\cdot\text{s} = \text{cP}$

#### Disclaimer

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

#### **In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:**

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

#### **In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

#### **In case products are delivered by Henkel Corporation, or Henkel Canada Corporation, the following disclaimer is applicable:**

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

#### Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 3

# Mouser Electronics

Authorized Distributor

Click to View Pricing, Inventory, Delivery & Lifecycle Information:

[Loctite:](#)

[2322249](#)