

LOCTITE STYCAST ES 4322

December 2012

PRODUCT DESCRIPTION

LOCTITE STYCAST ES 4322 provides the following product characteristics:

Technology	Epoxy
Appearance, Resin (Component A)	Black
Appearance, Hardener (Component B)	Gray Tan
Components	Two components - requires mixing
Mixing Ratio, by weight Component A: Component B	100 : 100
Product Benefits	<ul style="list-style-type: none">• High purity• High flow• Non-conductive
Cure	Heat cure
Application	Encapsulation
Typical Applications	Encapsulation of bare chips mounted to plastic substrates and Potting of small hybrid circuit modules

LOCTITE STYCAST ES 4322 liquid epoxy encapsulant is for protection of semiconductor devices. It is a high flow material which requires a cavity of flow control barrier to prevent excessive flow.

TYPICAL PROPERTIES OF UNCURED MATERIAL**Part A Properties EA4322**

Viscosity, Brookfield - RVF, 25 °C, mPa·s (cP):

Spindle 7, speed 20 rpm	140,000
Filler Content, ASTM D2584, %	65
Specific Gravity, ASTM D1475	1.68
Shelf Life:	
@ 5°C, months	18
@ 25°C, year	1
Flash Point - See SDS	

Part B Properties EB4322

Viscosity, Brookfield - RVF, 25 °C, mPa·s (cP):

Spindle 7, speed 20 rpm	17,000
Filler Content, ASTM D2584, %	65
Specific Gravity, ASTM D1475	1.68
Shelf Life:	
@ 5°C, months	18
@ 25°C, year	1
Flash Point - See SDS	

Mixed Properties LOCTITE STYCAST ES 4322

Mixed Viscosity @ 25 °C, mPa·s (cP):

Spindle 7, speed 20 rpm	50,000
Gel Time @ 121 °C, minutes	11
Pot Life @ 25°C, min day**	1

** Time to double in Viscosity

TYPICAL CURING PERFORMANCE**Recommended Cure Schedule**

2 to 3 hours @ 170°C or
3 to 6 @ 150°C

Alternate Cure Schedule

1 hour @ 125°C plus 4 hours @ 150°C

Curing below 140°C is not recommended.

Key material properties are affected by cure conditions, including: glass transition temperature, adhesion, modulus, moisture absorption, and chemical resistance. These properties generally improve with longer cure time due to increased cross link density. Cure time of 3 to 6 hours may be required for severe environmental conditions.

The above cure profile is a guideline recommendation. Cure conditions (time and temperature) may vary based on customers' experience and their application requirements, as well as customer curing equipment, oven loading and actual oven temperatures.

TYPICAL PROPERTIES OF CURED MATERIAL**Physical Properties :**

Appearance	Black
Coefficient of Linear Thermal Expansion:	
Below Tg, ppm/°C	26
Above Tg, ppm/°C	88
Glass Transition Temperature (Tg) by TMA, °C	175
Shore Hardness, ASTM D2240 Shore D	97
Linear Shrinkage, ASTM D2566,, %	0.43
Moisture Absorption, ASTM D570, %:	
8 hours immersion @ 100°C	0.25
Extractable Ionic Content, :	
Chloride (Cl-)	7
Sodium (Na+)	2
Potassium (K+)	1

Electrical Properties:

Volume Resistivity, ASTM D257ohm-cm	6.2×10^{14}
Surface Resistivity, ASTM D257, ohms	1.6×10^{14}
Dissipation Factor, (D), ASTM D150:	
1 KHz	0.005
10 KHz	0.006
100 KHz	0.011
Dielectric Constant , (K), ASTM D150:	
1 KHz	3.18
10 KHz	3.15
100 KHz	3.04

STORAGE:

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

Optimal Storage : 5 °C

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

Not for product specifications

The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on specifications for this product.

Conversions

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$
 $\text{kV/mm} \times 25.4 = \text{V/mil}$
 $\text{mm} / 25.4 = \text{inches}$
 $\text{N} \times 0.225 = \text{lb}$
 $\text{N/mm} \times 5.71 = \text{lb/in}$
 $\text{psi} \times 145 = \text{N/mm}^2$
 $\text{MPa} = \text{N/mm}^2$
 $\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$
 $\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$
 $\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$
 $\text{mPa}\cdot\text{s} = \text{cP}$

GENERAL INFORMATION

For safe handling information on this product, consult the Safety Data Sheet, (SDS).

DIRECTIONS FOR USE

1. LOCTITE STYCAST ES 4322 may settle upon storage at room temperature.
2. Cold storage @ 5°C will minimize filler settling.
3. Each container must be thoroughly mixed before combining Part A and Part B. After warming to room temperature, approximately 5 to 10 minutes on a standard paint shaker will normally ensure complete dispersion of the filler.
4. Stir with a large spatula to check for lumps.
5. Part B may form a crust if exposed to moist air for an extended period of time. Keep in a well sealed container. For best results, do not use Part B which contains this crust caused by moisture contamination.
6. Thorough mechanical mixing of Part A and Part B together is required for best results. Hand mixing alone is not recommended.

Disclaimer

Note:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage: [Except as otherwise noted] All trademarks in this document are trademarks and/or registered trademarks of Henkel and its affiliates in the U.S. and elsewhere.

Reference 1

Mouser Electronics

Authorized Distributor

Click to View Pricing, Inventory, Delivery & Lifecycle Information:

[Loctite:](#)

[530908](#) [530909](#)