

# LOCTITE STYCAST PC 40-UM

September 2012

## PRODUCT DESCRIPTION

LOCTITE STYCAST PC 40-UM provides the following product characteristics:

<b>Technology</b>	Urethane Acrylate
<b>Appearance</b>	Clear liquid
<b>Color</b>	Gardener 1
<b>Cure</b>	Ultraviolet (UV) light activation followed by room temperature moisture cure
<b>Application</b>	Conformal coating

LOCTITE STYCAST PC 40-UM is a single component, VOC free conformal coating. This product is specifically formulated to rapidly gel and immobilise when exposed to U.V. light, and then cure when exposed to atmospheric moisture, thus ensuring optimum performance even in shadowed areas. Thin layer coatings can be gelled, almost instantly, to a depth of 7 mils. LOCTITE STYCAST PC 40-UM fluoresces intensely with black light and exhibits excellent adhesion to a variety of metal, ceramic, and glass filled epoxy surfaces fulfilling the needs of the most demanding environmentally friendly applications in today's PCB marketplace.

## UL Classification

LOCTITE STYCAST PC 40-UM is listed in UL's recognized component index with 94V-0 flammability rating in 1.6mm thickness cross section, File No. E328327.

## TYPICAL PROPERTIES OF UNCURED MATERIAL

### Typical Properties of Liquid Material

Specific Gravity @ 25°C	1.07
Nominal Viscosity @ 25°C, cps	500

## TYPICAL CURING PERFORMANCE Recommended Curing Conditions

UV activated in 30 seconds @ 300 - 600 mW/cm<sup>2</sup>

Moisture cure for shadow areas on a populated board: 2 to 3 days @ RT for secondary cure.

## TYPICAL PROPERTIES OF CURED MATERIAL

### Physical Properties :

Hardness, Shore D	80
Continuous Operating Range, °C	-40 to 135
Flammability, 1.6mm, 94V-0	Passes

### Electrical Properties:

Dielectric Constant @ 25°C : 1 MHz	2.75 / 0.012
---------------------------------------	--------------

Volume Resistivity, ohm-cm	3.5×10 <sup>16</sup>
Surface Resistivity, ohms	3.8×10 <sup>16</sup>

## GENERAL INFORMATION

**For safe handling information on this product, consult the Safety Data Sheet, (SDS).**

### Not for product specifications

The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on specifications for this product.

Any tank should be pressurized with dry nitrogen.

Note: Do not use AC0305 to dilute with LOCTITE STYCAST PC 40-UM. Xylene is the preferred diluent. Do not use alcohols to clean equipment or dilute LOCTITE STYCAST PC 40-UM as this will advance the product.

### STORAGE:

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

**Storage between 20 and 30°C out of sunlight and in original unopened containers. Refer to packaging specific quote for shelf life information.** Once opened, containers should be purged with dry nitrogen.

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

**Conversions**

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$   
 $\text{kV/mm} \times 25.4 = \text{V/mil}$   
 $\text{mm} / 25.4 = \text{inches}$   
 $\text{N} \times 0.225 = \text{lb/F}$   
 $\text{N/mm} \times 5.71 = \text{lb/in}$   
 $\text{psi} \times 145 = \text{N/mm}^2$   
 $\text{MPa} = \text{N/mm}^2$   
 $\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$   
 $\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$   
 $\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$   
 $\text{mPa}\cdot\text{s} = \text{cP}$

**Disclaimer****Note:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:**

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

**In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada, Inc. the following disclaimer is applicable:**

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose

methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

**Trademark usage**

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

## Reference 1

# Mouser Electronics

Authorized Distributor

Click to View Pricing, Inventory, Delivery & Lifecycle Information:

[Loctite:](#)

[1162863](#) [1162864](#)