

LOCTITE STYCAST 2851FT

October 2015

PRODUCT DESCRIPTION

LOCTITE STYCAST 2851FT provides the following product characteristics:

Technology	Epoxy
Appearance	Black
Cure	Heat cure
Product Benefits	<ul style="list-style-type: none"> One component Solvent-free 100% Solids Low temperature cure High thermal conductivity Low thermal expansion
Operating Temperature	170°C
Application	Encapsulant

LOCTITE STYCAST 2851FT is recommended for encapsulation of components that require heat dissipation and thermal shock properties. It has a low coefficient of thermal expansion and exhibits excellent resistance to a wide variety of industrial chemicals and solvents.

TYPICAL PROPERTIES OF UNCURED MATERIAL

Viscosity, mPa·s (cP):

@ 25°C	85,000
@ °C	33,000

Density, g/cm³ 2.3

Shelf Life @ 0 to 8°C (from date of manufacture), days 180

Flash Point - See SDS

TYPICAL CURING PERFORMANCE

Cure Schedule

- 1 hour @ 120°C
- 2 hours @ 110°C
- 5 hours @ 90°C

Cure at any one of the recommended cure schedules.

For optimum smooth surface, cure temperature should not exceed 110°C.

A post cure of 4 hours @ 150°C will improve final end-properties.

The above cure profiles are guideline recommendations. Cure conditions (time and temperature) may vary based on customers' experience and their application requirements, as well as customer curing equipment, oven loading and actual oven temperatures.

TYPICAL PROPERTIES OF CURED MATERIAL

Physical Properties

Hardness, Shore D, Minimum	90
Thermal Conductivity, W/(m·K)	1.36
Coefficient of Linear Thermal Expansion, ppm/°C	31
Moisture Absorption, 24 hrs immersion, %	0.06
Machinability	Poor (must be ground)
Heat Distortion Temperature, °C	102
Arc Resistance, seconds	207

Electrical Properties

Volume Resistivity @ 25 °C, ohm-cm	1×10 ¹⁵
Dielectric Constant / Dissipation Factor @ 1 MHz	5.2/0.02

TYPICAL PERFORMANCE OF CURED MATERIAL

Miscellaneous

Impact Strength, J/cm	0.16
Compressive Strength	N/mm ² 130 (psi) (18,855)
Flexural Strength	N/mm ² 93 (psi) (13,488)
Tensile Strength	N/mm ² 50 (psi) (7,250)

GENERAL INFORMATION

For safe handling information on this product, consult the Material Safety Data Sheet, (MSDS).

DIRECTIONS FOR USE

- For applications requiring a lower viscosity, very slight warming will reduce viscosity significantly (e.g., to 45°C).
- Do not leave the material at a warm temperature any longer than necessary as it will shorten its shelf life considerably.
- Mix the entire contents of to a uniform consistency before removing material.
- Power mixing is preferred.
- In the event that release from the mold is desired, a coating of paste wax or a silicone mold release such as MOLD RELEASE 122S is recommended.

Storage

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

Optimal Storage : 0 to 8 °C

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

Conversions

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$
 $\text{kV/mm} \times 25.4 = \text{V/mil}$
 $\text{mm} / 25.4 = \text{inches}$
 $\text{N} \times 0.225 = \text{lb}$
 $\text{N/mm} \times 5.71 = \text{lb/in}$
 $\text{N/mm}^2 \times 145 = \text{psi}$
 $\text{MPa} = \text{N/mm}^2$
 $\text{MPa} \times 145 = \text{psi}$
 $\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$
 $\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$
 $\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$
 $\text{mPa}\cdot\text{s} = \text{cP}$

Reference 0.0

Disclaimer**Note:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Americas
+1.888.943.6535

Europe
+32.1457.5611

Asia
+86.21.3898.4800

For the most direct access to local sales and technical support visit: www.henkel.com/electronics

Mouser Electronics

Authorized Distributor

Click to View Pricing, Inventory, Delivery & Lifecycle Information:

Loctite:

[1188140](#) [1188141](#)