

# LOCTITE STYCAST EE 4215/HD 3561

June 2018

## PRODUCT DESCRIPTION

LOCTITE STYCAST EE 4215/HD 3561 provides the following product characteristics:

<b>Technology</b>	Epoxy
<b>Appearance (cured)</b>	Black
<b>Components</b>	Two components - requires mixing
<b>Mix Ratio, by volume - Part A: Part B</b>	100 : 24
<b>Mix Ratio, by weight - Part A: Part B</b>	100 : 15
<b>Product Benefits</b>	<ul style="list-style-type: none"> <li>Improved thermal conductivity</li> <li>Heat resistant</li> <li>Thermal shock resistant</li> </ul>
<b>Cure</b>	Heat cure
<b>Application</b>	Potting and Encapsulating

LOCTITE STYCAST EE 4215/HD 3561 is a filled system recommended for potting applications where rigid or flexible wire leads protrude directly from the encapsulation and where high impact strength is required. This system eliminates microscopic cracking on flexing of leads. It adheres extremely well to lead materials, such as vinyl or neoprene.

## TYPICAL PROPERTIES OF UNCURED MATERIAL

### Part A Properties LOCTITE STYCAST EE4215

Color	Black
Filler Content, %	50
Density, @ 25 °C, g/cm <sup>3</sup>	1.6
Viscosity, Brookfield - RVF, 25 °C, cP:	
Spindle 6, speed 10 rpm	80,000

### Part B Properties HD3561

Color, maximum	Gardner 3
Density, @ 25 °C, g/cm <sup>3</sup>	1.0
Viscosity, Brookfield - RVF, 25 °C, cP:	
Spindle 1, speed 20 rpm	20

### Mixed Properties

Viscosity @ 25 °C, cP	2,000
Pot Life, 200 gm mass, @ 25 °C, minutes	80
Peak Exotherm Temperature, 200 gram mass, °C	115

## TYPICAL CURING PERFORMANCE

### Recommended Cure Schedule

3 hours @ 60°C

### Alternative Cure Schedule

24 hours @ 22°C

The above cure profiles are guideline recommendations. Cure conditions (time and temperature) may vary based on customers' experience and their application requirements, as well as customer curing equipment, oven loading and actual oven temperatures.

## TYPICAL PROPERTIES OF CURED MATERIAL AS MIXED

### Physical Properties

Coefficient of Thermal Expansion, ppm/°C:	
Pre Tg (Alpha 1)	53
Post Tg (Alpha 2)	119
Coefficient of Thermal Conductivity, W/(m-K)	0.461
Shore Hardness, Durometer D	83
Density, @ 25 °C, g/cm <sup>3</sup>	1.5
Linear Shrinkage, %	0.5
Heat Deflection Temperature @ 1.8 N/mm <sup>2</sup> , °C	85
Izod Impact Strength, N/mm of notch	0.08
24 Hour Water Moisture Absorption, %	0.21
Specific Gravity @ 25 °C	1.5
Tensile Elongation, %	2.2

### Electrical Properties

Dielectric Strength, 10 mil thickness, volts/mil	1,500
Arc Resistance, seconds	138
Volume Resistivity, ohm-cm :	
@ 25°C	4×10 <sup>14</sup>
@ 80°C	2×10 <sup>10</sup>
Dielectric Constant / Dissipation Factor @ 25°C:	
100 Hz	4.51 / 0.01
1 kHz	4.5 / 0.086
10 kHz	4.41 / 0.017
100 kHz	4.21 / 0.027
Dielectric Constant / Dissipation Factor @ 80°C:	
100 Hz	6.92 / 0.021
1 kHz	6.1 / 0.007
10 kHz	5.58 / 0.046
100 kHz	5.27 / 0.03

## TYPICAL CURED PERFORMANCE AS MIXED

All measurements are taken at 25°C, unless otherwise noted.

### Miscellaneous

Tensile Strength	N/mm <sup>2</sup>	58
	(psi)	(8,500)
Compressive Strength	N/mm <sup>2</sup>	155
	(psi)	(22,500)
Compressive Yield Strength	N/mm <sup>2</sup>	104
	(psi)	(15,200)
Flexural Strength	N/mm <sup>2</sup>	106
	(psi)	(15,500)

## GENERAL INFORMATION

For safe handling information on this product, consult the Safety Data Sheet, (SDS).

**Not for product specifications**

The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on specifications for this product.

**Note:** Before using this product please purge approximately 30 ml. of material prior to application. Discard purged material in accordance with the Material Safety Data Sheet. A video instruction is available upon request.

**DIRECTIONS FOR USE**

LOCTITE STYCAST EE 4215 may crystallize during prolonged storage, if stored below 10°C. If crystallization does occur, warm the contents of the shipping container to 50 to 60°C until all crystals have dissolved. Shipping container must be loosely covered during the warming stage to prevent any pressure build-up.

**STORAGE:**

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

**Liquid Storage - Liquids should be stored at 25°C or below, in closed containers. If stored below 25°C, the material MUST be allowed to come to room temperature, in the sealed container, to avoid moisture contamination.**

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

**Conversions**

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$   
 $\text{kV/mm} \times 25.4 = \text{V/mil}$   
 $\text{mm} / 25.4 = \text{inches}$   
 $\text{N} \times 0.225 = \text{lb}$   
 $\text{N/mm} \times 5.71 = \text{lb/in}$   
 $\text{psi} \times 145 = \text{N/mm}^2$   
 $\text{MPa} = \text{N/mm}^2$   
 $\text{N} \cdot \text{m} \times 8.851 = \text{lb} \cdot \text{in}$   
 $\text{N} \cdot \text{m} \times 0.738 = \text{lb} \cdot \text{ft}$   
 $\text{N} \cdot \text{mm} \times 0.142 = \text{oz} \cdot \text{in}$   
 $\text{mPa} \cdot \text{s} = \text{cP}$

**Disclaimer****Note:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:**

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

**In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada Corporation, the following disclaimer is applicable:**

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

**Trademark usage:** [Except as otherwise noted] All trademarks in this document are trademarks and/or registered trademarks of Henkel and its affiliates in the U.S. and elsewhere.

Reference 2

# Mouser Electronics

Authorized Distributor

Click to View Pricing, Inventory, Delivery & Lifecycle Information:

Loctite:

[397690](#) [498949](#) [498162](#) [2218355](#) [646706](#)