

# LOCTITE STYCAST US 5000

August 2017

## PRODUCT DESCRIPTION

LOCTITE STYCAST US 5000 provides the following product characteristics:

<b>Technology</b>	Urethane
<b>Technology (Part A)</b>	Isocyanate
<b>Technology (Part B)</b>	Polyol
Appearance - Part A	Dark brown liquid
Appearance - Part B	Black liquid
Appearance (cured)	Black
Mix Ratio by weight: Part A: Part B	100 : 11.8
Mix Ratio by volume, Part A:Part B	6.1 : 1
<b>Cure</b>	Two component cure after mixing
Product Benefits	<ul style="list-style-type: none"> <li>• Flexible</li> <li>• Slightly thixotropic</li> <li>• Room temperature cure</li> <li>• Fast gel time</li> </ul>
<b>Application</b>	Encapsulant

LOCTITE STYCAST US 5000 encapsulant is designed for high throughput assembly operations. This material is suitable for potting stress sensitive components.

## TYPICAL PROPERTIES OF UNCURED MATERIAL

### Part A Properties (Isocyanate)

Viscosity, , mPa·s (cP):	
Spindle 5, speed 2.5 rpm	47,040
Spindle 5, speed 20 rpm	15,720
Shelf Life @ 25°C (from date of manufacture), days	180
Flash Point, Tag Closed Cup Flash Tester, °C	>110

### Part B Properties (Polyol)

Viscosity, @ 25 °C, mPa·s (cP)	80
Shelf Life @ 25°C (from date of manufacture), days	180
Flash Point, Tag Closed Cup Flash Tester, °C	>200

### Mixed Properties

Initial Mixed Viscosity, 200 gram mass, mPa·s (cP):	
Spindle 6, speed 20 rpm	10,250
Specific Gravity	1.64

## TYPICAL CURING PERFORMANCE

### Gel Time

Gel Time, 200 gram mass @ 25 °C, minutes	50
--	----

### Recommended Cure Schedule

24 hours @ 25°C

### Alternate Cure Schedule

4 hours @ 49°C

The above cure profiles are guideline recommendations. Cure conditions (time and temperature) may vary based on customers' experience and their application requirements, as well as customer curing equipment, oven loading and actual oven temperatures.

## TYPICAL PROPERTIES OF CURED MATERIAL

### Physical Properties

Hardness:	
Shore A	89
Shore D	41
Thermal Conductivity, cal/cm.sec.°C	11.5×10 <sup>-4</sup>

### Electrical Properties

Volume Resistivity, ohm-cm	2.7×10 <sup>12</sup>
Dielectric Constant/ Dissipation Factor:	
@ 25 °C:	
@ 100 Hz	10.1/0.15
@ 1 KHz	8.5/0.12
@ 10 KHz	7.2/0.09
@ 100 KHz	6.4/0.08
@ 85°C:	
@ 1 KHz	10.6/0.3
@ 10 KHz	9.5/0.07
@ 100 KHz	8.8/0.07
@ 120°C:	
@ 1 KHz	13.2/0.6
@ 10 KHz	9.0/0.1
@ 100 KHz	8.7/0.04

## GENERAL INFORMATION

For safe handling information on this product, consult the Safety Data Sheet, (SDS).

**DIRECTIONS FOR USE**

1. Pre-mix Isocyanate and pre-mix Polyol separately.
2. Weigh the above ratio of Isocyanate and Polyol into a clear container, and mix until a uniform color.
3. Pour mixture into another clean container, and mix for 30 seconds, then use.
4. Use low speed mixing to reduce air entrapment. If air bubbles persist, place unit under vacuum.
5. Cure mixture according to the above cycle. Cure time is measured after the product reaches curing temperature.

**STORAGE:**

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

**Optimal Storage : 25 °C**

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

**Conversions**

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$   
 $\text{kV/mm} \times 25.4 = \text{V/mil}$   
 $\text{mm} / 25.4 = \text{inches}$   
 $\text{N} \times 0.225 = \text{lb}$   
 $\text{N/mm} \times 5.71 = \text{lb/in}$   
 $\text{psi} \times 145 = \text{N/mm}^2$   
 $\text{MPa} = \text{N/mm}^2$   
 $\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$   
 $\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$   
 $\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$   
 $\text{mPa}\cdot\text{s} = \text{cP}$

**Disclaimer****Note:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:**

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

**In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada Corporation, the following disclaimer is applicable:**

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

**Trademark usage:** [Except as otherwise noted] All trademarks in this document are trademarks and/or registered trademarks of Henkel and its affiliates in the U.S. and elsewhere.

**Reference 1**

# Mouser Electronics

Authorized Distributor

Click to View Pricing, Inventory, Delivery & Lifecycle Information:

Loctite:

[235646](#) [2264264](#) [236039](#)