

LOCTITE TCP 7000

February 2017

PRODUCT DESCRIPTION

LOCTITE TCP 7000 provides the following product characteristics:

Technology	Phase Change Thermal Interface
Appearance	Gray
Application Method	Stencil or Screen print
Operating Temperature Range	up to 150°C
Typical Assembly Applications	Microprocessors, GPUs, Multichip modules, ASICs, IGBT, FBDIMM/Memory, Lidded processor applications and Active heat sinks in electronic applications
Application	Thermal management

LOCTITE TCP 7000 is a non-silicone and reworkable phase change material designed for use between heat generating devices and the surfaces to which they are mounted or other heat dissipating surfaces. This material offers the benefits of a phase change material by providing no pump out, dry out or silicone migration along with the enhanced performance, reliability and application ease of thermal grease.

LOCTITE TCP 7000 is supplied in cartridges. Other packaging formats are available upon request.

LOCTITE TCP 7000 has been formulated for stencil printing and not for inline dispense processes.

TYPICAL PROPERTIES

Specific Gravity, gm/cc	2
Storage Life @ 2 to 8°C, days	365
Flash Point - See SDS	

TYPICAL DRYING PERFORMANCE**Recommended Drying Conditions**

@ 0.051 mm Thickness:

30 hours @ 22°C or
22 minutes @ 60°C or
3 minutes @ 125°C

@ 0.152 mm Thickness:

50 hours @ 22°C or
50 minutes @ 60°C or
4.5 minutes @ 125°C

@ 0.254 mm Thickness:

65 hours @ 22°C or
65 minutes @ 60°C or
8 minutes @ 125°C

The above drying profile is a guideline recommendation. Conditions (time and temperature) may vary based on customers' experience and their application requirements, as well as customer drying equipment, oven loading and actual oven temperatures.

TYPICAL PROPERTIES OF DRIED MATERIAL**Physical Properties**

Phase Change Temperature, DSC, °C	45
Thermal Conductivity, ASTM D5470, W/(m-K)	>3.0

GENERAL INFORMATION

For safe handling information on this product, consult the Safety Data Sheet, (SDS).

DIRECTIONS FOR USE

1. Once the compound is applied, it will dry to a solid phase change material. Drying is required for optimal thermal performance.
2. The material flows at the phase change temperature and conforms to the surface features of the heat sink and component.
3. Upon flow, air is expelled from the interface, reducing thermal impedance and the material performs as a highly efficient thermal transfer material.

Application:**Printing**

1. Some bubbles may be present in the cartridge containing the material.
2. Place material onto the screen. With the substrate under the screen, draw the material down, applying the material onto the substrate.
3. Allow the material to dry per drying conditions listed on the TDS.
4. Recommended maximum thickness is 10 mils (254 µm) to ensure complete drying under normal conditions.

STORAGE:

Store product in the unopened container in a cool dry well ventilated area. Storage information may be indicated on the product container labeling.

Optimal Storage : 2 to 8 °C

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

Not for product specifications

The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on specifications for this product.

Conversions

$$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$$

$$\text{kV/mm} \times 25.4 = \text{V/mil}$$

$$\text{mm} / 25.4 = \text{inches}$$

$$\text{N} \times 0.225 = \text{lb}$$

$$\text{N/mm} \times 5.71 = \text{lb/in}$$

$$\text{psi} \times 145 = \text{N/mm}^2$$

$$\text{MPa} = \text{N/mm}^2$$

$$\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$$

$$\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$$

$$\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$$

$$\text{mPa}\cdot\text{s} = \text{cP}$$

Reference 0.2

Trademark usage: [Except as otherwise noted] All trademarks in this document are trademarks and/or registered trademarks of Henkel and its affiliates in the U.S. and elsewhere.

Disclaimer**Note:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Mouser Electronics

Authorized Distributor

Click to View Pricing, Inventory, Delivery & Lifecycle Information:

[Loctite:](#)

[2046437](#)