

PRODUCT DESCRIPTION

Laird Tputty™ 508 is a single part dispensable material designed with automation and vertical stability in mind. Laird has leveraged its knowledge of thermally conductive fillers and resin systems to develop a single part dispensable that demonstrates reliability in a variety of application orientations.

Tputty™ 508 is ideal for applications that can benefit from automation, and allows minimization of SKUs in applications with gap variability. In addition to providing application flexibility and variable gap adaptation, Tputty™ 508 will exert minimum stress on your component while maintaining interface contact to maximize thermal transfer. Combined with Laird's global technical support and global footprint, deploying Tputty™ 508 is easier than ever.

FEATURES AND BENEFITS

- RoHS Compliant
- Complete Dispensing Solution Options Available
- 3.7 W/mK
- Demonstrated thermal cycling stability
- Low outgassing per ASTM E595
- Available in cartridges (75cc, 180cc, 360cc, 600cc) and pails (1 gallon and 5 gallon)

Packaging Size	Fill Volume	Fill Weight
75cc (2.5 oz)	56cc	177g
180cc (6 oz)	159cc	503g
360cc (12 oz)	326cc	1030g
600cc (20 oz)	601cc	1900g
1 gallon	4110cc	13kg
5 gallon	6320cc	20kg

SPECIFICATIONS

PROPERTY	TYPICAL VALUE	METHOD
Construction	Ceramic filled silicone dispensable	N/A
Color	Green	Visual
Thermal Conductivity (w/mK)	3.7	Hot Disk
Flow Rate (75cc taper tip, 0.125" orifice, 40 psi)	50 g/min	Laird Test Method – A16724-00
Density (g/cc)	3.2	Helium Pycnometer
Flammability	V-0	UL 94
Temperature Range	-40 to 150°C	Laird Test Method
Outgassing TML (weight %)	0.04	ASTM E595
Outgassing CVM (weight %)	0.01	ASTM E595
Dielectric Breakdown	>3000 VAC	ASTM D149
Dielectric Constant @ 1MHz	8.62	ASTM D150
Minimum Bond line Thickness	0.09 mm (0.0036")	Laird Test Method -A16112-00
Volume Resistivity (ohm-cm)	10 ¹³	ASTM D257

Americas: +1.866.928.8181
Europe: +44.(0).8031.2460.0
Asia: +86.755.2714.1166

www.lairdtech.com

A17223-00 Tputty 508 DS_053017

Any information furnished by Laird Technologies, Inc. and its agents is believed to be accurate and reliable. All specifications are subject to change without notice. Responsibility for the use and application of Laird Technologies materials rests with the end user. Laird Technologies makes no warranties as to the fitness, merchantability, suitability or non-infringement of any Laird Technologies materials or products for any specific or general uses. Laird Technologies shall not be liable for incidental or consequential damages of any kind. All Laird Technologies products are sold pursuant to the Laird Technologies' Terms and Conditions of sale in effect from time to time, a copy of which will be furnished upon request. © Copyright 2013 Laird Technologies, Inc. All Rights Reserved. Laird, Laird Technologies, the Laird Technologies Logo, and other marks are trademarks or registered trademarks of Laird Technologies, Inc. or an affiliate company thereof. Other product or service names may be the property of third parties. Nothing herein provides a license under any Laird Technologies or any third party intellectual property rights.

Mouser Electronics

Authorized Distributor

Click to View Pricing, Inventory, Delivery & Lifecycle Information:

[Laird Performance Materials:](#)

[A17169-03](#)