



**\*Ready for 5G**

### SOFT AND LOW ABRASION GAP FILLER

Tputty<sup>™</sup> 403 is a single-part, silicone-based thermal gap filler that is soft and low abrasion. Tputty<sup>™</sup> 403 is ideal for applications where large or uneven gap tolerances are present. The soft and compliant nature of this material allows for the transfer of little to no pressure on mating parts. Tputty<sup>™</sup> 403 provides excellent thermal performance and compliance.

### FEATURES AND BENEFITS

- Soft and Compliant
- 2.3 W/mK
- Low Abrasion
- RoHS Compliant
- Available in cartridges (75cc, 180cc, 360cc, 600cc) and pails (1 gallon and 5 gallon)

Packaging Size	Fill Volume	Fill Weight
<b>75cc (2.5 oz)</b>	56cc	140g
<b>180cc (6 oz)</b>	159cc	395g
<b>360cc (12 oz)</b>	326cc	809g
<b>600cc (20 oz)</b>	601cc	1490g
<b>1 gallon</b>	4030cc	10kg
<b>5 gallon</b>	8070cc	20kg

### SPECIFICATIONS

PROPERTY	TYPICAL VALUE	METHOD
<b>Construction</b>	Single part silicone based dispensable gap filler	N/A
<b>Color</b>	White	Visual
<b>Thermal Conductivity (w/mK)</b>	2.3	Hot Disk
<b>Flow Rate (75cc taper tip, 0.125" orifice, 40 psi)</b>	29 g/min	Laird Test Method – A16724-00
<b>Density (g/cc)</b>	2.48	Helium Pycnometer
<b>Flammability</b>	V-0	UL 94
<b>Temperature Range</b>	-45 to 150°C	Laird Test Method
<b>Outgassing TML (weight %)</b>	0.05	ASTM E595
<b>Outgassing CVCM (weight %)</b>	0.02	ASTM E595
<b>Dielectric Breakdown</b>	>6000 VAC	ASTM D149
<b>Dielectric Constant @ 1MHz</b>	4.9	ASTM D150
<b>Minimum Bond line Thickness</b>	0.05mm (0.002")	Laird Test Method -A16112-00
<b>Volume Resistivity (ohm-cm)</b>	10 <sup>13</sup>	ASTM D257

Americas: +1.866.928.8181  
Europe: +44.(0).8031.2460.0  
Asia: +86.755.2714.1166

[www.lairdtech.com](http://www.lairdtech.com)

A16875-00 Tputty 403 DS 72018

Any information furnished by Laird Technologies, Inc. and its agents is believed to be accurate and reliable. All specifications are subject to change without notice. Responsibility for the use and application of Laird Technologies materials rests with the end user. Laird Technologies makes no warranties as to the fitness, merchantability, suitability or non-infringement of any Laird Technologies materials or products for any specific or general uses. Laird Technologies shall not be liable for incidental or consequential damages of any kind. All Laird Technologies products are sold pursuant to the Laird Technologies' Terms and Conditions of sale in effect from time to time, a copy of which will be furnished upon request. © Copyright 2013 Laird Technologies, Inc. All Rights Reserved. Laird, Laird Technologies, the Laird Technologies Logo, and other marks are trademarks or registered trademarks of Laird Technologies, Inc. or an affiliate company thereof. Other product or service names may be the property of third parties. Nothing herein provides a license under any Laird Technologies or any third party intellectual property rights.

# Mouser Electronics

Authorized Distributor

Click to View Pricing, Inventory, Delivery & Lifecycle Information:

Laird Performance Materials:

[A16872-02](#) [A16872-03](#) [A16872-04](#)