



LOCTITE® EDAG PF 410

November 2024

PRODUCT DESCRIPTION

LOCTITE® EDAG PF 410 provides the following product characteristics:

Technology	Thermoplastic
Appearance	Gray paste
Filler type	Silver
Product benefits	<ul style="list-style-type: none">• Applicable with manual, semi-automatic or high speed reel-to-reel screen printing equipment• Extended screen residence time• Excellent print definition• Non-critical, flexible low temperature drying cycles.• Superior adhesion to polyester film• Good abrasion resistance and hardness• Good conductivity
Operating temperature, °C	120, maximum
Cure	Heat drying
Application	Conductive ink
Typical assembly applications	PET, PI, PEN, paper, copper, ITO, glass

LOCTITE® EDAG PF 410 is a halogen-free, good reliability, conductive silver ink with good flexibility. The resistance level of LOCTITE® EDAG PF 410 typically lies around 16 mOhm/sq/25µm. It can be dried at low temperature, down to 80°C. This ink can further be blended with LOCTITE® EDAG 965SS to adjust resistance levels and make the material more economical. Thanks to good thermal and chemical stability, this product is compatible with high operating temperature, has good adhesion to many substrates, and is compatible with a large range of electrically conductive adhesives for component attach or solderable with low melting Sn42Bi58 solder. LOCTITE® EDAG PF 410 is suitable for screen printing and often used to create flexible circuits, keyboards, membrane switches, medical electrodes or biosensors.

TYPICAL PROPERTIES OF UNDRIED MATERIAL

Solid content, wt%	74
Density, kg/m ³	2,500
Viscosity, Brookfield - RVT, 20°C, after 15 min, mPa·s (cP) Speed 20 rpm	16,000
Theoretical coverage, @ 10µm dry coating thickness, m ² /kg	15
Shelf life @ 5 to 30°C, (from date of qualification in original seal), year	1
Flash point, °C	110

TYPICAL SCREEN PRINTING PROCESS

Printing equipment type

Manual	
Semi-automatic	
High speed reel-to-reel	
Recommended dry coating thickness	
Dry coating thickness, µm	6 to 12
Recommended screen type	
Monofilament polyester screen, mesh/cm	68 to 110
Stainless steel screen, mesh/cm	90 to 154

Recommended squeegee

Polyurethane, durometer	70 to 75
-------------------------	----------

Emulsion thickness

Emulsion thickness, µm	20 to 40
------------------------	----------

TYPICAL DRYING CYCLE

Recommended drying cycle

15 minutes @ 120°C

LOCTITE® EDAG PF 410 can be dried immediately after printing at temperatures between 80 to 140°C. Higher temperatures will yield lower sheet resistance and better mechanical properties.

For high speed production, jet drying, infra-red drying and drying in high speed reel-to-reel equipment can be used.

The above drying profile is a guideline recommendation. Conditions (time and temperature) may vary based on customers' experience and their application requirements, as well as customer drying equipment, oven loading and actual oven temperatures.



TYPICAL PROPERTIES OF THE DRIED MATERIAL**Physical properties**

Adhesion on PET, Cross hatch, ASTM 3359, grade 5B

Electrical properties

Sheet resistance, 4-point probe, Ohm/sq/25µm	0.016
15 min at 120°C	
After 15 min at 90°C	0.022

GENERAL INFORMATION

Please consult the Safety Data Sheet (SDS) for safe handling information of this product.

DIRECTIONS FOR USE**Surface preparation**

- Clean surface thoroughly prior to application.

Mixing/Dilution

- Mix thoroughly before use to ensure the entire ink volume is homogenous. A slow speed propeller may be utilized to mix until product is uniform.
- Should dilution be necessary, use 2-(2-Ethoxyethoxy) ethyl acetate (CAS: 112-15-2). Henkel recommends a maximum of 10 wt%. This should be accomplished by adding solvent at 0.5 wt% intervals until desired viscosity and printability is achieved.

CLEAN UP

The screen and equipment can be cleaned with dilution solvent, or esters (butylacetate, propylacetate, or ethylacetate), or ketones (MEK, Acetone), or similar solvents.

STORAGE

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

Optimal Storage: 5 to 30°C. Storage below 5°C or greater than 30°C can adversely affect product properties.

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Henkel representative.

Not for product specifications

The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on the specifications of this product.

Conversions

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$
 $\text{kV/mm} \times 25.4 = \text{V/mil}$
 $\text{mm} / 25.4 = \text{inches}$
 $\mu\text{m} / 25.4 = \text{mil}$
 $\text{N} \times 0.225 = \text{lb}$
 $\text{N/mm} \times 5.71 = \text{lb/in}$
 $\text{N/mm}^2 \times 145 = \text{psi}$
 $\text{MPa} \times 145 = \text{psi}$
 $\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$
 $\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$
 $\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$
 $\text{mPa}\cdot\text{s} = \text{cP}$

Disclaimer

The information provided in this Technical data sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical data sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.



In case products are delivered by Henkel Corporation, or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 2

For the most direct access to local sales and technical support visit: <https://www.henkel-adhesives.com>