

1086848

https://www.phoenixcontact.com/us/products/1086848

Please be informed that the data shown in this PDF document is generated from our online catalog. Please find the complete data in the user documentation. Our general terms of use for downloads are valid.



Shrink sleeve, Roll, yellow, unmarked, can be labeled with: THERMOMARK E.300 (D)/600 (D), THERMOMARK ROLLMASTER 300/600, THERMOMARK ROLL X1, THERMOMARK ROLL, THERMOMARK ROLL 2.0, THERMOMARK X1.2, cable diameter range: 6.4 ... 12.7 mm, perforated, mounting type: slide-on, Number of individual labels: 1000, text field height: 20 mm, text field width: 30 mm

### Product description

Due to their ladder-style format, the preassembled shrink sleeves in the WMS-2 HF... product family provide a good overview and facilitate quick use. After the printing and applying process, you have the option of shrinking the marked shrink sleeves by applying heat manually and thus fixing them on the cable/wire.

#### Your advantages

- · Permanent and captive identification of single-core wires, wires, cables, pneumatic hoses, and other cylindrical objects
- Ladder style design: For a good overview and to facilitate quick use, the sleeves are preassembled in cut lengths: 15 mm, 30 mm, or 60 mm
- · As an option, the sleeves can be shrunk by applying heat manually to fix the sleeve in position
- · High diameter coverage with a shrink ratio of 2:1
- · Widely used and proven worldwide in the railway industry

#### Commercial data

Item number	1086848
Packing unit	1 pc
Minimum order quantity	1 pc
Sales key	BG14
Product key	BG2216
GTIN	4055626881652
Weight per piece (including packing)	1,113.6 g
Weight per piece (excluding packing)	22.22 g
Customs tariff number	39173200
Country of origin	DK



1086848

https://www.phoenixcontact.com/us/products/1086848

### Technical data

#### Notes

Material information	The specified minimum wire diameter of the shrink sleeve refers to its use as a marking material and does not guarantee any insulation characteristics once shrunk.
	Depending on the processed material batch, as well as the storage and processing conditions, the maximum insertable wire diameter may be reduced.

#### Product properties

Product type	Shrink sleeve
Area of application	Railway industry
Marking	

#### Marking

Number of individual labels	1000
Number of individual labels per row	2
Identification technology	Thermal transfer for rolls

#### **Dimensions**

Width	30 mm
Height	20.9 mm

#### Material specifications

	yellow (RAL 1018)
Material	Polyolefine
Base element material	polyolefine
Shrink rate	2:1
Fire protection for rail vehicles (DIN EN 45545-2) R22	HL 1 - HL 3
Fire protection for rail vehicles (DIN EN 45545-2) R23	HL 1 - HL 3
Fire protection for rail vehicles (DIN EN 45545-2) R24	HL 1 - HL 3
Components	halogen-free
Shrink temperature	> 90 °C

#### Cable/line

External cable diameter	6.4 mm 12.7 mm

### Environmental and real-life conditions

Test for substances that would hinder coating with paint or varnish

Result	Test passed
Test for substances that would hinder coating	g with paint or varnish
Result	Test passed
Specification	EN ISO 1518-1:2023 (following)
Requirements	> 5 N



1086848

https://www.phoenixcontact.com/us/products/1086848

	Test passed
esafilm test	
Specification	DIN EN ISO 2409:2020-12 (following)
Result	Test passed
IV resistance	
Specification	DIN EN ISO 4892-2:2021-11 (following)
Result	Test passed
Test duration	96 h
emperature resistance	
Specification	ANSI/UL 969-2018:03 (following)
Test duration	240 h
Rating 100 °C (121 °C)	Test passed
N	
Vipe resistance of inscriptions  Specification	DIN EN 61010-1 (VDE 0411-01):2020-03
Ореспісацоп	DIN EN 61010-1 (VDE 0411-01):2020-03  DIN EN 62208 (VDE 0660-511):2012-06 (in parts)
Isopropyl [CAS No. 67-63-0]	Test passed
Water + Petroleum ether [CAS No. 64742-82-1]	Test passed
Sodium hydroxide 0.1 mol/l [CAS No. 1310-73-2]	Test passed
Ethanol (99 %) [CAS No. 64-17-5]	Test passed
Specification	ISO 175:2010 (following)
Test duration	168 h
Sodium hydroxide 0.1 mol/l [CAS No. 1310-73-2]	Test passed
Ethanol (99 %) [CAS No. 64-17-5]	Test passed
Diesel [CAS No. 68476-34-6]	Test passed
IRM 901	Test passed
IRM 902	Test passed
esting in a condensation changing climate in the pre	ssence of sulfur dioxide
Specification	EN ISO 22479:2022-06
Result	Test passed
Procedure	Method B
Cycles	2
salt spray test	
Specification	DIN EN 60068-2-11:2000-02
Result	Test passed
Test duration	96 h



1086848

https://www.phoenixcontact.com/us/products/1086848

Ambient temperature (operation)	-30 °C 105 °C
Recommended ambient temperature (storage/transport)	10 °C 25 °C
Recommended humidity (storage/transport)	$45\ \%\\ 55\ \%$ (Storage in a dry and dark place in the original packaging is recommended)
Shelf life	2 years

### Standards and regulations

Wipe resistance	DIN EN 61010-1 (VDE 0411-1)
Standards	
Standards/regulations	EN 45545-2

### Mounting

Mounting type	slide-on
---------------	----------



1086848

https://www.phoenixcontact.com/us/products/1086848

### Classifications

#### **ECLASS**

	ECLASS-13.0	27281102	
	ECLASS-15.0	27281102	
ΕΊ	ETIM		
	ETIM 9.0	EC001530	
U	NSPSC		
	UNSPSC 21.0	39131500	



1086848

https://www.phoenixcontact.com/us/products/1086848

### Environmental product compliance

#### EU RoHS

Le rone	
Fulfills EU RoHS substance requirements	Yes, No exemptions
EU REACH SVHC	
EU REACH SVHC  REACH candidate substance (CAS No.)	No substance above 0.1 wt%

Phoenix Contact 2025 © - all rights reserved https://www.phoenixcontact.com

Phoenix Contact USA 586 Fulling Mill Road Middletown, PA 17057, United States (+717) 944-1300 info@phoenixcon.com